

Plain and Reinforced Concrete Laboratory Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

A carbon copy for the report has been retained in the lab for record.

6987 Dr. Qasim Khan

To: Engr. Jawad Ahmad

Civil Engineer, Watersprint Limited.

Project: Construction Site at House No. 814 - Z Block, DHA Phase-III.

Our Ref. No. CL/CED/ 4624-3 of 3 02/05/2024 Dated:

Your Ref. No. WSL-172/GL Dated: 02/04/2024

Test Specification

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

03/04/2024 Tested on: 02/05/2024 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(met.Tons)	(psi)	on (%)	
1	SIKA GROUT-114	3	4	2024	2x2x2		325	4	20	11020		Non Engraved
2	SIKA GROUT-114	3	4	2024	2x2x2		325	4	18	9918		Non Engraved
3	SIKA GROUT-114	3	4	2024	2x2x2		330	4	14.2	7824		Non Engraved
4												
5						GINE	RINE					
6						READIN	200					
7						OF THY LORD WHO	- C - P - C -	E				
8					%			W				
9							1			-		
10						LA	ORE					
11												
12												
13										-		
14												
15												
16												

Witnessed by: Mr. Kamran Sheikh, Sika Pakistan & Mr. Arsalan Saghir, Water Sprint

- Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/ 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2.The test results are recommended to be interpreted in the light of above factors by the engineer.



Plain and Reinforced Concrete Laboratory Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 7077 Dr. M. Yousaf

To: Sub Divisional Officer

Buildings Sub Division Shahkot

Project: Construction / Rehabilitation / Improvement of Offices etc in ARCs E-Registration Centers, Sub

Registrat Office etc in Punjab (ARC Center One at Tehsil Shahkot District Nankana Sahib.)

Our Ref. No. CL/CED/ 4763 Dated: 02/05/2024

Your Ref. No. 53/SDO/BSD/NNS Dated: 22/03/2024

Test Specification

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 26/04/2024 Tested on: 02/05/2024 in dry/wet condition



Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Rectangular, Grey, 60mm				7.9 x 3.9 x 2.3		2720	30.81	106	7707		
2	Rectangular, Grey, 60mm				7.9 x 3.9 x 2.3		2670	30.81	103	7488		
3	Rectangular, Grey, 60mm				7.9 x 3.9 x 2.3		2740	30.81	103	7488		
4												
5					=	RINE	RINTE					
6						READ IN	2017			-		
7					<u> </u>	THE NAME OF THY LORD WHO	()	3				
8						Juliano						
9												
10						-LA	ORE			-		
11					-		-			-		
12										-		
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



Plain and Reinforced Concrete Laboratory Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

7070 Dr. M. Yousaf

To: Sub Divisional Officer

Building Sub Division Nankana Sahib.

Project: Construction of PHP Post Zafar Ullah District Nankana Sahib. (Main Building Roof Slab of Ground

Floor)

Our Ref. No. CL/CED/ 4764 Dated: 02/05/2024 Test Specification

Your Ref. No. 88/SDO/BSD/NNS Dated: 21/01/2024

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 26/04/2024 Tested on: 02/05/2024 in dry/wet condition



(BS 1881-116)



Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)) (Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	(1:2:4)	22	12	2023	6 x 6 x 6		8.4	36	54	3360		Non Engraved
2	(1:2:4)	22	12	2023	6 x 6 x 6		8.6	36	52	3236		Non Engraved
3												
4												
5						GRE	RINZ					
6						KEAU IN	910					
7						THE NAME OF THY LORD WHO	<u>رئي</u> الدي علم					
8					88	10.000		Ha				
9							-	5 /				
10						LA	ORE					
11												
12					-					1		
13					-					1		
14												
15		-										
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.