

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

1037 Engr. Ubaid

To: Mr. Z.H. Kazmi (Principal Architect)

Z. H. Kazmi & Associates, Lahore. Project: Expansion Works (Construction of New Godowns/ Sheds & Pavements at Allied Bank Limited Warehouse Munirabad

Our Ref. No. CL/CED/	2890	Dated:	26-04-21
Your Ref. No.	Nil	Dated:	08-04-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

09-04-21 Tested on:

22-04-21 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	НН		8.9x4.2x3.0	3142	37.38	40	2400	
2	НН		8.8x4.2x3.0	3078	36.96	41	2490	
3	НН		8.8x4.3x2.9	3068	37.84	43	2550	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website <u>http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6</u>

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

1013 Engr. Ubaid

To: Sub Divisional Officer, (Buildings)

Sub Division Ferozwala Project: Construction of Judicial Academy at Lahore kala Shah Kaku, Lahore, (ADP No. 3271/2020-21) (Group No.2)

Our Ref. No. CL/CED/	2891	Dated:	26-04-21
Your Ref. No.	No.986	Dated:	03-04-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

05-04-21 Tested on:

22-04-21 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	НВ		8.9x4.4x3.0	3283	39.16	53	3040	
2	HB		8.8x4.3x2.9	3138	37.84	37	2190	
3	HB		8.9x4.4x3.0	3312	39.16	37	2120	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer, (Buildings) **Sub Division Ferozwala**

1013

Engr. Ubaid

Project: Construction of Judicial Academy at Lahore kala Shah Kaku, lahore, (ADP No. 3271/2020-21)

Our Ref. No. CL/CED/	2892	Dated:	26-04-21
Your Ref. No.	No.984	Dated:	03-04-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

05-04-21 Tested on: 22-04-21 in dry/wet condition

-								
ġ		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0,		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	12		8.8x4.3x2.1	3383	37.84	30	1780	
2	12		8.8x4.4x3.0	3262	38.72	34	1970	
3	12		8.9x4.4x3.1	3366	39.16	34	1950	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

1013 Engr. Ubaid

To: Sub Divisional Officer, (Buildings)

Sub Division Ferozwala Project: Construction of Judicial Academy at Lahore kala Shah Kaku, lahore, (ADP No. 3271/2020-21) Group-2

Our Ref. No. CL/CED/	2893	Dated:	26-04-21
Your Ref. No.	No.988	Dated:	03-04-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

05-04-21 Tested on:

22-04-21

21 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Н		8.8x4.3x3.0	2786	37.84	39	2310	
2	Н		9.0x4.4x3.0	2869	39.6	33	1870	
3	Н		8.8x4.3x3.0	2983	37.84	25	1480	
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Justin Nawaz (Project Manager ZAHB) M/s Zohra Al-Hayat Builders (Pvt.) Ltd. **Project: Nil**

Our Ref. No. CL/CED/ 2894 Dated: 26-04-21 Your Ref No ZAHB/P1/POR Dated: 12-04-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

Tested on: 16-04-21

26-04-21 in dry/wet condition

1077

Dr Umbreen

		Ocation						
		Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0,		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Fly Ash Brick ZB		8.9x4.3x3.5	3883	38.27	35	2050	
2	Fly Ash Brick ZB		9.0x4.3x3.5	3912	38.7	31	1800	
3	Fly Ash Brick ZB		9.0x4.3x3.5	4224	38.7	37	2150	
4	Fly Ash Brick ZB		9.0x4.3x3.5	4026	38.7	35	2030	
5	Fly Ash Brick ZB		9.0x4.3x3.5	4123	38.7	35	2030	
6	Fly Ash Brick ZH		9.0x4.5x3.1	3860	40.5	41	2270	
7	Fly Ash Brick ZH		9.0x4.5x3.0	3183	40.5	29	1610	
8	Fly Ash Brick ZH		9.0x4.5x3.0	3658	40.5	41	2270	
9	Fly Ash Brick ZH		8.9x4.5x3.0	3553	40.05	39	2190	
10	Fly Ash Brick ZH		9.0x4.5x3.0	3555	40.5	35	1940	
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)