

1736 Dr. Aqsa

To:	Brig. Saeed Ahn NESPAK (Pvt.) L	nad Malik (Resident Engineer) .td. Lahore (Highways &Transportation	Division)						
	Project: Constuction of Secuirty Plan for Ladies and Gents Entry and Exit at Shrine Hazrat Data Gunj Bakhs (RA) Lahore.								
	Our Ref. No. CL	/CED/ 4800	Dated:	27-08-21					
	Your Ref. No.	4084/BSAM/104/453	Dated:	19-06-21					

COMPRESSION TEST REPORT



Test Specification (----)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimo	ens received on:	1	2-08	-21	Tested on:	26-0	08-21	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	S				8.7x4.1x2.8	3459	3120	35.67	79	4961	10.87	
2	S				8.7x4.2x2.9	3595	3255	36.54	76	4659	10.45	
3	S				8.6x4.2x2.9	3491	3160	36.12	78	4837	10.47	
4	S				8.4x4.2x2.8	3404	3080	35.28	79	5016	10.52	
5	S				8.7x4.2x2.8	3442	3120	36.54	84	5149	10.32	
6	S				8.5x4.1x2.9	3374	3055	34.85	82	5271	10.44	
7						DHE NAME OF THY LIDRO VING		F				
8												
9						2		V				
10					- <	-LA	INRE !!					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory

	Plain and Reinforced Co Civil Engineering Dep University of Engineering and Technolo Landline: 042-99029245 & 042-99029202	ncrete Labor partment gy, Lahore. Pakistan Mobile: 0307-049689	atory	ORIGINAL A carbon copy for the report has been retained in the lab for record.
				1789 Dr. Aqsa
To: Deput Sec I&	ty Director, Engg. kⅡ, Package, -I, LOLMTP, LDA , Lahore.			
Proje Proje Our R	ct: Constuction of Bagbhanpura Police Station GT ct (Package-I) ef. No. CL/CED/ 4801	Road Lahore. Lahore Or Dated:	range Line Metro Train 27-08-21	Test Specification

(BS 1881-116)

25-06-21

Dated:

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

DD/PKG-1/LOLMTP/DA/69

Specim	ens received on:	2	5-08	-21	Tested on:	26-0	08-21	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1		28	7	2021	6x6x6		9	36	79	4916		Engraved
2		28	7	2021	6x6x6		9	36	80	4978		Engraved
3		28	7	2021	6x6x6		9.2	36	79	4916		Engraved
4												
5					/	GINE	RIATE					
6					-)	NEAD W						
7						DHE NAME OF THY LORD WHO	4	EB				
8					/ 8.81			IND				
9						2	- 5	—				
10					- <	-14	IORE ?					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

Your Ref. No.

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



Plain and Reinforced Concrete Laboratory Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 1780 Dr. Aqsa

To: **Sub Divisional Officer**

Maintenance Sub Division No-III GOR-II Lahore.

Project: Constuction of Multi-Storey Flats / Suites For Officers of P&D and in GOR-III, Shadman Lahore.

Our Ref. No. CL/CE	D/ 4802	Dated:	27-08-21	Test Specification
Your Ref. No.	No.421	Dated:	21-06-21	(BS 1881-116)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	2	5-08	-21	Tested on:	26-0	08-21	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas	ting MM	Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Ka/ ams)	Area of X-Section (Sg. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(1:2:4)	17	7	2021	6x6x6		8.4	36	81	5040		Engraved
2	(1:2:4)	17	7	2021	6x6x6		8.4	36	82	5102		Engraved
3	(1:2:4)	17	7	2021	6x6x6		8.8	36	81	5040		Engraved
4												
5					/	RINE	RIATE					
6					>	I READ W						
7						DHE NAME OF THY CORD VIND	4	FP				
8					188			IND				
9						à	-					
10					<	-LA	INRE .					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



Plain and Reinforced Concrete Laboratory Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 1780 Dr. Aqsa

To: **Sub Divisional Officer**

Maintenance Sub Division No-III GOR-II Lahore.

Project: Constuction of Multi-Storey Flats / Suites For Officers of P&D and in GOR-III, Shadman Lahore.

Our Ref. No. CL/0	ED/ 4803	Dated:	27-08-21	Test Specification
Your Ref. No.	No.471	Dated:	21-06-21	(BS 1881-116)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	2	5-08	-21	Tested on:	26-0	08-21	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas	ting MM	Date*	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(1:1.5:3)	3	7	2021	6x6x6		9	36	95	5911		Engraved
2	(1:1.5:3)	3	7	2021	6x6x6		8.4	36	108	6720		Engraved
3	(1:1.5:3)	3	7	2021	6x6x6		8.6	36	110	6844		Engraved
4												
5					/	RINE	RIATE					
6					>	T READ W						
7						DHE NAME OFTHY CORD VIND		FF				
8					188			IND				
9						à						
10					<	-LA	INKE .					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



- M/s CMPak Limited.
- To: M/s CMPak Lir Islamabad.

Project: Construction of CMPak Data Center Quaid-e-Azam Insdustrial Estate (KPL)Lahore.

Our Ref. No. CL	/CED/ 4805	Dated:	27-08-21	Test Specification
Your Ref. No.	CMPak/NDC/Cylinder/01	Dated:	03-08-21	(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 09-08-2021.				2021.	Tested on:	12-08-21		in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(1:1.5:3) A1	6	7	2021	6Diax12		13.4	28.28	49	3881		Non Engraved
2	(1:1.5:3) C2	6	7	2021	6Diax12		13.8	28.28	55	4356		Non Engraved
3												
4												
5					1	RINE	RIATE					
6					-	READ W	205 D					
7						DHE NAME OF THY CORD VIND		F				
8					188							
9					I		-					
10					-	-LA	INR E					
11												
12												
13												
14												
15												
16												
Witness	ed by: Usama Ma	ieed	3510)1-132	7513-7							

witnessed by: Usama Majeed 35101-132/513-7

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



FIOJECI. ONIFAN				
Our Ref. No. CL/	CED/ 4806	Dated:	27-08-21	Test Specification
Your Ref. No.	CME/Cubes/CMPAK/719	Dated:	20-08-21	(BS 1881-116)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	2	3-08	-21	Tested on:	26-0)8-21	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	RT Complete Found (1:1.5:3)	13	8	2021	6x6x6		8.2	36	77	4791		Non Engraved
2	RT Complete Found (1:1.5:3)	13	8	2021	6x6x6		8.2	36	73	4542		Non Engraved
3												
4												
5						RINE	RIATE					
6						I READ IN						
7						DHE NHOLE <u>OE</u> THY LORD WHO	14.	EB				
8					4.81			IND				
9						2-	6	7				
10					<	-14	ORE					
11												
12												
13												
14												
15												
16												
Witness	ed hv											

vitnessea by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



Project: CMPAK	Project Site ID: 42942			
Our Ref. No. CL/	'CED/ 4807	Dated:	27-08-21	Test Specification
Your Ref. No.	CME/Cubes/CMPAK/722	Dated:	21-08-21	(BS 1881-116)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	2	3-08	-21	Tested on:	26-0)8-21	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Raft (1:1.5:3)	14	8	2021	6x6x6		8.4	36	69	4293		Non Engraved
2	Raft (1:1.5:3)	14	8	2021	6x6x6		8.2	36	96	5973		Non Engraved
3												
4												
5					/	GINE	RIATE					
6					>	I NEAD W	San C					
7						DHE NARDE COE THY LORD WHE	-4					
8					- 38			IND				
9						×	- 6	7				
10					<	-14	IORE °					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



Project: CMPAK	Project Site ID: 42942			
Our Ref. No. CL/	CED/ 4808	Dated:	27-08-21	Test Specification
Your Ref. No.	CME/Cubes/CMPAK/754	Dated:	22-08-21	(BS 1881-116)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	2	3-08	-21	Tested on:	26-0)8-21	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date*	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Col+ ODU PAD (1:1.5:3)	15	8	2021	6x6x6		8.6	36	113	7031		Non Engraved
2	Col+ ODU PAD (1:1.5:3)	15	8	2021	6x6x6		8.8	36	110	6844		Non Engraved
3												
4												
5					/	RINE	RIATE					
6					>	I READ IN						
7						DHE NHOLE <u>OE</u> THY LORD WHO	14	EB				
8					- SA			IND				
9							-					
10					- <	-14	ORE					
11												
12												
13												
14												
15												
16												
Witness	ed hv:											

illesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



Project: CMPAK	Project Site ID: 43461			
Our Ref. No. CL/	CED/ 4809	Dated:	27-08-21	Test Specification
Your Ref. No.	CME/Cubes/CMPAK/753	Dated:	24-08-21	(BS 1881-116)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	2	3-08	-21	Tested on:	26-0)8-21	in dry/we	t condition			
Sr. No.	Mark*	Cas DD	ting MM	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Col+ODU PAD (1:1.5:3)	17	8	2021	6x6x6		8.4	36	116	7218		Non Engraved
2	Col+ODU PAD (1:1.5:3)	17	8	2021	6x6x6		8.6	36	114	7093		Non Engraved
3												
4												
5					/	RINE	RINE					
6					-)	READ W	ALK N					
7						DHE NAME <u>OE</u> THY LORD WHO	14.4	EB				
8					- ASI			HN0				
9						×	- 6	7				
10					<	-14	ORE					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



Project: CMPAK	Project Site ID: 43461			
Our Ref. No. CL/	CED/ 4810	Dated:	27-08-21	Test Specification
Your Ref. No.	CME/Cubes/CMPAK/752	Dated:	23-08-21	(BS 1881-116)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	2	3-08	-21	Tested on:	26-0)8-21	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate Ioad (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Raft (1:1.5:3)	16	8	2021	6x6x6		8.4	36	127	7902		Non Engraved
2	Raft (1:1.5:3)	16	8	2021	6x6x6		8.2	36	60	3733		Non Engraved
3												
4												
5					/	RINE	RIATE	-				
6					- >	E READ IN						
7						DHE NAME <u> OE</u> THY LORD WHO	14.	EB				
8					- ASI			IND				
9												
10					- <		INRE .					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

illesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



Project: CMPAK	Project Site ID: 53231			
Our Ref. No. CL/	CED/ 4811	Dated:	27-08-21	Test Specification
Your Ref. No.	CME/Cubes/CMPAK/747	Dated:	26-08-21	(BS 1881-116)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	2	3-08	-21	Tested on:	26-0)8-21	in dry/we	t condition			ONLINE REPORT
Sr. No.	r. No. Mark* Casting		asting Date*		Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	ODU PAD (1:1.5:3)	29	7	2021	6x6x6		8.6	36	82	5102		Non Engraved
2	ODU PAD (1:1.5:3)	29	7	2021	6x6x6		8.6	36	93	5787		Non Engraved
3												
4												
5					-	RINE	RIATE	-				
6					-	READIN						
7						DHE NAME OF THY LORD VIND						
8					188							
9					-	-	1					
10					-	(A	INR E .					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

inesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory