C To:	Mr. Mirza M. Arst	ntory ng nore 611 Dr.Mazhar Saleem										
	Project: PEC Bui	lding	g Pi	roject.								
	Our Ref. No. CL/CE	D/		20	008	Dated:	10-0	2-21				
	Your Ref. No.		Ρ	MPPL/I EC/LHR/	Proj (RE/96	Dated:	01-0	2-21				
	COMPRESSION TEST REPORT											
Conc	crete Cubes/Concret	te Cy	lind	lers/Bric	ks/Cores/Tu:	ff Tiles/Pave	ers					
Spec	imens received on:	C)3-0	2-21	Tested on:		04-02-21	in dry/wet c	ondition			
		Ca	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate			
ŝr. No	Mark* /Wet Weight		Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks			
0)		(gms)		ns)			(Sq. in)	(Tons/lbs)	(Psi)			
1	683-1	24	1	2021	6Diax12	14	28.28	51	4040	Engraved		
2	696-1	24	1	2021	6Diax12	13.4	28.28	47	3730	Engraved		
3	693-1	24	1	2021	6Diax12	14	28.28	39	3090	Engraved		
4												
5												
6												
7												
8												
9												
10												
12												
13												
14												
15												
16												
		L	<u> </u>	I	I					1		

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202. 042-99029217

To: MR. Umar Safdar

619 Dr Mazhar Saleem

Usman Industries 92 B-2, Gulberg III, Lahore.										
Project:										
Our Dof No. CL/CED/	2000	Datad								

Our Ref. No. CL/CED/	2009	Dated:	10-02-21
Your Ref. No.	Nil	Dated:	01-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21 Tested on:

08-02-21 in dry/wet condition

		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	w	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	GR-153	25	1	2021	6Diax12	14	28.28	75	5950	Non Engraved
2	GR-154	25	1	2021	6Diax12	14.6	28.28	59	4680	Non Engraved
3	GR-8838	25	1	2021	6Diax12	14	28.28	53	4200	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202. 042-99029217

Directorate of Power

To: Projects

Energy Department Government of the Punjab.(M/s Mian Hydro Construction Engineers) Project: Infrastructure Development of Quaid-E-Azam Solar Park.

Our Ref. No. CL/CED/	2010	Dated:	10-02-21
Your Ref. No.	DOPP/351/QASP/2021	Dated:	28-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

28-01-21 Tested on:

10-02-21 in dry/wet condition

-		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	757		8.8X4.3X3.0	3402	37.84	49	2910	
2	757		9.0X4.3X3.1	3460	38.7	50	2900	
3	757		8.9X4.3X3.0	3442	38.27	56	3280	
4	757		8.9X4.3X3.0	3377	38.27	60	3520	
5	757		8.9X4.3X3.1	3548	38.27	58	3400	
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

572

Engr. Ubaid



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr.M.Hanif Khokhar (Construction Manager) NESPAK (M/s HCS).

Project: Establishment of Punjab Local Government Academy Building - Lahore.

Our Ref. No. CL/CED/	2011	Dated:	10-02-21
Your Ref. No.	3976/13/MHK/01/196	Dated:	04-02-21

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21

08-02-21 in dry/wet condition

Sr. No.	Mark*	Cas /W	Casting Date* /Wet Weight (gms)		Size (in)	Weight (Ibs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
							(Sq. In)	(IONS/IDS)	(PSI)	
1	L#72 (5000) Psi	19	1	2021	6Diax12	13.8	28.28	86	6820	Non Engraved
2	L#72 (5000) Psi	19	1	2021	6Diax12	14	28.28	83	6580	Non Engraved
3	L#72 (5000) Psi	19	1	2021	6Diax12	13.8	28.28	88	6970	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

627 Dr Mazar



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: MR. Umair Maqsood (Sub Divisional Officer) Dr Mazar Building Sub Division, Assembly Lahore. Project: Construction of 60-No Staff Quarters (Grade 1 to Grade to 10) at MPA'S Hostel ,Lahore (ADP NO.3429 for the Year of 2020-21)

Our Ref. No. CL/CED/	2012	Dated:	10-02-21
Your Ref. No.	No.94	Dated:	28-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21 Tested on: 08-02-21

in dry/wet condition

		Са	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark*	M	/et W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)	(gms)		s)			(Sq. in)	(Tons/lbs)	(Psi)		
1	2nd Floor Column (1:1:1/2:3)	26	10	2020	6x6x6	9	36	86	5360	Engraved
2	2nd Floor Column (1:1:1/2:3)	26	10	2020	6x6x6	9	36	102	6350	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

626



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: MR. Umair Maqsood (Sub Divisional Officer) Dr. Mazar Building Sub Division, Assembly Lahore. Project: Construction of 60-No Staff Quarters (Grade 1 to Grade to 10) at MPA'S Hostel ,Lahore (ADP NO. 3429 for the Year of 2020-21)

Our Ref. No. CL/CED/	2013	Dated:	10-02-21
Your Ref. No.	No.94	Dated:	28-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21

Tested on:

08-02-21 in dry/wet condition

		С	asting I	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/	Wet We	eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	1st Floor Column (1:1:1/2:3)	28	10	2020	6x6x6	9	36	112	6970	Engraved
2	1st Floor Column (1:1:1/2:3)	28	10	2020	6x6x6	9	36	132	8220	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to

be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

626 Mazar



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: MR. Umair Maqsood (Sub Divisional Officer) Dr Mazar Building Sub Division, Assembly Lahore. Project: Construction of 60-No Staff Quarters (Grade 1 to Grade to 10) at MPA'S Hostel ,Lahore (ADP NO. 3429 for the Year of 2020-21)

Our Ref. No. CL/CED/	2014	Dated:	10-02-21
Your Ref. No.	No.95	Dated:	28-01-21

COMPRESSION TEST REPORT

Tested on:

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21

08-02-21 in dry/wet condition

		Са	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No.	Mark*	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks	
0)			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	1st Floor Column (1:11/2:3)	31	10	2020	6x6x6	8.6	36	77	4800	Engraved
2	1st Floor Column (1:11/2:3)	31	10	2020	6x6x6	8.6	36	77	4800	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

626



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: MR. Umair Maqsood (Sub Divisional Officer) Dr Mazar Building Sub Division, Assembly Lahore. Project: Repair & Rehabilitation of Punjab Assembly, MPA Hostels, Speaker, Deputy Speaker Houses, and **PIPAL House Lahore.** IT Ref. No. CL/CED/ 2016 Datad 10 02 21

Our Ret. No. CL/CED/	2016	Dated:	10-02-21
Your Ref. No.	No.101	Dated:	29-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21 Tested on:

08-02-21 in dry/wet condition

			Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	M	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	is)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Ground Floor Slab (1:11/2:3)	17	11	2020	6x6x6	8.6	36	83	5170	Engraved
2	Ground Floor Slab (1:11/2:3)	17	11	2020	6x6x6	8.6	36	96	5980	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

626



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

 To:
 MR. Umair Maqsood (Sub Divisional Officer)
 Dr. Mazar

 Building Sub Division, Assembly Lahore.
 Project: Construction of 60-No Staff Quarters (Grade 1 to Grade to 10) at MPA'S Hostel ,Lahore (ADP NO. 3429 for the Year of 2020-21)

Our Ref. No. CL/CED/	2016	Dated:	10-02-21
Your Ref. No.	No.101	Dated:	29-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21 Tested on:

08

08-02-21 in dry/wet condition

		Са	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks	
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	1st Floor Column (1:11/2:3)	22	11	2020	6x6x6	8.6	36	61	3800	Engraved
2	1st Floor Column (1:11/2:3)	22	11	2020	6x6x6	8.6	36	73	4550	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

626 r Mazar



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To:MR. Umair Maqsood (Sub Divisional Officer)Dr. MazarBuilding Sub Division, Assembly Lahore.Project: Construction of 60-No Staff Quarters (Grade 1 to Grade to 10) at MPA'S Hostel ,Lahore (ADP NO.
3429 for the Year of 2020-21)

Our Ref. No. CL/CED/	2017	Dated:	10-02-21
Your Ref. No.	No.102	Dated:	29-01-21

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21

08-0

08-02-21 in dry/wet condition

		Ca	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	1st Floor Slab (1:2:4)	7	12	2020	6x6x6	9	36	106	6600	Engraved
2	1st Floor Slab (1:2:4)	7	12	2020	6x6x6	9	36	114	7100	Engraved
3			s							
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

626 r Mazar



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: MR. Umair Maqsood (Sub Divisional Officer) Dr Mazar Building Sub Division, Assembly Lahore. Project: Construction of 60-No Staff Quarters (Grade 1 to Grade to 10) at MPA'S Hostel ,Lahore (ADP NO. 3429 for the Year of 2020-21)

Our Ref. No. CL/CED/	2018	Dated:	10-02-21
Your Ref. No.	No.103	Dated:	29-01-21

COMPRESSION TEST REPORT

Tested on:

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21

08-02-21 in dry/wet condition

		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	M	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	2nd Floor Column (1:11/2:3)	11	12	2020	6x6x6	8.6	36	57	3550	Engraved
2	2nd Floor Column (1:11/2:3)	11	12	2020	6x6x6	8.6	36	47	2930	Engraved
3			s							
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

626



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

 To:
 MR. Umair Maqsood (Sub Divisional Officer)
 Dr. Mazar

 Building Sub Division, Assembly Lahore.
 Project: Construction of 60-No Staff Quarters (Grade 1 to Grade to 10) at MPA'S Hostel ,Lahore (ADP NO. 34 the Year of 2020-21)

Our Ref. No. CL/CED/	2019	Dated:	10-02-21
Your Ref. No.	No.104	Dated:	29-01-21

Tested on:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21

08-0

08-02-21 in dry/wet condition

		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	M	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Block-B,2nd Floor Slab(1:2:4)	22	12	2020	6x6x6	8.8	36	65	4050	Engraved
2	Block-B,2nd Floor Slab(1:2:4)	22	12	2020	6x6x6	9	36	69	4300	Engraved
3			s							
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

626 r Mazar



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To:MR. Umair Maqsood (Sub Divisional Officer)Dr. MazarBuilding Sub Division, Assembly Lahore.Project: Construction of 60-No Staff Quarters (Grade 1 to Grade to 10) at MPA'S Hostel ,Lahore (ADP NO.
3429 for the Year of 2020-21)

Our Ref. No. CL/CED/	2020	Dated:	10-02-21
Your Ref. No.	No.105	Dated:	29-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21 Tested on:

C

08-02-21 in dry/wet condition

		Ca	astin	ig Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	4th Floor Column(1:112:3)	2	1	2021	6x6x6	8.6	36	61	3800	Engraved
2	4th Floor Column(1:112:3)	2	1	2021	6x6x6	8.6	36	57	3550	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

626 r Mazar



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: MR. Umair Maqsood (Sub Divisional Officer) Building Sub Division, Assembly Lahore.

Project: Construction of MPA Hostel(Phase-II) Lahore (Group No. 02)

Our Ref. No. CL/CED/	2021	Dated:	10-02-21
Your Ref. No.	No.106	Dated:	29-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21 Tested on: 08-02-21 in dry/wet condition

626

Dr Mazar

		Ca: Da		ng *	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/We	t We	eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,		(gms	6)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(1:2:4)	20	1	21	6x6x6	9	36	57	3550	Engraved
2	(1:2:4)	20	1	21	6x6x6	8.8	36	59	3680	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Umair Nisar (Project Engineer)

616 Dr. Mazar

Sky High Builders,s IZMIR Society, Lahore. (Strong Ready Mix) Project: Construction of IZMIR Executive Shopping Mall & Apartments

Our Ref. No. CL/CED/	2022	Dated:	10-02-21
Your Ref. No.	IZMIR/006	Dated:	03-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

04-02-21 Tested on:

10-02-21 in dry/wet condition

			astir Date	ng *	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/We ⁻	t We	eight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms	;)			(Sq. in)	(Tons/lbs)	(Psi)	
1	RW2 (3000)Psi	18	1	21	6Diax12	13.2	28.28	51	4040	Engraved
2	RW2 (3000)Psi	18	1	21	6Diax12	13.8	28.28	59	4680	Engraved
3	UGWT Slab (3000)Psi	25	1	21	6Diax12	14	28.28	43	3410	Engraved
4	UGWT Slab (3000)Psi	25	1	21	6Diax12	14.6	28.28	45	3570	Engraved
5	Column Cap2(4000)Psi	19	1	21	6Diax12	13.4	28.28	59	4680	Engraved
6	Column Cap2(4000)Psi	19	1	21	6Diax12	14	28.28	65	5150	Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix

proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

609 Dr. Mazar

To: Mr. Shoaib Razzaq (Project Coordinator) SINACO Engineers (PVT.) Ltd. Project: Construction Works at CCL Pharma, Quaid-E- Azam Industinal State, Labor

Project: Construction Works at CCL Pharma, Quaid-E- Azam Industiral State, Lahore.

Our Ref. No. CL/CED/	2023	Dated:	10-02-21
Your Ref. No.	SEL/LHR/C-441/11762	Dated:	02-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

03-02-21 Tested on:

10-02-21 in dry/wet condition

		Cas	Casting Date*		Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	w	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1		4	1	2021	6Diax12	13.4	28.28	67	5310	Not Engraved
2		4	1	2021	6Diax12	13.4	28.28	61	4840	Not Engraved
3		25	1	2021	6Diax12	13.4	28.28	51	4040	Not Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

505 Engr. Ubaid

To: Municipal Officer (Infrastructure) Municipal Committee, Vehari

Project: Rehabilitation of Municipal Infrastructure in Vehari City Under Punjab Cities Program

Our Ref. No. CL/CED/	2024	Dated:	10-02-21
Your Ref. No.	103/MO(I)/MC(VR)	Dated:	20-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

21-01-21 Tested on:

10-02-21 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	SP		8.7x4.3x2.7	2638	37.41	61	3660	
2	SP		8.6x4.3x2.8	2675	36.98	58	3520	
3	SP		8.7x4.3x2.8	2644	37.41	51	3060	
4	SP		8.7x4.2x2.6	2618	36.54	49	3010	
5	SP		8.7x4.2x2.7	2629	36.54	53	3250	
6	SP		8.6x4.3x2.6	2681	36.98	47	2850	
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to

be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

515

To: Sub Divisional Officer (Buildings) Engr. Ubaid Sub Division Ferozewala. Project: Construction of Judicial Academy at Lahore Kala Shah Kaku, Lahore (ADP No. 3271/2020-21), Group No. 2, Residence Grade 1 to 10

Our Ref. No. CL/CED/	2025	Dated:	10-02-21
Your Ref. No.	872/F	Dated:	21-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 22-01-21

Tested on:

10-02-21 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	AT		8.8x4.2x2.9	3116	36.96	41	2490	
2	AT		8.8x4.2x2.8	3106	36.96	41	2490	
3	AT		8.7x4.1x2.8	2806	35.67	40	2520	
4	AT		8.7x4.2x2.9	3107	36.54	36	2210	
5	AT		8.8x4.2x2.8	3076	36.96	36	2190	
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

539

To: Sub Divisional Officer (Buildings) Engr. Ubaid Sub Division Ferozewala. Project: Construction of Judicial Academy at Lahore Kala Shah Kaku, Lahore (ADP No. 3271/2020-21)

Group No. 2, Residence Grade 1 to 10

Our Ref. No. CL/CED/	2026	Dated:	10-02-21
Your Ref. No.	880/F	Dated:	25-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

26-01-21 Tested on:

10-02-21 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	FB		8.8x4.2x2.8	3116	36.96	53	3220	
2	FB		8.9x4.2x2.9	3153	37.38	45	2700	
3	FB		8.7x4.2x2.9	3145	36.54	47	2890	
4	FB		8.8x4.1x2.8	3110	36.08	42	2610	
5	FB		8.9x4.3x2.9	3272	38.27	57	3340	
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202. 042-99029217

To: Sub Divisional Officer

557 Engr. Ubaid

Buildings Sub Division Kasur (M/s Jathol & Co) Project: Re-Const: of Dangerous Building (ADP 2020-21/GS No. 17) Re-Construction of 04-Nos. Class Rooms in Govt Boys High School Muhallah Kalan Tehsil & District Kasur (EMIS Code: 35120028)

Our Ref. No. CL/CED/	2027	Dated:	10-02-21
Your Ref. No.	17	Dated:	23-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

27-01-21 Tested on:

10-02-21 in dry/wet condition

		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	ND		9.0x4.3x2.9	3246	38.7	49	2840	
2	ND		8.8x4.3x2.9	3289	37.84	45	2670	
3	ND		8.7x4.2x3.0	3230	36.54	48	2950	
4	ND		8.7x4.3x3.0	3276	37.41	41	2460	
5	ND		8.8x4.3x3.0	3108	37.84	43	2550	
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer

557 Engr. Ubaid

Buildings Sub Division Kasur (M/s Jathol & Co) Project: Re-Const: of Dangerous Building (ADP 2020-21/GS No. 15) Construction of 02-Nos. Additional Class Rooms at Govt Boys Primary School Haveli Kamlay Khan Tehsil K.R.K District Kasur (EMIS Code: 35140876)

Our Ref. No. CL/CED/	2028	Dated:	10-02-21
Your Ref. No.	11	Dated:	20-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		27-01-21	Tested on: 10-02-21 in dry/wet condition					
No.	Mark*	Casting Date* /Wet	Size	Weight	Area of	Ultimate	Ultimate	Remarks
Sr.	Maik	Weight	(11)	(103./9113)	X-0601011	loau	01633	Remains

S		((gms))			(Sq. in)	(Tons/lbs)	(Psi)	
1	ND				8.9x4.3x3.0	3218	38.27	61	3570	
2	ND				8.7x4.3x2.8	3125	37.41	36	2160	
3	ND				8.7x4.3x2.9	3190	37.41	60	3600	
4	ND				8.9x4.3x3.1	3236	38.27	49	2870	
5	ND				8.8x4.3x2.9	3263	37.84	49	2910	
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Sub Divisional Officer

557 Engr. Ubaid

Buildings Sub Division Pattoki (M/s Jathol & Co) Project: Re-Const: of Dangerous Building (ADP 2020-21/GS No. 17) Re-Construction of 02-Nos. Dangerous Class Rooms at Govt Model Primary School Boor Singh Tehsil Chunian District Kasur (EMIS Code: 35110387)

Our Ref. No. CL/CED/	2029	Dated:	10-02-21
Your Ref. No.	3350/P	Dated:	20-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Spec	imens received on:	27-01-21	Tested on:		10-02-21	in dry/wet c	ondition	
_		Casting Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/Wet Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	ND		8.7x4.2x3.0	3144	36.54	45	2760	
2	ND		8.7x4.3x3.1	3354	37.41	51	3060	
3	ND		8.8x4.3x3.0	3284	37.84	45	2670	
4	ND		8.8x4.2x3.0	3208	36.96	40	2430	
5	ND		8.8x4.3x2.9	3126	37.84	34	2020	
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)