

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

655

To:	Syed Tasawur Hussain Naqvi (Assistant Executive Engineer-III)	Engr. Ubaid
	CCD, Pak. PWD. Gujranwala.	
	Project: Enhancement & Expansion of Building Infrastructure of NHMP Trainin	g College Sheikhupura,
	Phase-I (Sh: Admin Block) (Strip Foundation)	

Our Ref. No. CL/CED/	2075	Dated:	15-02-21
Your Ref. No.	AEE-III/CCD/GA/Work/ NHMP/Admn/P-I/Lab/04	Dated:	19-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Spec	pecimens received on:		ns received on: 10-02-21		Tested on: 10-02-21		in dry/wet condition			
		Ca	sting Da	ate*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/M	/et Wei	ght	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1		21	12	2020	6x6x6	9.2	36	82	5110	Engraved
2		21	12	2020	6x6x6	9.2	36	76	4730	Engraved
3		22	12	2020	6x6x6	8.6	36	41	2560	Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

655

To:	Syed Tasawur Hussain Naqvi (Assistant Executive Engineer-III)	Engr. Ubaid
	CCD, Pak. PWD. Gujranwala.	
	Project: Enhancement & Expansion of Building Infrastructure of NHMP Training College She	eikhupura,
	Phase-I (Sh: Admin Block) (Columns in Foundation)	

Our Ref. No. CL/CED/	2076	Dated:	15-02-21
Your Ref. No.	AEE-III/CCD/GA/Work /NHMP/Admn/P-I/Lab/05	Dated:	25-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		10-02-21		Tested on:		10-02-21	in dry/wet condition			
r. No.	Mark*	Casting Date*			Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
S			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1		27	12	2020	6x6x6	9	36	39	2430	Non Engraved
2		28	12	2020	6x6x6	9	36	78	4860	Non Engraved
3		28	12	2020	6x6x6	8.6	36	54	3360	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

655

To:	Syed Tasawur Hussain Naqvi (Assistant Executive Engineer-III)	Engr. Ubaid
	CCD, Pak. PWD. Gujranwala.	
	Project: Enhancement & Expansion of Building Infrastructure of NHMP Trainin	g College Sheikhupura
	Phase-I (Sh: Admin Block) (Plinth Beam)	

Our Ref. No. CL/C	ED/	2077	Dated:	15-02-21
	AEE-I	II/CCD/GA/Work/	Datadi	02 02 04
Your Ref. No.	NHMP	/Admn/P-I/Lab/06	Dated:	03-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Spec	imens received on:	10	-02-2	21	Tested on:		10-02-21	in dry/wet c	ondition	
Sr. No.	Mark*	Casti /We	ing E t We	Date*	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
0,		(gms)			(Sq. in)	(Tons/lbs)	(Psi)	
1		15	1	2021	6x6x6	8	36	35	2180	Non Engraved
2		15	1	2021	6x6x6	8	36	31	1930	Non Engraved
3		16	1	2021	6x6x6	8.2	36	38	2370	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

655

To:	Syed Tasawur Hussain Naqvi (Assistant Executive Engineer-III)	Engr. Ubaid
	CCD, Pak. PWD. Gujranwala.	
	Project: Enhancement & Expansion of Building Infrastructure of NHMP Training College S	heikhupura,
	Phase-I (Sh: Admin Block) (Ground Floor Columns)	

Our Ref. No. CL/CED/	2078	Dated:	15-02-21
Your Ref. No.	AEE-III/CCD/GA/Work/ NHMP/Admn/P-I/Lab/07	Dated:	09-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Spec	imens received on:	10	-02-2	21	Tested or	ר:	10-02-21	in dry/wet c	ondition			
Sr. No.	Mark*	Casting Date* /Wet Weight		Casting Date* /Wet Weight		Date*	Size (in)	Weight (Ibs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
		(gms)			(Sq. in)	(Tons/lbs)	(Psi)			
1		12	1	2021	6x6x6	8.8	36	92	5730	Non Engraved		
2		14	1	2021	6x6x6	8.8	36	44	2740	Engraved		
3		14	1	2021	6x6x6	9	36	79	4920	Engraved		
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Abdul Rehman Okawa Concrete, Sheikhupura **Project: Nil**

Our Ref. No. CL/CED/	2079	Dated:	15-02-21
Your Ref. No.	Nil	Dated:	09-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

09-02-21 Tested on:

10-02-21 in dry/wet condition

Ċ		Cast Dat	ing e*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark*	/Wet W	/eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)		(gm	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Rectangular Red			7.8x3.8x2.3	2555	29.64	66	4990	
2	Rectangular Red			7.8x3.8x2.3	2672	29.64	94	7110	
3									
4									
5									
6									
7									
8									
9									
10									
11									
12									
13									
14									
15									
16									

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

650 Engr. Ubaid



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Resident Engineer

652 Engr. Ubaid

ESS-I-AAR Consultant, Karachi

Project: Rehabilitation / Improvement of Sewerage System Jhang Phase-I

Tested on:

Our Ref. No. CL/CED/	2080-1 of 2	Dated:	15-02-21
Your Ref. No.	683	Dated:	08-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

09-02-21

10-02-21 in dry/wet condition

o.			astir	ng Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. N	Mark*	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks	
0)		(gms)				(Sq. in)	(Tons/lbs)	(Psi)		
1		9	1	2021	4x4x4	3	16	20.3	2850	
2										
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore Project: Nil

657 Dr. M. Yousaf

Our Ref. No. CL/CED/	2081	Dated:	15-02-21
Your Ref. No.	IHPL/Con/58	Dated:	08-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

11-02-21 in dry/wet condition

0.		Са	astin	ig Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi	1	2	2021	6Diax12	13.8	28.28	46	3650	Non Engraved
2	4000 Psi	1	2	2021	6Diax12	13.8	28.28	49	3890	Non Engraved
3	4000 Psi	1	2	2021	6Diax12	13.6	28.28	46	3650	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <u>http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6</u>

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore **Project: Nil**

657 Dr. M. Yousaf

Our Ref. No. CL/CED/	2082	Dated:	15-02-21
Your Ref. No.	IHPL/Con/57	Dated:	08-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

11-02-21 in dry/wet condition

r		1							-	
		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/W	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0)			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi	30	1	2021	6Diax12	13.8	28.28	53	4200	Non Engraved
2	4000 Psi	30	1	2021	6Diax12	13.6	28.28	56	4440	Non Engraved
3	4000 Psi	30	1	2021	6Diax12	13.8	28.28	56	4440	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore

Project: Nil

Our Ref. No. CL/CED/	2083	Dated:	15-02-21
Your Ref. No.	IHPL/Con/55	Dated:	08-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

11-02-21 in dry/wet condition

657

Dr. M. Yousaf

		Cas	Casting Date* /Wet Weight		Size	Weight	Area of	Ultimate	Ultimate	
Sr. N	Mark*	/W			(in)	(lbs./gms)	A- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi	29	1	2021	6Diax12	14	28.28	73	5790	Non Engraved
2	4000 Psi	29	1	2021	6Diax12	14	28.28	73	5790	Non Engraved
3	4000 Psi	29	1	2021	6Diax12	14	28.28	69	5470	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore

Project: Nil

657 Dr. M. Yousaf

Our Ref. No. CL/CED/	2084	Dated:	15-02-21
Your Ref. No.	IHPL/Con/48	Dated:	28-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

11-02-21 in dry/wet condition

		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	w	'et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi	11	1	2021	6Diax12	13.8	28.28	51	4040	Non Engraved
2	4000 Psi	11	1	2021	6Diax12	13.4	28.28	55	4360	Non Engraved
3	4000 Psi	11	1	2021	6Diax12	13.8	28.28	51	4040	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore Project: Nil

657 Dr. M. Yousaf

Our Ref. No. CL/CED/	2085	Dated:	15-02-21
Your Ref. No.	IHPL/Con/47	Dated:	28-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

11-02-21 in dry/wet condition

		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	ſW	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0,			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi	10	1	2021	6Diax12	13.4	28.28	63	4990	Non Engraved
2	4000 Psi	10	1	2021	6Diax12	14	28.28	68	5390	Non Engraved
3	4000 Psi	10	1	2021	6Diax12	14	28.28	65	5150	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore

Project: Nil

657 Dr. M. Yousaf

Our Ref. No. CL/CED/	2086	Dated:	15-02-21
Your Ref. No.	IHPL/Con/46	Dated:	28-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

11-02-21 in dry/wet condition

		Са	astir	ng Date*	Size	Weight	Area of	Ultimate	Ultimate	
ir. No	Mark*	Λ	/Wet Weight		(in)	(lbs./gms)	X-Section	load	Stress	Remarks
S			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	8000 Psi	9	1	2021	6Diax12	14	28.28	104	8240	Non Engraved
2	8000 Psi	9	1	2021	6Diax12	14	28.28	108	8560	Non Engraved
3	8000 Psi	9	1	2021	6Diax12	14	28.28	110	8720	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore

Project: Nil

657 Dr. M. Yousaf

Our Ref. No. CL/CED/	2087	Dated:	15-02-21
Your Ref. No.	IHPL/Con/45	Dated:	28-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

11-02-21 in dry/wet condition

h										
		Ca	astir	ng Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	Λ	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi	8	1	2021	6Diax12	13.8	28.28	82	6500	Non Engraved
2	4000 Psi	8	1	2021	6Diax12	13.8	28.28	81	6420	Non Engraved
3	4000 Psi	8	1	2021	6Diax12	13.2	28.28	79	6260	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore

Project: Nil

657 Dr. M. Yousaf

Our Ref. No. CL/CED/	2088	Dated:	15-02-21
Your Ref. No.	IHPL/Con/53	Dated:	28-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

11-02-21 in dry/wet condition

	Ö		astir	ng Date*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark*	Λ	/Wet Weight (gms)		(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)							(Sq. in)	(Tons/lbs)	(Psi)	
1	8000 Psi	8	1	2021	6Diax12	13	28.28	110	8720	Non Engraved
2	8000 Psi	8	1	2021	6Diax12	14	28.28	114	9030	Non Engraved
3	8000 Psi	8	1	2021	6Diax12	13	28.28	112	8880	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore Project: Nil

672 Dr. M. Yousaf

Our Ref. No. CL/CED/	2089	Dated:	15-02-21
Your Ref. No.	IHPL/Con/54	Dated:	28-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

12-02-21 Tested on:

12-02-21 in dry/wet condition

Jz-z i in dry/wet condition

		Casting Date*		g Date*	Size	Weight	Area of	Ultimate	Ultimate	
ŝr. No	Mark*	/W	/Wet Weight (gms)		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0)							(Sq. in)	(Tons/lbs)	(Psi)	
1	4000 Psi	12	1	2021	6Diax12	13.6	28.28	61	4840	Non Engraved
2	4000 Psi	12	1	2021	6Diax12	14	28.28	62	4920	Non Engraved
3	4000 Psi	12	1	2021	6Diax12	13.4	28.28	62	4920	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore **Project: Nil**

672 Dr. M. Yousaf

Our Ref. No. CL/CED/	2090	Dated:	15-02-21
Your Ref. No.	IHPL/Con/49	Dated:	28-01-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

12-02-21 Tested on: 12-02-21 in dry/wet condition

		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	w	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	8000 Psi	12	1	2021	6Diax12	14	28.28	98	7770	Non Engraved
2	8000 Psi	12	1	2021	6Diax12	14	28.28	112	8880	Non Engraved
3	8000 Psi	12	1	2021	6Diax12	14	28.28	110	8720	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore Project: Nil

672 Dr. M. Yousaf

Our Ref. No. CL/CED/	2091	Dated:	15-02-21
Your Ref. No.	IHPL/Con/56	Dated:	08-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

12-02-21 Tested on:

12-02-21 in dry/wet condition

		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	8000 Psi	29	1	2021	6Diax12	13.2	28.28	106	8400	Non Engraved
2	8000 Psi	29	1	2021	6Diax12	14	28.28	102	8080	Non Engraved
3	8000 Psi	29	1	2021	6Diax12	13.8	28.28	112	8880	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Shahbaz Imperium Hospitality (Pvt.) Ltd. Lahore

Project: Nil

672 Dr. M. Yousaf

Our Ref. No. CL/CED/	2092	Dated:	15-02-21
Your Ref. No.	IHPL/Con/59	Dated:	08-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

12-02-21 Tested on:

12-02-21 in dry/wet condition

		Ca	astir	ig Date*	Size	Weight	Area of	Ultimate	Ultimate	
r. No	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
S			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	8000 Psi	5	2	2021	6Diax12	14	28.28	97	7690	Non Engraved
2	8000 Psi	5	2	2021	6Diax12	13.8	28.28	103	8160	Non Engraved
3	8000 Psi	5	2	2021	6Diax12	14	28.28	99	7850	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Tahir Mehmood

662 Dr Yousaf

Husnain Builders (Pvt.)Ltd. Client (Vision Builders Pvt. Ltd) Project: Rehabilitation / Improvement of Sewerage System Jhang Phase-I

Our Ref. No. CL/CED/	2093	Dated:	15-02-21
Your Ref. No.	Nil	Dated:	10-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

12-02-21 in dry/wet condition

-						1		1		
ö		Ca	astin	ig Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. X	Mark*	Λ	/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mumty Slab	7	1	2021	6Diax12	13	28.28	60	4760	Non Engraved
2	Mumty Slab	7	1	2021	6Diax12	13.2	28.28	58	4600	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Furqan UI Haq (General Manager) AYQ Developers (Pvt.) Ltd. **Project: Union Complex**

Our Ref. No. CL/CED/ 2094 Dated: 15-02-21 Your Ref. No. Nil Dated: 10-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

12-02-21 in dry/wet condition

		Casting Date*		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*	w	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ıs)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Ready-Mix (4000)Psi	13	1	2021	6Diax12	14	28.28	60	4760	Engraved
2	Ready-Mix (4000)Psi	13	1	2021	6Diax12	14	28.28	59	4680	Engraved
3	Ready-Mix (4000)Psi	13	1	2021	6Diax12	14	28.28	63	4990	Engraved
4	Ready-Mix (1500)Psi	2	2	2021	6Diax12	13	28.28	3	240	Engraved
5	Ready-Mix (1500) Psi	2	2	2021	6Diax12	13	28.28	4	320	Engraved
6	Ready-Mix (1500) Psi	2	2	2021	6Diax12	13	28.28	4	320	Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

660 Dr. Yousaf



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Umar Nisar (Project Engineer)

663 Dr. Yousaf

Sky High Builder's IZMIR Society, Lahore. **Project: IZMIR Executive Shopping Mall and Apparments**

Our Ref. No. CL/CED/	2095	Dated:	15-02-21
Your Ref. No.	IZMIR/007	Dated:	09-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

10-02-21 Tested on:

12-02-21 in dry/wet condition

		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	w	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Raft 1st Pour (3000) Psi	8	1	2021	6Diax12	14	28.28	43	3410	Engraved
2	Raft 1st Pour (3000) Psi	8	1	2021	6Diax12	14	28.28	43	3410	Engraved
3	Raft 2nd Pour (3000) Psi	10	1	2021	6Diax12	14	28.28	63	4990	Engraved
4	Raft 2nd Pour (3000) Psi	10	1	2021	6Diax12	14.6	28.28	58	4600	Engraved
5	Footing Beam (3000) Psi	12	1	2021	6Diax12	14	28.28	80	6340	Engraved
6	Footing Beam (3000) Psi	12	1	2021	6Diax12	14	28.28	87	6900	Engraved
7	UGWT Slab 2 (3000) Psi	25	1	2021	6Diax12	14	28.28	41	3250	Engraved
8	UGWT Slab 2 (3000) Psi	25	1	2021	6Diax12	14	28.28	42	3330	Engraved
9	Plinth Beam (3000) Psi	28	1	2021	6Diax12	14	28.28	35	2780	Engraved
10	Plinth Beam (3000) Psi	28	1	2021	6Diax12	14	28.28	35	2780	Engraved
11										
12										
13										
14										
15										
16										

Results can also be seen on website

http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: SAB Construction Faislabad.

680 Dr.Mazar

Project: Construction of Fusing at PAF Risalewala" CA NO. CEAF-CZ-48/2020

Our Ref. No. CL/CED/	2096	Dated:	15-02-21
Your Ref. No.	Nil	Dated:	15-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

15-02-21

Specimens received on:

Tested on:

12-02-21 in dry/wet condition

i		1								
ġ		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No	Mark*	ſW	et V	Veight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
0)			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1		15	1	2021	6Diax12	14	28.28	81	6420	Non Engraved
2		15	1	2021	6Diax12	13.8	28.28	71	5630	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhammad Moosa (XEN) AGE (AIR) Risalewala. (M/s SAB Construction)

Project: Construction of Fusing at PAF Risalewala" CA NO. CEAF-CA-48/2020

Our Ref. No. CL/CED/	2097	Dated:	15-02-21
Your Ref. No.	6400-48/2020/43/E-6	Dated:	15-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

15-02-21 Tested on: 15-02-21 in dry/wet condition

Sr. No.	Mark*	Casting Date*		g Date*	Size	Weight	Area of	Ultimate	Ultimate	
		/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1		15	1	2021	6Diax12	14	28.28	96	7610	Non Engraved
2		15	1	2021	6Diax12	14	28.28	88	6970	Non Engraved
3		15	1	2021	6Diax12	14	28.28	96	7610	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

679 Dr Mazar



Lahore.

Plain and Reinforced Concrete Laboratory Department of Civil Engineering

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muhamad Azeem (Operational Manager)

658 Engr.Ubaid

Project: Construction of Hotel Building at 24-A Block E/2 at Gulberg III Lahore.

Our Ref. No. CL/CED/	2098	Dated:	15-02-21
Your Ref. No.	AAA/24A./0024	Dated:	15-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

15-02-21 Tested on:

15-02-21 in dry/wet condition

-										
Sr. No.	Mark*	Casting Date*			Size	Weight	Area of	Ultimate	Ultimate	
		/Wet Weight			(in)	(lbs./gms)	X-Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(5000) Psi	9	1	2021	6Diax12	15	28.28	108	8560	Non Engraved
2	(5000) Psi	9	1	2021	6Diax12	14	28.28	99	7850	Non Engraved
3	(5000) Psi	9	1	2021	6Diax12	14.4	28.28	108	8560	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)