

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Hassan khan Sherwani (Provinvial Construction Supervision Manager) Dr.M. Yousaf Humqadam SCRP (M/s Astral Constructions) Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (GGHS Ghania Key)

Our Ref. No. CL/CED/	2259	Dated:	01-03-21
Your Ref. No.	IMC-LHR/SCRP/2020/ MaterialTesting/LHR-1	Dated:	26-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

26-02-21 T

Tested on:

26-02-21 in dry/wet condition

		Casting Date* /Wet Weight		g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*			(in)	(lbs./gms)	X- Section	load	Stress	Remarks	
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube	25	1	2021	2.0x2.0x2.0	271	4	8	4410	
2	Mortar Cube	25	1	2021	2.0x2.0x2.0	270	4	4.5	2480	
3	Mortar Cube	25	1	2021	2.0x2.0x2.0	273	4	6	3310	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix

proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

Director/Dy. Director Concrete Laboratory

775 Dr.M. Yousaf



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

775

Dr.M. Yousaf

To: Mr. Hassan khan Sherwani (Provinvial Construction Supervision Manager) Humqadam SCRP (M/s Astral Constructions) Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (GPS Tabbu Munday Key)

Our Ref. No. CL/CED/	2260	Dated:	01-03-21
Your Ref. No.	IMC-LHR/SCRP/2020/ MaterialTesting/LHR-1	Dated:	26-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Spec	Specimens received on:		26-02-21		Tested on:	26-02-21		in dry/wet condition		
Sr. No.	Mark*	Casting Date* /Wet Weight		-	Size (in)	Weight (Ibs./gms)	Area of X-	Ultimate	Ultimate Stress	Remarks
Sr.	Mark			-	("')	(103./9113)	Section			Remains
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube	25	1	2021	2.0x2.0x2.0	271	4	8	4410	
2	Mortar Cube	25	1	2021	2.0x2.0x2.0	270	4	4.5	2480	
3	Mortar Cube	25	1	2021	2.0x2.0x2.0	273	4	6	3310	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption


*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

14

15

16

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

775

To: Mr. Hassan khan Sherwani (Provinvial Construction Supervision Manager) Dr.M. Yousaf Humqadam SCRP (M/s Astral Constructions) Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (GHS Chatian Wala)

Our Ref. No. CL/CED/	2262	Dated:	01-03-21
Your Ref. No.	IMC-LHR/SCRP/2020/ MaterialTesting/LHR-1	Dated:	26-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Spec on:	imens received		26-0	02-21	Tested on:		26-02-21	in dry/wet c	ondition	
Sr. No.	Mark*	Casting Date* /Wet Weight (gms)			Size (in)	Weight (Ibs./gms)	Area of X- Section (Sq. in)	Ultimate load (Tons/lbs)	Ultimate Stress (Psi)	Remarks
1	Mortar Cube	18	1	2021	2.0x2.0x2.0	266	4	2.5	1380	
2	Mortar Cube	18	1	2021	2.0x2.0x2.0	269	4	55	30310	
3	Mortar Cube	18	1	2021	2.0x2.0x2.0	275	4	3.5	1930	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website <u>http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6</u>

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Majid Yaseen (Senior District Engineer) Humgadam SCRP (M/s Astral Constructions) Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (Chak 207 RB) Taka Garh Chakhh)

Our Ref. No. CL/CED/ 2264 Dated: 01-03-21

Your Ref. No.

IMC-LHR/SCRP/2020/

MaterialTesting/LHR-1

26-02-21

Dated:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

26-02-21

Tested on:

26-02-21 in dry/wet condition

		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0,			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube	19	2	2021	2.0x2.0x2.0	268	4	3	1660	
2	Mortar Cube	19	2	2021	2.0x2.0x2.0	272	4	7	3860	
3	Mortar Cube	19	2	2021	2.0x2.0x2.0	269	4	3.5	1930	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

Director/Dy. Director Concrete Laboratory

774 Dr.M. Yousaf



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Majid Yaseen (Senior District Engineer) Humqadam SCRP (M/s Astral Constructions)

774 Dr.M. Yousaf

Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (GGHS 24 GB)

Our Ref. No. CL/CED/	2266	Dated:	01-03-21
Your Ref. No.	IMC-LHR/SCRP/2020/ MaterialTesting/LHR-1	Dated:	26-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received	
on:	26-02-21

Tested on:

26-02-21 in dry/wet condition

		Casting Date* ark* /Wet Weight		Size	Weight	Area of	Ultimate	Ultimate		
Sr. No.	Mark*			(in)	(lbs./gms)	X- Section	load	Stress	Remarks	
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube	27	1	2021	2.0x2.0x2.0	281	4	5	2760	
2	Mortar Cube	27	1	2021	2.0x2.0x2.0	278	4	3.5	1930	
3	Mortar Cube	27	1	2021	2.0x2.0x2.0	291	4	5	2760	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muneeb Ur Rehman (Senior District Engineer) Humqadam SCRP Sialkot (M/s Sardar Gohar & Co. Islamabad) Project: Retro - Fitting / Humgadam SCRP- Sialkot

Dr.M. Yousaf

726

Our Ref. No. CL/CED/	2267-1of 2	Dated:	0-03-2021
Your Ref. No.	Nil	Dated:	18-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

19-02-21

Specimens received on:

Tested on:

26-02-21 in dry/wet condition

		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	ອິ Mark* ເວັ		/Wet Weight		(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(gn	าร)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube (GPS Gogial)	25	1	2021	2.0x2.0x2.0	268	4	12.25	6750	
2	Mortar Cube (GPS Gogial)	25	1	2021	2.0x2.0x2.0	254	4	13	7170	
3	Mortar Cube (GPS Gogial)	25	1	2021	2.0x2.0x2.0	248	4	11	6070	
4	Mortar Cube (GGPS Bhattian)	5	1	2021	2.0x2.0x2.0	271	4	12	6620	
5	Mortar Cube (GGPS Bhattian)	5	1	2021	2.0x2.0x2.0	253	4	5.25	2900	
6	Mortar Cube (GGPS Bhattian)	5	1	2021	2.0x2.0x2.0	264	4	13	7170	
7	Mortar Cube (GPS Saleh Pur)	8	1	2021	2.0x2.0x2.0	248	4	4	2210	
8	Mortar Cube (GPS Saleh Pur)	8	1	2021	2.0x2.0x2.0	253	4	4.5	2480	
9	Mortar Cube (GPS Saleh Pur)	8	1	2021	2.0x2.0x2.0	259	4	3.75	2070	
10	Mortar Cube (GPS Gojra #2)	2	2	2021	2.0x2.0x2.0	261	4	20.5	11300	
11	Mortar Cube (GPS Gojra #2)	2	2	2021	2.0x2.0x2.0	270	4	13	7170	
12	Mortar Cube (GPS Gojra #2)	2	2	2021	2.0x2.0x2.0	269	4	14	7720	
13	Mortar Cube (GPPS Mehtab)	18	1	2021	2.0x2.0x2.0	272	4	14	7720	
14	Mortar Cube (GPPS Mehtab)	18	1	2021	2.0x2.0x2.0	268	4	3.25	1800	
15	Mortar Cube (GPPS Mehtab)	18	1	2021	2.0x2.0x2.0	279	4	2.25	1240	
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Muneeb Ur Rehman (Senior District Engineer) Humqadam SCRP Sialkot (M/s Sardar Gohar & Co. Islamabad) Project: Retro - Fitting / Humqadam SCRP- Sialkot

726 Dr.M. Yousaf

Our Ref. No. CL/CED/	2267-1of 2	Dated:	01-03-21
Your Ref. No.	Nil	Dated:	18-02-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:

19-02-21 Tested on:

26-02-21 in dry/wet condition

										1
Sr. No.	Mark*	Casting Date*		Date*	Size	Weight	Area of	Ultimate	Ultimate	
		/Wet Weight			(in)	(lbs./gms)	X- Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube (GGPS Sabal Pur)	27	1	2021	2.0x2.0x2.0	273	4	15	8270	
2	Mortar Cube (GGPS Sabal Pur)	27	1	2021	2.0x2.0x2.0	269	4	8.75	4830	
3	Mortar Cube (GGPS Sabal Pur)	27	1	2021	2.0x2.0x2.0	265	4	12.75	7030	
4	Mortar Cube (GES Darya Bider)	25	1	2021	2.0x2.0x2.0	268	4	12	6620	
5	Mortar Cube (GES Darya Bider)	25	1	2021	2.0x2.0x2.0	259	4	12	6620	
6	Mortar Cube (GES Darya Bider)	25	1	2021	2.0x2.0x2.0	254	4	6.5	3590	
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

* as engraved on the specimens (if any)

** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

*** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

**** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix

proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)