

University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

934

Dr. Rizwan Riaz

To: Mr. Ehmad Ejaz (Assistant Quality Surveyor)

M/S LINKER (Pvt.) Ltd, Lahore. (M/S NYK Associates)

Subject: Constrction of Corporate Office Tower 9-Jail Road, Lahore.

Our Ref. No. CL/CED/ 2579 Dated: 25-03-21

Your Ref. No. Nil Dated: 24-03-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-03-21 Tested on: 25-03-21 in dry/wet condition

		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	'et V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(4000) Psi	24	2	2021	6Diax12	13.4	28.28	55	4360	Non Engraved
2	(4000) Psi	24	2	2021	6Diax12	13.4	28.28	57	4520	Non Engraved
3	(4000) Psi	24	2	2021	6Diax12	13.4	28.28	67	5310	Non Engraved
4	(4000) Psi	9	3	2021	6Diax12	13.2	28.28	27	2140	Engraved
5	(4000) Psi	9	3	2021	6Diax12	13	28.28	33	2620	Engraved
6	(4000) Psi	9	3	2021	6Diax12	13.2	28.28	31	2460	Engraved
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

25-03-21

934 Dr. Rizwan Riaz

To: Mr. Majid Yaseen (Senior District Engineer)

Humqadam SCRP (M/s Astral Constructions)

Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (GGHS Chak No.209 RB)

Our Ref. No. CL/CED/ 2580 Dated:

IMC-FSD/SCRP/2021/

Your Ref. No. MaterialTesting/FSD-1 Dated: 24-03-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received

on: 24-03-21 Tested on: 25-03-21 in dry/wet condition

Sr. No.	Mark*			ng Date* Weight	Size (in)	Weight (lbs./gms)	Area of X- Section	Ultimate load	Ultimate Stress	Remarks
S			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube	19	2	2021	2.0x2.0x2.0	241	4	16.5	9100	
2	Mortar Cube	19	2	2021	2.0x2.0x2.0	239	4	5	2760	
3	Mortar Cube	19	2	2021	2.0x2.0x2.0	249	4	6	3310	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

934

To: Mr. Majid Yaseen (Senior District Engineer)

Dr. Rizwan Riaz

Humqadam SCRP (M/s Astral Constructions)

Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (GGHS Auyb

Colony)

Our Ref. No. CL/CED/ 2581 Dated: 25-03-21

IMC-FSD/SCRP/2021/

Your Ref. No. MaterialTesting/FSD-1 Dated: 24-03-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received

on: 24-03-21 Tested on: 25-03-21 in dry/wet condition

					•					
		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	٨	Vet	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube	25	2	2021	2.0x2.0x2.0	238	4	6.5	3590	
2	Mortar Cube	25	2	2021	2.0x2.0x2.0	246	4	4.5	2480	
3	Mortar Cube	25	2	2021	2.0x2.0x2.0	258	4	5.5	3040	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

Director/Dy. Director Concrete Laboratory

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

934

To: Mr. Majid Yaseen (Sr. District Engineer)

Dr. Rizwan Riaz

Humqadam SCRP (M/s Astral Constructions)

Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (GHS Talwandi)

Our Ref. No. CL/CED/ 2582 Dated: 25-03-21

IMC-FSD/SCRP/2021/

Your Ref. No. MaterialTesting/FSD-1 Dated: 24-03-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received

on: 24-03-21 Tested on: 25-03-21 in dry/wet condition

		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube	20	2	2021	2.0x2.0x2.0	253	4	5	2760	
2	Mortar Cube	20	2	2021	2.0x2.0x2.0	247	4	12.2	6730	
3	Mortar Cube	20	2	2021	2.0x2.0x2.0	241	4	10	5510	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

935

To: Mr. Hassan Khan Sherwani (Provincial Construction Supervision)

Dr. Qasim

Humqadam SCRP (M/s Astral Constructions)

Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (GHS Talwandi)

Our Ref. No. CL/CED/ 2583 Dated: 25-03-21

IMC-LHS/SCRP/2021/

Your Ref. No. MaterialTesting/LHS-1 Dated: 24-03-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received

on: 24-03-21 Tested on: 25-03-21 in dry/wet condition

		C	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*			Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
,			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube	16	3	2021	2.0x2.0x2.0	268	4	8.1	4470	
2	Mortar Cube	16	3	2021	2.0x2.0x2.0	271	4	5.6	3090	
3	Mortar Cube	16	3	2021	2.0x2.0x2.0	270	4	9.2	5070	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

935

To: Mr. Hassan Khan Sherwani (Provincial Construction Supervision)

Dr. Qasim

Humqadam SCRP (M/s Astral Constructions)

Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (GGHS Khara)

Our Ref. No. CL/CED/ 2584 Dated: 25-03-21

IMC-LHS/SCRP/2021/

Your Ref. No. MaterialTesting/LHS-1 Dated: 24-03-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received

on: 24-03-21 Tested on: 25-03-21 in dry/wet condition

F		,							1	
		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	٨	Vet	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube	22	2	2021	2.0x2.0x2.0	252	4	3.4	1880	
2	Mortar Cube	22	2	2021	2.0x2.0x2.0	263	4	4	2210	
3	Mortar Cube	22	2	2021	2.0x2.0x2.0	249	4	13.5	7440	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab) Director/Dy. Director Concrete Laboratory

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

935

To: Mr. Hassan Khan Sherwani (Provincial Construction Supervision)

Dr. Qasim

Humqadam SCRP (M/s Astral Constructions)

Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide (GHS Chatian Wala)

Our Ref. No. CL/CED/ 2586 Dated: 25-03-21

IMC-LHS/SCRP/2021/

Your Ref. No. MaterialTesting/LHS-1 Dated: 24-03-21

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received 25-03-

on: 24-03-21 Tested on: 21 in dry/wet condition

		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	N	Vet '	Weight	(in)	(lbs./gms)	X- Section	load	Stress	Remarks
			(g	ms)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Mortar Cube	18	2	2021	2.0x2.0x2.0	271	4	7.2	3970	
2	Mortar Cube	18	2	2021	2.0x2.0x2.0	269	4	12.5	6890	
3	Mortar Cube	18	2	2021	2.0x2.0x2.0	273	4	4.8	2650	
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

Director/Dy. Director Concrete Laboratory

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

906

To: M/S MG Construction & Services (Pvt.) Ltd.

Dr. Ambreen

Lahore.

Project: Construction of Contact PTCL Centre Wafaqi Colony

Our Ref. No. CL/CED/ 2586 Dated: 25/03/2021

Your Ref. No. Nil Dated: 18/3/2021

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18/3/2021 Tested on: 25/03/2021 in dry/wet condition

		Ca	astin	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	Λ	Vet	Weight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gms)				(Sq. in)	(Tons/lbs)	(Psi)	
1	Roof Beam & Slab (4000) Psi	5	3	2021	6Diax12	14	28.28	33	2620	Engraved
2	Roof Beam & Slab (4000) Psi	5	3	2021	6Diax12	13.8	28.28	33	2620	Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

907

Dr. Ambreen

To: Mr. Furqan-Ul-Haq (General Manager) AYQ Developers (Pvt.) Ltd., Lahore.

Project: Nil

Our Ref. No. CL/CED/ 2587 Dated: 25/03/2021

Your Ref. No. Nil Dated: 18/3/2021

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18/3/2021 Tested on: 25/03/2021 in dry/wet condition

Ċ		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	(1:3:6)	20	2	2021	6Diax12	14	28.28	39	3090	Non Engraved
2	(1:3:6)	20	2	2021	6Diax12	13.8	28.28	37	2940	Non Engraved
3	(1:3:6)	20	2	2021	6Diax12	14	28.28	41	3250	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

928

To: Resident Engineer

Dr. Ambreen

Ess-I-AAR Consultant

Project: Rehabilitation/Improvement of Sewerage System Jhang Phase-I

Our Ref. No. CL/CED/ 2588 Dated: 25/03/2021

Your Ref. No. No.754 Dated: 24/3/2021

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24/3/2021 Tested on: 25/03/2021 in dry/wet condition

		l _								
		Cas	sting	g Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	W	'et V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0,			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	Solid Wall of Wet Well (1:1:2)	22	2	2021	6x6x6	8.8	36	126	7840	Non Engraved
2	Solid Wall of Wet Well (1:1:2)	22	2	2021	6x6x6	8.8	36	110	6850	Non Engraved
3										
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

To: Mr. Hassan Khan Sherwani (Provincial Construction Supervision Manager) **Humqadam SCRP (M/S Dawn Construction)**

Dr Ambreen

Project: Humqadam-School Construction and Rehabilitation Programme IMC WorldWide.

Our Ref. No. CL/CED/ 25/03/2021 2589-1 of 2 Dated:

IMC-LHR-SCRP-2020/

Your Ref. No. Material Testing/ LHR-6 Dated: 25/3/2021

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

22/3/2021 Specimens received on: Tested on: 25/03/2021 in dry/wet condition

_		Cast	ting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/We	et W	eight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)			(gm:	s)			(Sq. in)	(Tons/lbs)	(Psi)	
1		16	3	2021	6Diax12	11	28.28	21	1670	Non Engraved
2		16	3	2021	6Diax12	13	28.28	49	3890	Non Engraved
3		16	3	2021	6Diax12	13.2	28.28	63	4990	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

Director/Dy. Director Concrete Laboratory

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

927

To: Mr. Muneeb Ur Rehman (Sr. District Engineer)

Dr. Ambreen

Humqadam SCRP Sialkot.

Project : Humqadam-School Construction and Rehabilitation Programme IMC WorldWide. (GGPS Galotian

Kalan)

Our Ref. No. CL/CED/ 2590 Dated: 25/03/2021

Your Ref. No. Nil Dated: 25/3/2021

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 22/3/2021 Tested on: 25/03/2021 in dry/wet condition

						1			<u> </u>	
		Cas	sting	Date*	Size	Weight	Area of	Ultimate	Ultimate	
Sr. No.	Mark*	/W	et V	Veight	(in)	(lbs./gms)	X-Section	load	Stress	Remarks
			(gn	ns)			(Sq. in)	(Tons/lbs)	(Psi)	
1	EMIS Code (34310461)	16	3	2021	6Diax12	12.2	28.28	45	3570	Non Engraved
2	EMIS Code (34310461)	16	3	2021	6Diax12	12.4	28.28	53	4200	Non Engraved
3	EMIS Code (34310461)	16	3	2021	6Diax12	12.4	28.28	49	3890	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

 $Results\ can\ also\ be\ seen\ on\ website\ \underline{http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports\&id=6}$

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

927

Dr Ambreen

To: Mr. Magssod (Project Coordinator)

M/S Banu Mukhtar Contracting (Pvt.) Ltd.

Project: Novatex (Pvt.) Ltd M3 industrial State FSD.

Our Ref. No. CL/CED/ 2593 Dated: 25/03/2021

Your Ref. No. BML/300841/010 Dated: 19/3/2021

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19/3/2021 Tested on: 25/03/2021 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Weight	Area of	Ultimate	Ultimate	
		/Wet Weight			(in)	(lbs./gms)	X-Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	Production Hall Flooring (3500) Psi	8	3	2021	6Diax12	14	28.28	48	3810	Non Engraved
2	Production Hall Flooring (3500) Psi	8	3	2021	6Diax12	14.2	28.28	73	5790	Non Engraved
3	Production Hall Flooring (3500) Psi	8	3	2021	6Diax12	14.4	28.28	86	6820	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

927

To: Mr. Maqssod (Project Coordinator)

Dr. Ambreen

M/S Banu Mukhtar Contracting (Pvt.) Ltd.

Project: Novatex (Pvt.) Ltd M3 industrial State FSD.

Our Ref. No. CL/CED/ 2594 Dated: 25/03/2021

Your Ref. No. BML/300841/011 Dated: 19/3/2021

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19/3/2021 Tested on: 25/03/2021 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Weight	Area of	Ultimate	Ultimate	
		/Wet Weight			(in)	(lbs./gms)	X-Section	load	Stress	Remarks
0)		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	Power House Column (3500) Psi	16	16 2 2021		6Diax12	14.8	28.28	65	5150	Non Engraved
2	Power House Column (3500) Psi	16	2	2021	6Diax12	14.4	28.28	55	4360	Non Engraved
3	Power House Column (3500) Psi	16	2	2021	6Diax12	14.2	28.28	69	5470	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength



University of Engineering and Technology, Lahore Phone Nos. 042-99029202, 042-99029217

927

Dr Ambreen

To: Mr. Maqssod (Project Coordinator)

M/S Banu Mukhtar Contracting (Pvt.) Ltd.

Project: Novatex (Pvt.) Ltd M3 industrial State FSD.

Our Ref. No. CL/CED/ 2595 Dated: 25/03/2021

Your Ref. No. BML/300841/009 Dated: 19/3/2021

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19/3/2021 Tested on: 25/03/2021 in dry/wet condition

				_						
Sr. No.		Casting Date*			Size	Weight	Area of	Ultimate	Ultimate	
	Mark*	/Wet Weight			(in)	(lbs./gms)	X-Section	load	Stress	Remarks
		(gms)					(Sq. in)	(Tons/lbs)	(Psi)	
1	Warehouse (3500) Psi	28	2	2021	6Diax12	14.2	28.28	77	6100	Non Engraved
2	Warehouse (3500) Psi	28	2	2021	6Diax12	14.4	28.28	67	5310	Non Engraved
3	Warehouse (3500) Psi	28	2	2021	6Diax12	14.4	28.28	45	3570	Non Engraved
4										
5										
6										
7										
8										
9										
10										
11										
12										
13										
14										
15										
16										

Results can also be seen on website http://www.uet.edu.pk/faculties/faculties/facultiesinfo/department?RID=testing_reports&id=6

Note: Above results pertain to the unsealed samples supplied to the laboratory

The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients). The test results are recommended to be interpreted in the light of above factors by the engineer.

supervisor(lab)

^{*} as engraved on the specimens (if any)

^{**} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength