

**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895



2236 Dr. Mazhar

Test Specification

To: (Tougeer Afzal), XEN

GE (Army) Const LRC

Project: Const of CT Angio Complex at CMH, LHR, Cantt-CA No. CEA-CZ-01/2021

Our Ref. No. CL/0	CED/ 6447	Dated:	24-11-21	
Your Ref. No.	754/88/E6	Dated:	13-10-21	

## **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

22-11-21 in dry/wet condition Specimens received on: 10-11-21 Tested on:

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Plinth Beam (3000psi)	18	9	2021	6Diax12		13.2	28.28	51	4040		Non Engraved
2	Plinth Beam (3000psi)	18	9	2021	6Diax12		14	28.28	59	4673		Non Engraved
3	Plinth Beam (3000psi)	18	9	2021	6Diax12		14	28.28	41	3248		Non Engraved
4												
5												
6												
7												
8												
9			-									
10			1									
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895



2236 Dr. Mazhar

Test Specification

To: (Tougeer Afzal), XEN

GE (Army) Const LRC

Project: Const of CT Angio Complex at CMH, LHR, Cantt-CA No. CEA-CZ-01/2021

Our Ref. No. CL/CED/ 6448	Dated:	24-11-21
Your Ref. No. 754/92/E6	Dated:	01-11-21

## **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

22-11-21 in dry/wet condition Specimens received on: 10-11-21 Tested on:

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Walls CT Scan Room (4000psi)	4	10	2021	6Diax12		13	28.28	61	4832	-	Non Engraved
2	Walls CT Scan Room (4000psi)	4	10	2021	6Diax12		13	28.28	55	4356		Non Engraved
3	Walls CT Scan Room (4000psi)	4	10	2021	6Diax12		13	28.28	53	4198		Non Engraved
4												
5			1								1	
6												
7											-	
8												
9												
10											-	
11												
12												
13												
14												
15				-								
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895



2263 Dr. Mazhar

Test Specification

To: Engr Muhammad Salman

Assistant Resident Engineer (Contractor; M/S CBS)

Project: Construction of Jewel-1 Apartment Plaza at Gulberg-III, LHR

Our Ref. No. CL/C	ED/ 6449	Dated:	24-11-21
Your Ref. No.	DOC#ARST-0014	Dated:	16-11-21

## **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-11-21 Tested on: 22-11-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	мм	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	GFS-1 (Grid A~G/1- 10)	6	10	2021	6Diax12		14	28.28	39	3089	-	Engraved
2	GFS-2 (Grid A~G/1- 10)	6	10	2021	6Diax12		14.2	28.28	49	3881		Engraved
3	GFS-3 (Grid A~G/1- 10)	6	10	2021	6Diax12		14	28.28	45	3564		Engraved
4	GFS-4 (Grid A~G/1- 10)	6	10	2021	6Diax12		14.4	28.28	41	3248		Engraved
5	GFS-5 (Grid A~G/1- 10)	6	10	2021	6Diax12		14.2	28.28	37	2931	1	Engraved
6	GFS-6 (Grid A~G/1- 10)	6	10	2021	6Diax12		14.4	28.28	55	4356		Engraved
7		-										
8		-										
9			-									
10		-	1									
11		-										
12		-										
13		-										
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895



2263 Dr. Mazhar

Test Specification

To: Engr Muhammad Salman

Assistant Resident Engineer (Contractor; M/S CBS)

Project: Construction of Jewel-1 Apartment Plaza at Gulberg-III, LHR

Our Ref. No. CL/C	ED/ 6450	Dated:	24-11-21	
Your Ref. No.	DOC#ARST-0015	Dated:	16-11-21	_

## **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-11-21 Tested on: 22-11-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	FFC-1 (Grid A~G/1- 10)	16	10	2021	6Diax12		13.6	28.28	57	4515	1	Engraved
2	FFC-2 (Grid A~G/1- 10)	16	10	2021	6Diax12		14.2	28.28	51	4040		Engraved
3	FFC-3 (Grid A~G/1- 10)	16	10	2021	6Diax12		14	28.28	63	4990		Engraved
4												
5												
6												
7		-	-									
8		-	-									
9			-									
10		-	-									
11		-										
12		-	-									
13		-	-									
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895



2314 Dr. Umbreen

Test Specification

To: (Mr. Khalid Bashir)

Ittefaq Building Solutions Pvt Ltd.

Project: New Apparel Facility, Ferozwatwan. (IBS/L-0054, Social Block Slab).

Our Ref. No. CL/0	ED/ 6451	Dated:	24-11-21	
Your Ref. No.	IBS/SD/CT-13	Dated:	23-11-21	

## **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 23-11-21 Tested on: 24-11-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	мм	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (78)	
1	3000 Psi	23	10	2021	6Diax12		13	28.28	81	6416		Engraved
2	3000 Psi	23	10	2021	6Diax12		13.4	28.28	75	5941		Engraved
3	3000 Psi	23	10	2021	6Diax12		13.4	28.28	83	6574		Engraved
4			-									
5					-							
6		-	-									
7		-	-									
8		-	-									
9			-									
10		-	-									
11												
12		-	-									
13		-	-									
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL
A carbon copy for
the report has
been retained in
the lab for record.

2314 Dr. Umbreen

**Test Specification** 

To: (Mr. Khalid Bashir)

Ittefaq Building Solutions Pvt Ltd.

Project: New Apparel Facility, Ferozwatwan. (IBS/L-0056, Apparel Building RCC Columns).

Our Ref. No. CL/CED/ 6452	Dated:	24-11-21	
Your Ref. No. IBS/SD/CT-14	Dated:	23-11-21	

## **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

24-11-21 in dry/wet condition Specimens received on: 23-11-21 Tested on:

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	ΥΥΥΥ	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (70)	
1	4000 Psi	24	10	2021	6Diax12		13	28.28	81	6416		Engraved
2	4000 Psi	24	10	2021	6Diax12		13.4	28.28	83	6574		Engraved
3	4000 Psi	24	10	2021	6Diax12		13.8	28.28	104	8238		Engraved
4												
5											1	
6		-	-									
7		-	-									
8		-	-									
9			-									
10		-	-									
11												
12		-	-									
13		-	-									
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895



2303 Dr. Umbreen

(----)

To: (Mr. Sarfraz Rasheed) GM Projects Ittefaq Building Solutions (Pvt) Ltd.

Project: Fauji Fresh n Freeze-Sahiwal.

Our Ref. No. CL/CED/ 6453

Your Ref. No. Nil

## COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	2	2-11	-21	Tested on:	24-'	11-21	in dry/we	t condition			
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti on (%)	Remarks
1	Rectangular, Grey,				7.7x3.8x3.0	(r.g/ gills) 	(Rg/ gills) 3290	29.26	51	(psi) 3904		
2	Rectangular, Grey, 80 mm				7.7x3.8x3.0		3385	29.26	75	5742		
3	Rectangular, Grey, 80 mm				7.7x3.8x3.0		3505	29.26	59	4517		
4												
5												
6												
7												
8		1										
9												
10		-										
11												
12		-										
13												
14												
15												
16												

#### Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

24-11-21 22-11-21

Dated:

Dated:



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL
A carbon copy fo
the report has
been retained in
the lab for record

2296 Dr. Umbreen

Test Specification

To: Mr. Adnan Baig

Wali Constructions, Shalimar Link Road, Lahore.

Project: Nil		
Our Ref. No. CL/CED/ 6454	Dated:	24-11-21
Your Ref. No. Nil	Dated:	19-11-21

## **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

24-11-21 in dry/wet condition Specimens received on: 19-11-21 Tested on:

Sr. No.	Mark*	Cas DD	ting MM	Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Ka/ ams)	Area of X-Section (Sg. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1		16	3	2021	6Diax12		13.6	28.28	59	4673		Non Engraved
2												
3												
4												
5			-									
6		-	1									
7			-									
8			-									
9			-									
10												
11			-									
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895



2284 Dr. Mazhar

Test Specification (----)

To: Sub Divisional Officer

Public Health Engineering Sub Division Kamalia.

Project: Provision of Tuff Tiles / PCC and Sewerage in Pir Mahal City, District T.T.Singh.

Our Ref. No. CL/CED/ 6455	Dated:	24-11-21
Your Ref. No. 163/K	Dated:	15-11-21

### **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-11-21 Tested on: 22-11-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti	Remarks
		DD	мм	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Rectangular, Grey, 60 mm				7.7x3.8x2.3		2630	29.26	102	7809		
2	Rectangular, Grey, 60 mm				7.7x3.8x2.3		2620	29.26	110	8421		
3	Rectangular, Grey, 60 mm				7.7x3.8x2.3		2590	29.26	86	6584		
4	Rectangular, Grey, 60 mm				7.7x3.8x2.3		2655	29.26	116	8880		
5												
6		1										
7												
8												
9		-									-	
10		1										
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL
A carbon copy fo
the report has
been retained in
the lab for record

2287 Dr. Umbreen

To: Mr. Ali Raza, QA/QC EEPL Elite Engineering Pvt. Ltd.

> Project: Al Khair Rice Mill Renala. Our Ref. No. CL/CED/ 6456 Dated: Your Ref. No. Nil Dated:

24-11-21 19-11-21

Test Specification (----)

## **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

24-11-21 in dry/wet condition Specimens received on: 19-11-21 Tested on:

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Rectangular, Grey, 80 mm				7.7x3.8x3.1		3465	29.26	83	6354		
2	Rectangular, Grey, 80 mm				7.7x3.8x3.1		3540	29.26	102	7809		
3	Rectangular, Grey, 80 mm				7.7x3.8x3.1		3420	29.26	63	4823		
4	Rectangular, Grey, 80 mm				7.7x3.8x3.1		3450	29.26	75	5742		
5	Rectangular, Grey, 80 mm	1			7.7x3.8x3.1		3655	29.64	88	6650		
6	Rectangular, Grey, 80 mm	1			7.7x3.8x3.1		3500	29.64	86	6499		
7		-										
8		1										
9		1										
10		1									-	
11		I									-	
12		I									-	
13		I									-	
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895



2288 Dr. Umbreen

Test Specification

To: Sub Divisional Officer

Buildings Sub Division No.22, Lahore.

Project: Up-Gradation and Development of Shrine of Hazrat Bibi Pak Daman, Lahore.

Our Ref. No. CL/CED/ 6457	Dated:	24-11-21
Your Ref. No. 269/22nd	Dated:	17-11-21

## **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19-11-21 Tested on: 24-11-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	ΥΥΥΥ	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (70)	
1	RCC (1:2:4)	17	10	2021	6x6x6		8.4	36	81	5040		Engraved
2	RCC (1:2:4)	17	10	2021	6x6x6		8.6	36	67	4169		Engraved
3	RCC (1:2:4)	17	10	2021	6x6x6		8.2	36	79	4916		Engraved
4	RCC (1:1.5:3)	19	10	2021	6x6x6		8.2	36	98	6098		Engraved
5	RCC (1:1.5:3)	19	10	2021	6x6x6		8.2	36	114	7093		Engraved
6												
7												
8												
9			-									
10			1									
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895



2300 Dr. Umbreen

Test Specification (----)

To: Sub Divisional Officer

Highway Sub Division No.01, Lahore.

Project: Rehabilitation of Carpet Road in UC 86, 87, 88 in NA-130, Lahore.

Our Ref. No. CL/C	ED/ 6458	Dated:	24-11-21	
Your Ref. No.	265-SDO-1	Dated:	20-11-21	

## **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 22-11-21 Tested on: 24-11-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Rectangular, Grey, 80 mm				7.8x3.8x3.0		3745	29.64	79	5970		
2	Rectangular, Grey, 80 mm				7.8x3.8x3.0		3690	29.64	96	7255		
3	Rectangular, Grey, 80 mm				7.8x3.8x3.0		3655	29.64	100	7557	-	
4	Rectangular, Grey, 80 mm				7.8x3.8x3.0		3670	29.64	104	7860	-	
5												
6												
7											-	
8											-	
9												
10												
11											-	
12											-	
13											-	
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

\*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
\*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)