

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2122 Engr. Ubaid

Test Specification

**Sub Divisional Officer** 

Highway Sub Division No. 1, Lahore

Project:Rehabilitation of Carpet Road in UC 86,87,88 in NA-130 Lahore

Our Ref. No. CL/CED/ 6230 Dated: 28-10-21 Your Ref. No.

198/SDO-I Dated: 18-10-21 BS 1881-116)

# **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-10-21 Tested on: 28-10-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Plain Cement Concrete	6	10	2021	6x6x6		9	36	65	4044		Non Engraved
2	Plain Cement Concrete	6	10	2021	6x6x6		9	36	67	4169		Non Engraved
3	Plain Cement Concrete	6	10	2021	6x6x6		8.8	36	65	4044		Non Engraved
4	Plain Cement Concrete	6	10	2021	6x6x6		8.8	36	70	4356		Non Engraved
5												
6												
7										I		
8										I		
9							-		-	I		
10							-			I	-	
11										I		
12										I		
13										I		
14										1		
15										-		
16					-		1			1		
\A/:4	and have											

## Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2097 Eng. Ubaid

Resident Engineer

**Engineering Services Consultants** 

Project: Establishment of Excellence Boys at Chakwal

Our Ref. No. CL/CED/ 6231 Dated: 28-10-21

Your Ref. No. RE/ESC/CEO/2021-08 Dated: 13-10-21 Test Specification ( BS 3921\*\* )



# **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14-10-21 Tested on: 28-10-21 in dry/wet condition

Sr. No.	Mark*		_	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	15			-	8.7 x 4.3 x 2.8	3089	2670	37.41	44	2635	15.69	
2	15				8.5 x 4.2 x 2.7	2984	2590	35.7	30	1882	15.21	
3	15				8.6 x 4.2 x 2.7	2939	2550	36.12	36	2233	15.25	
4	15			-	8.7 x 4.3 x 2.8	3089	2680	37.41	50	2994	15.26	
5	15			-	8.7 x 4.3 x 2.7	2891	2470	37.41	28	1677	17.04	
6	15				8.7 x 4.3 x 2.7	3120	2725	37.41	28	1677	14.5	
7	15				8.7 x 4.3 x 2.8	3030	2615	37.41	42	2515	15.87	
8										-		
9			-	-	-		-		-	-		-
10			-	-			-			-		-
11			-									
12			-									
13												
14			-									
15			-									
16												

## Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

28-10-21

2115 Eng. Ubaid

Test Specification

( BS 3921\*\* )

Project Manager

Q-Links Property Management Pvt. Ltd.

Project:Jasmine Villas, Bahria Orchard, Lahore

Our Ref. No. CL/CED/ 6232 Dated:

Your Ref. No. QLC-BO-BH2-2021-076 Dated: 14-10-21

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-10-21 Tested on: 28-10-21 in dry/wet condition

-								•				
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Water Absorpti	Remarks
		DD	мм	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)		on (%)	
1	мс				8.8 x 4.4 x 3		3230	38.72	50	2893		
2	Machine Made				8.8 x 4.2 x 2.8		3085	36.96	40	2424		
3	s				8.9 x 4.3 x 2.8		3040	38.27	44	2575		
4	s				8.7 x 4.2 x 2.8		2930	36.54	42	2575		
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16					-							
Witness	ed by:						<del>-</del>	<del>-</del>			<del>-</del>	

### Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2117 Engr. Ubaid

Haris Ali, Model Town, Islamabad.

Project: Raya Villa, 118, DRGCC, Lahore

Our Ref. No. CL/CED/ 6233 Dated: 28-10-21 Your Ref. No. Dated: 18-10-21 Test Specification ( ASTM C39 )



### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-10-21 Tested on: 28-10-21 in dry/wet condition

Sr. No.	Mark*		_	Date*	Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks					
				YYYY	. ,	(Kg/ gms)	(Kg/ gms)		(Imp.Tons)		. ()						
1	3000 Psi	17	9	2021	6Diax12		13.4	28.28	13	1030		Engraved					
2	3000 Psi	17	9	2021	6Diax12		13.4	28.28	19.5	1545		Engraved					
3							-										
4							I										
5							-				-						
6																	
7																	
8																	
9							I										
10																	
11																	
12																	
13																	
14																	
15				-													
16					-												
Witness	sed by:				Witnessed by:												

### Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2121 Engr. Ubaid

Muhammad Azeem, Operation Manager

Amer Adnan Associates, #17-E-II, Gulberg III, Lahore.

Project: Hotel Building at 24-A Block E/2, Gulberg III, Lahore.

Our Ref. No. CL/CED/ 6234 Dated: 28-10-21

Your Ref. No. AAA/24A/0055 Dated: 18-10-21 Test Specification ( ASTM C39 )



# **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-10-21 Tested on: 28-10-21 in dry/wet condition

Engraved Engraved
Engraved 
-
-
-
-
-
-
-
1

## Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2124 Engr. Ubaid

**Project Manager** 

Q-Links Property Management Pvt. Ltd.

Project: Orchard Mall, Bahria Orchard Lahore. (Slab Over 1st Floor Grid # 0-7)

Our Ref. No. CL/CED/ 6235 Dated: 28-10-21 Your Ref. No. QLC-BO-BH2-2021-079 Dated: 18-10-21

Test Specification ( ASTM C39 )



# **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-10-21 Tested on: 28-10-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	5000 Psi	18	9	2021	6Diax12		13.4	28.28	35	2772		Non Engraved
2	5000 Psi	18	9	2021	6Diax12		13.2	28.28	37	2931		Non Engraved
3	5000 Psi	18	9	2021	6Diax12		13.4	28.28	36	2851		Non Engraved
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14					-		-			-		
15												
16												

## Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2123 Engr. Ubaid

Project Manager

Q-Links Property Management Pvt. Ltd.

Project: Jasmine Grand Mall, Bahria Town Lahore

28-10-21 Our Ref. No. CL/CED/ 6236 Dated: Your Ref. No. QLC-BO-BH2-2021-078 Dated: 18-10-21

Test Specification ( ASTM C39 )



# **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-10-21 Tested on: 28-10-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Retaining Wall Grid #16-18 D-E	21	9	2021	6Diax12		13.4	28.28	38	3010		Engraved
2	Retaining Wall Grid #16-18 D-E	21	9	2021	6Diax12		13	28.28	41	3248		Engraved
3	Retaining Wall Grid #16-18 D-F	21	9	2021	6Diax12		13.8	28.28	42	3327		Engraved
4	Retaining Wall Grid #14-16 F	24	9	2021	6Diax12		14	28.28	62	4911		Engraved
5	Retaining Wall Grid #14-16 F	24	9	2021	6Diax12		14	28.28	57	4515	-	Engraved
6	Retaining Wall Grid #14-16 E	24	9	2021	6Diax12		13	28.28	59	4673		Engraved
7												
8												
9		-	-				1	-		I		
10		-	-				I			ł	-	
11												
12												
13		-	-				-	-		1		
14							1	-		1		
15										-		
16												
\A/:4	d b			-							-	

### Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2151 Engr. Ubaid

Test Specification

BS 1881-116)

Umair Magsood, Sub Divisional Officer.

Buildings Sub Division, Assembly, Lahore.

Project: Construction of MPA Hostel (Phase-II) Lahore (Group No.2)

Our Ref. No. CL/CED/ 6237 Dated: 28-10-21

Your Ref. No. 774 Dated: 18-10-21

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 26-10-21 Tested on: 28-10-21 in dry/wet condition

•	!					l						
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Emergency Stair Lower Basement	8	9	2021	6x6x6		8.8	36	37	2302		Non Engraved
2	Emergency Stair Lower Basement	8	9	2021	6x6x6		8.2	36	37	2302		Non Engraved
3							-			-		
4							I			1		
5							I			1		
6							-					
7												
8												
9												-
10												
11												
12												
13												
14							-					
15												-
16											-	
Witness	sed by:											

### Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1.The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2151 Engr. Ubaid

**Umair Magsood, Sub Divisional Officer** 

**Buildings Sub Division, Assembly, Lahore** 

Project:Construction of Hostel MPA (Phase-II) Lahore (Group No.2)

Our Ref. No. CL/CED/ 6238 Dated: 28-10-21 Your Ref. No. 775 Dated: 18-10-21

Test Specification BS 1881-116)



# **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 26-10-21 Tested on: 28-10-21 in dry/wet condition

Sr. No.	Mark*		_	Date*	Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (%)	
1	Upper Basement Raise Portion Slab	18	9	2021	6x6x6		9	36	132	8213		Non Engraved
2	Upper Basement Raise Portion Slab	18	9	2021	6x6x6		9	36	116	7218		Non Engraved
3												
4												
5												
6												
7		-										
8		-	-									
9		-										-
10		1	ł				-			I	-	-
11		-	-									
12		-										
13			1							-		
14			I		-		-			1	-	-
15												
16			-									

## Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1.The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2150 Engr. Ubaid

**Test Specification** 

BS 1881-116)

**Sub Divisional Officer** 

Maintenance Sub Division No-III, GRO-II, Lahore

Project:Construction of Multistory Flats/Suites for Officers of P&D and S&GAD in GOR-III, Shadman, Lahore

Our Ref. No. CL/CED/ 6239 Dated: 28-10-21

Your Ref. No. 650 Dated: 06-10-21

# **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 26-10-21 Tested on: 28-10-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight		Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	GOR-III Flats 4th Floor Slab	27	8	2021	6x6x6		9	36	95	5911		Engraved
2	GOR-III Flats 4th Floor Slab	27	8	2021	6x6x6		8.6	36	94	5849		Engraved
3	GOR-III Flats 4th Floor Slab	27	8	2021	6x6x6		8.4	37	94	5691		Engraved
4												
5												
6												
7												
8			-									
9			-				-			1	-	-
10							-			-		
11												
12										-		
13												
14												
15												
16					-		1					-

## Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2144 Engr. Ubaid

To: Riasat Ali

Style Textile (PVT) Ltd.

Project:Style P3 SAP Project

Our Ref. No. CL/CED/ 6240 Dated: 28-10-21

Your Ref. No. ASE Dated: 21-10-21 Test Specification

BS 1881-116)

### **COMPRESSION TEST REPORT**

### Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

28-10-21 in dry/wet condition Specimens received on: 25-10-21 Tested on:

Mark*		_		Size	Wet Weight				Ultimate Stress	Absorpti	Remarks
C-20 Drain				. ,				, ,			Non Engraved
0-20 Brain			2021	0,0,0				- 30	0030		Non Englaved
C-20 Drain	22	9	2021	6x6x6		8.6	36	95	5911		Non Engraved
C-20 Drain	22	9	2021	6x6x6		8.8	36	75	4667		Non Engraved
C-30 Raft	22	9	2021	6x6x6		8.8	36	91	5662		Non Engraved
C-30 Raft	22	9	2021	6x6x6		8.6	36	89	5538		Non Engraved
C-30 Raft	22	9	2021	6x6x6		8.4	36	98	6098		Non Engraved
C-35 Column	22	9	2021	6x6x6		8.8	36	100	6222		Non Engraved
C-35 Column	22	9	2021	6x6x6		8.6	36	115	7156		Non Engraved
C-35 Column	22	9	2021	6x6x6		9	36	93	5787		Non Engraved
	-		-								
	-		-								
				-		ŀ			-		
				-							
	C-20 Drain C-20 Drain C-20 Drain C-30 Raft C-30 Raft C-30 Raft C-35 Column C-35 Column C-35 Column	Mark* DD C-20 Drain 22 C-20 Drain 22 C-20 Drain 22 C-30 Raft 22 C-30 Raft 22 C-30 Raft 22 C-35 Column 22 C-35 Column 22 C-35 Column 22	Mark* DD MM  C-20 Drain 22 9  C-20 Drain 22 9  C-20 Drain 22 9  C-30 Raft 22 9  C-30 Raft 22 9  C-30 Raft 22 9  C-35 Column 22 9  C-35 Column 22 9  C-35 Column 22 9	DD MM YYYYY C-20 Drain 22 9 2021 C-20 Drain 22 9 2021 C-20 Drain 22 9 2021 C-30 Raft 22 9 2021 C-30 Raft 22 9 2021 C-30 Raft 22 9 2021 C-35 Column 22 9 2021	Mark* DD MM YYYY (in)  C-20 Drain 22 9 2021 6x6x6  C-20 Drain 22 9 2021 6x6x6  C-20 Drain 22 9 2021 6x6x6  C-30 Raft 22 9 2021 6x6x6  C-35 Column 22 9 2021 6x6x6	Mark*         Casting Date*         Size         Weight           DD MM YYYY         (in)         (Kg/ gms)           C-20 Drain         22         9         2021         6x6x6            C-20 Drain         22         9         2021         6x6x6            C-30 Raft         22         9         2021         6x6x6            C-30 Raft         22         9         2021         6x6x6            C-30 Raft         22         9         2021         6x6x6            C-35 Column         22         9         2021         6x6x6            C-35 Column         22         9         2021         6x6x6                          C-35 Column         22         9         2021         6x6x6	Mark*         Casting Date*         Size         Weight         Weight           C-20 Drain         22         9         2021         6x6x6          9           C-20 Drain         22         9         2021         6x6x6          8.6           C-20 Drain         22         9         2021         6x6x6          8.8           C-30 Raft         22         9         2021         6x6x6          8.6           C-30 Raft         22         9         2021         6x6x6          8.6           C-35 Column         22         9         2021         6x6x6          8.8           C-35 Column         22         9         2021         6x6x6          8.6           C-35 Column         22         9         2021         6x6x6          8.6           C-35 Column         22         9         2021         6x6x6          9	Mark*         Casting Date*         Size         Weight (Kg/ gms)         Weight (Kg/ gms)         X-Section (Sq. in)           C-20 Drain         22         9         2021         6x6x6          9         36           C-20 Drain         22         9         2021         6x6x6          8.6         36           C-20 Drain         22         9         2021         6x6x6          8.8         36           C-30 Raft         22         9         2021         6x6x6          8.8         36           C-30 Raft         22         9         2021         6x6x6          8.6         36           C-30 Raft         22         9         2021         6x6x6          8.4         36           C-35 Column         22         9         2021         6x6x6          8.6         36           C-35 Column         22         9         2021         6x6x6          8.6         36           C-35 Column         22         9         2021         6x6x6          9         36 <td>Mark*         Casting Date*         Size         Weight (Kg/gms)         X-Section (Sq. in)         load (Imp.Tons)           C-20 Drain         22         9         2021         6x6x6          9         36         98           C-20 Drain         22         9         2021         6x6x6          9         36         98           C-20 Drain         22         9         2021         6x6x6          8.6         36         95           C-20 Drain         22         9         2021         6x6x6          8.8         36         75           C-30 Raft         22         9         2021         6x6x6          8.8         36         91           C-30 Raft         22         9         2021         6x6x6          8.4         36         98           C-35 Column         22         9         2021         6x6x6          8.6         36         115           C-35 Column         22         9         2021         6x6x6          9         36         93                 -</td> <td>Mark*         Casting Date*         Size         Weight (Kg/gms)         Weight (Kg/gms)         X-Section (Sq. in)         load (Imp.Tons)         Stress (psi)           C-20 Drain         22         9         2021         6x6x6          9         36         98         6098           C-20 Drain         22         9         2021         6x6x6          8.6         36         95         5911           C-20 Drain         22         9         2021         6x6x6          8.8         36         75         4667           C-30 Raft         22         9         2021         6x6x6          8.8         36         91         5662           C-30 Raft         22         9         2021         6x6x6          8.6         36         89         5538           C-35 Column         22         9         2021         6x6x6          8.8         36         100         6222           C-35 Column         22         9         2021         6x6x6          8.6         36         93         5787               </td> <td>Mark*         Casting Date* DD MM YYYY         Size Weight (in)         Weight (Kg/gms) (Kg/gms)         X-Section (sq. in)         load (lmp.Tons) (psi)         Water Absorption (%) on (%)           C-20 Drain         22         9         2021         6x6x6          9         36         98         6098            C-20 Drain         22         9         2021         6x6x6          8.6         36         95         5911            C-20 Drain         22         9         2021         6x6x6          8.8         36         75         4667            C-30 Raft         22         9         2021         6x6x6          8.8         36         91         5662            C-30 Raft         22         9         2021         6x6x6          8.6         36         89         5538            C-30 Raft         22         9         2021         6x6x6          8.8         36         100         6222            C-35 Column         22         9         2021         6x6x6          8.6         36         93         5787</td>	Mark*         Casting Date*         Size         Weight (Kg/gms)         X-Section (Sq. in)         load (Imp.Tons)           C-20 Drain         22         9         2021         6x6x6          9         36         98           C-20 Drain         22         9         2021         6x6x6          9         36         98           C-20 Drain         22         9         2021         6x6x6          8.6         36         95           C-20 Drain         22         9         2021         6x6x6          8.8         36         75           C-30 Raft         22         9         2021         6x6x6          8.8         36         91           C-30 Raft         22         9         2021         6x6x6          8.4         36         98           C-35 Column         22         9         2021         6x6x6          8.6         36         115           C-35 Column         22         9         2021         6x6x6          9         36         93                 -	Mark*         Casting Date*         Size         Weight (Kg/gms)         Weight (Kg/gms)         X-Section (Sq. in)         load (Imp.Tons)         Stress (psi)           C-20 Drain         22         9         2021         6x6x6          9         36         98         6098           C-20 Drain         22         9         2021         6x6x6          8.6         36         95         5911           C-20 Drain         22         9         2021         6x6x6          8.8         36         75         4667           C-30 Raft         22         9         2021         6x6x6          8.8         36         91         5662           C-30 Raft         22         9         2021         6x6x6          8.6         36         89         5538           C-35 Column         22         9         2021         6x6x6          8.8         36         100         6222           C-35 Column         22         9         2021         6x6x6          8.6         36         93         5787	Mark*         Casting Date* DD MM YYYY         Size Weight (in)         Weight (Kg/gms) (Kg/gms)         X-Section (sq. in)         load (lmp.Tons) (psi)         Water Absorption (%) on (%)           C-20 Drain         22         9         2021         6x6x6          9         36         98         6098            C-20 Drain         22         9         2021         6x6x6          8.6         36         95         5911            C-20 Drain         22         9         2021         6x6x6          8.8         36         75         4667            C-30 Raft         22         9         2021         6x6x6          8.8         36         91         5662            C-30 Raft         22         9         2021         6x6x6          8.6         36         89         5538            C-30 Raft         22         9         2021         6x6x6          8.8         36         100         6222            C-35 Column         22         9         2021         6x6x6          8.6         36         93         5787

## Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1.The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 A carbon copy for the report has been retained in

> 2109 Eng. Ubaid

Mr. Hafiz Ozair Ahmad,

Deputy Director (QCD) WASA, LDA, Lahore

Project: Tender No. P&S/25.01/6341. Construction of Lift Station at Tallat Park, Shaheenabad and Adjoining

Abadies, Alongwith Sewerage System and PCC in Streets Lahore. (M/s PACON International).

Our Ref. No. CL/CED/ 6241 Dated: 28-10-21

14-10-21 Your Ref. No. NO.QCD/1436-37 Dated:

Test Specification

( BS 3921\*\* )

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-10-21 Tested on: 28-10-21 in dry/wet condition

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	NO.1				8.9 x 4.3 x 2.9	3684	3345	38.27	70	4097	10.13	
2	NO.1		ł		8.8 x 4.3 x 2.9	3665	3325	37.84	52	3078	10.23	
3	NO.1		ł		8.9 x 4.3 x 3.1	3881	3530	38.27	58	3395	9.94	
4	NO.1				8.8 x 4.2 x 2.9	3692	3350	36.96	49	2970	10.21	-
5	NO.1		ł	-	8.8 x 4.3 x 3	3752	3410	37.84	40	2368	10.03	
6	NO.1		-	-	8.9 x 4.2 x 3	3728	3390	37.38	44	2637	9.97	
7			ł							-		
8			ł							-		
9			ł	-			I			-		
10			1	-			-			-	-	
11			ł							-		
12			ł							-		
13			I									
14			1	-			-			-	-	
15			ł									
16			I		-							
Witness	ed by:											

### Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
  4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)