

## **Plain and Reinforced Concrete Laboratory Civil Engineering Department**

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

> 3067 & 3070 Dr. Aqsa

To: Mr. Sohail Anjum, Project Manager

MS Tower Developers, J4 Lahore.

Project: Construction of MS Tower at Plot 450, 451 Johar Town, Lahore.

Our Ref. No. CL/CED/ 8483 Dated: 05-04-22 **Test Specification** ( ASTM C39 )

Your Ref. No. MST/UET/2022/001 Dated: 04-04-22

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 04-04-22 Tested on: 05-04-22 in dry/wet condition





Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	3000 Psi	25	3	2022	6Diax12		13.2	28.28	26	2059		Non Engraved
2	3000 Psi	25	3	2022	6Diax12		12.8	28.28	34	2693		Non Engraved
3												
4							-					
5					/	GINE	RINE					
6						READIN	200					
7						DHE NAME OF THY LIDRO WHO	-E					
8					SS			ONI				
9						) <u> </u>						
10						"-LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

**Note:** Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



## Plain and Reinforced Concrete Laboratory Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

> 3067 & 3070 Dr. Aqsa

To: Mr. Sohail Anjum, Project Manager

MS Tower Developers, J4 Lahore.

Project: Construction of MS Tower at Plot 450, 451 Johar Town, Lahore.

Our Ref. No. CL/CED/ 8484 Dated: 05-04-22 <u>Test Specification</u>

Your Ref. No. MST/UET/2022/002 Dated: 04-04-22 (ASTM C39)

## **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 04-04-22 Tested on: 05-04-22 in dry/wet condition





<del></del>								,				
Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD MM YYYY			(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	3000 Psi	26	3	2022	6Diax12		13.2	28.28	27	2139		Non Engraved
2	3000 Psi	26	3	2022	6Diax12		12.4	28.28	15	1188		Non Engraved
3	3000 Psi	26	3	2022	6Diax12		13	28.28	23	1822		Non Engraved
4												
5					/	MAINE	RING					
6						READIN	200					
7						DE NAME OF THY LORD WHO	- N	=				
8					- 00	رقتال	E ST	<u> </u>				
9					\		9	7				
10					(	-UA	IOR'S					
11												
12												
13												
14												
15												
16												
Nation and but												

Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

**Note:** Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.