

ORIGINAL A carbon copy for the report has been retained in the lab for record.

4353 Dr. Umbreen

To: Mr. M. Afzal, Site Engineer M/S Linker

Project: Construction of Hassan & Huma Residence-DHA Phase VIII, Sector-A, Lahore.

Our Ref. No. CL/	CED/ 573	Dated:	08-12-22	Test Specification
Your Ref. No.	LD/H&H/444-A/C-01	Dated:	05-12-22	( ASTM C39 )

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	5/	/12/2	022	Tested on:	08-1	12-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate Ioad (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Basement Slab (3000 Psi)	29	10	2022	6Diax12		13	28.28	47	3723		Non Engraved
2	Basement Slab (3000 Psi)	29	10	2022	6Diax12		13	28.28	33	2614		Non Engraved
3												
4												
5					/	HINE	RINE					
6					>	T READ IN	2015					
7						DHE NAME OF THY LORD WHO	- F	EB-				
8								Han				
9							-					
10					<	[A	INK- ·					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil											

#### messeu by.

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

### **Director/Dy. Director Concrete Laboratory**



### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

SA-466F/103/GH/ML/Lab/56

Specime	ens received on:	0	6-12	-22	Tested on:	08-	12-22	in dry/we	t condition			
Sr. No.	Mark*	Cas DD	•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(1:1.5:3)	26	10	2022	6x6x6		8.4	36	94	5849		Non Engraved
2	(1:1.5:3)	26	10	2022	6x6x6		8.4	36	134	8338		Non Engraved
3	(1:1.5:3)	26	10	2022	6x6x6		8.4	36	138	8587		Non Engraved
4	(1:1.5:3)	30	10	2022	6x6x6		8.4	36	92	5724		Non Engraved
5	(1:1.5:3)	30	10	2022	6x6x6 🧹	GINE	8.8	36	75	4667		Non Engraved
6	(1:1.5:3)	30	10	2022	6x6x6	READIN	8.4	36	94	5849		Non Engraved
7	(1:1.5:3)	31	10	2022	6x6x6	CORD VAR	8.4	36	104	6471		Non Engraved
8	(1:1.5:3)	31	10	2022	6x6x6		8.6	36	94	5849		Non Engraved
9	(1:1.5:3)	31	10	2022	6x6x6	à	8.6	36	88	5476		Non Engraved
10	(1:2:4)	26	10	2022	6x6x6 🤇	-LA	8.6	36	73	4542		Non Engraved
11	(1:2:4)	26	10	2022	6x6x6		8.6	36	71	4418		Non Engraved
12	(1:2:4)	26	10	2022	6x6x6		8.8	36	81	5040		Non Engraved
13	(1:2:4)	31	10	2022	6x6x6		8.4	36	88	5476		Non Engraved
14	(1:2:4)	31	10	2022	6x6x6		8.4	36	86	5351		Non Engraved
15	(1:2:4)	31	10	2022	6x6x6		8.4	36	81	5040		Non Engraved
16												
Vitness	ed by: Nil			1		•		•		I	L1	

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

Your Ref. No.

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

19/11/2022

(BS 1881-116)

Dated:



ORIGINAL
A carbon copy for
the report has
been retained in
the lab for record.

4369 Dr. Umbreen

To: Prof. Dr. Engr. Abdullah Yasar Campus Engineer, GC University, Lahore.

Project: Construction of New Girls Hostel at GCU Lahore Main Campus.

Our Ref. No. CL/	(CED/ 575	Dated:	08-12-22	Test Specification
Your Ref. No.	GCU/Engr/2099/P	Dated:	Nil	( BS 1881-116 )

### COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	7-12	-22	Tested on:	08-1	2-22	in dry/wet condition				
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(1:2:4)	4	11	2022	6x6x6		8.8	36	100	6222		Engraved
2	(1:2:4)	4	11	2022	6x6x6		8.8	36	98	6098		Engraved
3	(1:2:4)	4	11	2022	6x6x6		8.8	36	90	5600		Engraved
4												
5					/	RINE	RINE					
6						READIN						
7						DHE NHOLE OE THY LORD VIND	149	EB				
8					188		T	i Ma				
9						-	ł					
10						(A	R					
11							.I					
12												
13												
14												
15												
16												
Witness	ed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory

	Plain and Reinforced Conc Civil Engineering Depar University of Engineering and Technology, I Landline: 042-99029245 & 042-99029202	ment	2	ORIGINAL A carbon copy for the report has been retained in the lab for record.
				4369 Dr. Umbreen
То:	Mr. Malik Abdul Rauf Assistant Engineer (Technical), GC University, Lahore			
	Project: Construction of Sheikh Abdul Hassan Al-Shadhili Re Technology GC University Kala Shah Kaku Campus, Lahore. Our Ref. No. CL/CED/ 576	search Centre on S Dated:	Sufism, Science & 08-12-22	Test Specification

# **COMPRESSION TEST REPORT**

(BS 1881-116)

06-12-22

Dated:

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

GCU/Engr/3000/P

Specim	ens received on:	0	7-12	-22	Tested on:	08-1	2-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)		Water Absorpti on (%)	Remarks
1	(1:2:4)	7	11	2022	6x6x6		8.4	36	57	3547		Engraved
2	(1:2:4)	7	11	2022	6x6x6		8.4	36	73	4542		Engraved
3	(1:2:4)	7	11	2022	6x6x6		8.8	36	73	4542		Engraved
4												
5					/	GINE	RIATE					
6					- )	T NEAD IN	(FIRE )					
7					11	DIE NICOE COE THY LORD VIND						
8					4.81			IND				
9						2	-	<b>Z</b>				
10					- <	-4	IDRE .					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil											

#### illiesseu by. Nii

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

Your Ref. No.

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

4367 Dr. Umbreen

To: Mr. Ashiq Ali

Lahore Cantt. District Lahore.

Project: Construction of Residence of Mr. Saad Asghar 88-C Model Town, Lahore.

Our Ref. No. CL/CED/ 577	Dated:	08-12-22	Test Specification
Your Ref. No. Gen-429/4	Dated:	07-12-22	( BS 1881-116 )

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:			07-12-22 Tested on:		Tested on:	08-1	2-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Beams and Slab	8	11	2022	6x6x6		8.2	36	86	5351		Non Engraved
2	Beams and Slab	8	11	2022	6x6x6		8.4	36	83	5164		Engraved
3												
4												
5					- /	GINE	RIATE					
6					- )	TINEADIN	(Filter					
7					11	DE THY LORD WHO	1	EP-				
8					181							
9							-	<b>7</b>				
10					- <	-14	IORE .					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil	·	•	•		•	·	·	·	·	<u> </u>	

#### illesseu by.

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



To: Mr. Saifullah Amin, Sr. Resident Engineer NESPAK (Pvt.) Limited, Environmental & Public Health Engineering Division Project: Punjab Intermediate Cities Improvement Investment Program (PICIIP). Consultancy Services for Engineering, Procurement and Construction Management, Watsan Sialkot (NCB-WORKS/PICIIP-11) LOT-01 Our Ref. No. CL/CED/ 578 Dated: 08-12-22

Nespak/SAH/UET/L1/057 06-12-22 Your Ref. No. Dated:

## COMPRESSION TEST REPORT

Test Specification

(----)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	7-12	-22	Tested on:	08-1	2-22	in dry/we	t condition		E	
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Rectangular, Grey 60mm				7.7 x 3.8 x 2.3		2380	29.26	55	4211		
2	Rectangular, Grey 60mm				7.7 x 3.8 x 2.3		2330	29.26	57	4364		
3	Rectangular, Grey 60mm				7.7 x 3.8 x 2.3		2405	29.26	65	4976		
4	Rectangular, Grey 60mm				7.7 x 3.8 x 2.3		2375	29.26	59	4517		
5					-	RINE	RIATE					
6						I READ IN						
7						DHE NHOLE OF THY LORD VIND	144	FB				
8					188							
9							-					
10					<	-LA	IONE .					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

#### Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory