

2785 Dr. Aqsa

To: M A Shehzad

First Enterprises, 23 Km Raiwind Road, Lahore.

Project: PMAHS F	taiwind.			
Our Ref. No. CL/C	ED/ 8101	Dated:	22-02-22	Test Specification
Your Ref. No.	Nil	Dated:	17-02-22	(BS 3921**)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	1	7-02	-22	Tested on:	22-0)2-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	LC-1				9 x 4.4 x 2.9		3470	39.6	35	1980		Fly Ash Brick
2	LC-2				9 x 4.4 x 2.9		3505	39.6	36	2036		Fly Ash Brick
3	LC-3				9 x 4.4 x 2.9		3480	39.6	37	2093		Fly Ash Brick
4	LC-4				9 x 4.4 x 2.9		3400	39.6	34	1923		Fly Ash Brick
5	LC-5				9 x 4.4 x 2.9	GINE	3435	39.6	33	1867		Fly Ash Brick
6					- >	T READ IN	San C					
7					-	CORD WHO						
8								IND				
9						2	- 5	7				
10					<	-14	IORE ?					
11												
12												
13												
14												
15												
16												
Witness	ed by:	·	•		·	•						

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory





ORIGINAL
A carbon copy for
the report has
been retained in
he lab for record.

2785 Dr. Aqsa

To: M A Shehzad

First Enterprises, 23 Km Raiwind Road, Lahore.

Project: PMAHS F	taiwind.			
Our Ref. No. CL/C	ED/ 8102	Dated:	22-02-22	Test Specification
Your Ref. No.	Nil	Dated:	17-02-22	(BS 3921**)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	1	7-02	-22	Tested on:	22-0)2-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti on (%)	Remarks
		סט			(111)	(r.g/ gms)	(r.g/ gms)	(34. 11)	(imp.rons)	(psi)	. ,	
1	BRK-1				9 x 4.4 x 2.7		3160	39.6	19	1075		Fly Ash Brick
2	BRK-2				9 x 4.4 x 2.8		3640	39.6	40	2263		Fly Ash Brick
3	BRK-3				9 x 4.4 x 2.8		3570	39.6	44	2489		Fly Ash Brick
4	BRK-4				9 x 4.4 x 3		3375	39.6	29	1640		Fly Ash Brick
5	BRK-5				9 x 4.4 x 2.9	GINE	3560	39.6	38	2149		Fly Ash Brick
6					- >	T READ IN	ALK N					
7					11	DHE NAME OF THY LORD WHO	4	EC				
8					4.81			I Na				
9						×						
10					- <		INK- ·					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



Phata, Sub Regi	on, Okara (M/s Pak Shahid Developers JV)			
Project: Constru	ction of Housing Units 03/05 Marla (Single B	ed and Double Bed	l) in Ads-II Renala Kh	urd
District Okara U	nder Naya Pakistan Housing Program			
Our Ref. No. CL/	CED/ 8103	Dated:	22-02-22	Test Specification
Your Ref. No.	Memo No.786	Dated:	28-12-21	(BS 1881-116)

COMPRESSION TEST REPORT



ORIGINAL A carbon copy for

the report has been retained in

the lab for record.

2802 Dr. Umbreen

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 21		1-02	-22	Tested on:	22-02-22		in dry/wet condition			ONLINE REPORT		
Sr. No.	Mark*	Cas DD	ting MM	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1		20	12	2021	6x6x6		8.4	36	51	3173		Engraved
2		20	12	2021	6x6x6		8.4	36	53	3298		Engraved
3		20	12	2021	6x6x6		8.2	36	55	3422		Engraved
4												
5					/	HINE	RINE					
6)	READ W	205 D					
7						DHE NAME OF THY LORD WHO	- F					
8					- Sa	1000						
9							-					
10					<	-LA	IONE .					
11												
12												
13												
14												
15												
16												
Witness	Witnessed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

2803 Engr.Abdu Rehman

To: Engr. Imran Saddique (Planning & Coordination Engineer) Ittefaq Building Solutions (Pvt.) Ltd. Lahore

Project: Power House (Extension) Reliance Cotton Spinning Mills Ltd.

Our Ref. No. CL/C	ED/ 8104	Dated:	22-02-22	Test Specification
Your Ref. No.	IBS/RPH/04	Dated:	21-02-22	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		21-02-22		-22	Tested on:	22-02-22		in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*	Cas	ting MM	Date*	Size	Wet Weight (Ka/ ams)	Dry Weight (Ka/ ams)	Area of X-Section (Sq. in)	Ultimate load (Imp Tons)	Ultimate Stress (nsi)	Water Absorpti on (%)	Remarks
1	C3,C1 above Plinth	13	1	2022	6x6x6		8.4	36	106	6596		Non Engraved
2	Plinth Beam @ Grid (9-12/C1)	14	1	2022	6x6x6		8.4	36	104	6471		Non Engraved
3	Basement SOG @ Grid (8-9/A-C)	17	1	2022	6x6x6		8.4	36	94	5849		Non Engraved
4	Branch Pipe Trench Bed	18	1	2022	6x6x6		8.4	36	138	8587		Non Engraved
5	Branch Pipe Trench Bed	18	1	2022	6x6x6 🧹	HILE	8.2	36	140	8711		Non Engraved
6	Plinth Beams on Line 9	19	1	2022	6x6x6	READIN	8.2	36	94	5849		Non Engraved
7	Cable Trench Bed @Grid(9-10/A1-C1)	20	1	2022	6x6x6		8.4	36	142	8836		Non Engraved
8												
9						à	1					
10					<	-LA	INRE .					
11												
12												
13												
14												
15												
16												
Witness	Witnessed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory