

## Plain and Reinforced Concrete Laboratory Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

2713 Dr. Umbreen

To: Sub Divisional Officer

**Buildings Sub Division No.22, Lahore.** 

Project: Construction of Building for E,Library and Research Facilities in Board for Advancement of

Literature, Lahore,

Our Ref. No. CL/CED/ 7080

Dated: 09-02-22

Test Specification
( ASTM C39 )

Your Ref. No. 12/22nd Dated: 04-02-22

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 07-02-22 Tested on: 09-02-22 in dry/wet condition





Sr. No.	Mark*	Casting Date*			Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	(1:1.5:3)	10	1	2022	6Diax12		13.4	28.28	49	3881		Engraved
2	(1:1.5:3)	10	1	2022	6Diax12		14	28.28	45	3564		Engraved
3												
4												
5					/	GINE	RING					
6						READIN	200					
7						DE NAME OF THY LIDRO WHO	-E.					
8												
9			-			-						
10			-			-LA	IORE.					
11			ł				-					
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.