

## Plain and Reinforced Concrete Laboratory Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

> 2647 Dr. Aqsa

To: Mr. Javed Igbal

For ZZ Associates. Bahria Town, Lahore.

Project: MVRE Calendria Unit Wall at Plot # 413 Sundar Industrial Estate Lahore.

Our Ref. No. CL/CED/ 6958 Dated: 25-01-22 <u>Test Specification</u>

Your Ref. No. ZZA/UET/0003-22 Dated: 22-01-22

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-01-22 Tested on: 25-01-22 in dry/wet condition



( ASTM C39 )



Sr. No.	Mark*	Casting Date*			Size (in)	Wet Weight	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	4000 Psi	25	12	2021	6Diax12		(Kg/ gills)	28.28	72	5703		Engraved
2	4000 Psi	25	12	2021	6Diax12		13.6	28.28	69	5465		Non Engraved
3												
4												
5						.cinE	RIAVA					
6						T READ IN		<b>X</b>				
7						DHE NAME OF THY LIDRO WHO	- N	=				
8					es		200	<b>3</b> -				
9								<b></b>				
10					<	· LA	IORE					
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.