

Plain and Reinforced Concrete Laboratory Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL
A carbon copy for
the report has
been retained in
he lab for record.

2520 Dr. M. Yousaf

t

To: **Sub Divisional Officer**

Public Health Engg: Sub Division, Lahore (M/s Malik Sayyad Ali)

Project: Providing and laying tuff tiles and PCC, Laghari Group C-Block, in UC-211, NA-130, Lahore

Our Ref. No. CL/C	ED/ 6795	Dated:	07-01-22	Test Specification
Your Ref. No.	1936/LHR	Dated:	20-12-21	()

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 03-01-22 Tested on: 07-01-22 in dry/wet condition												
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)		Water Absorpti on (%)	Remarks
1	Rectangular, Grey, 80 mm				7.7 x 3.8 x 3		3495	29.26	146	11177		
2	Rectangular, Grey, 80 mm	-			7.7 x 3.8 x 3		3470	29.26	114	8727		
3	Rectangular, Red, 80 mm	-			7.7 x 3.8 x 3		3720	29.26	134	10258		
4	Rectangular, Red, 80 mm	-			7.7 x 3.8 x 3		3585	29.26	126	9646		
5					/	RINE	RIATE					
6		-				I READ IN						
7						DHE NAME CE THY LORD WHO	14.9	EB				
8					/ RSI			UNI I				
9							1					
10		-			<	- (A	ER L					
11		-					-					
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



Project: Nil			
Our Ref. No. CL/CED/ 6796	Dated:	07-01-22	Test Specification
Your Ref. No. Nil	Dated:	03-01-22	()

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	3-01	-22	Tested on:	06-0)1-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Rectangular Grey, 60 mm				7.8 x 3.9 x 2.3		2630	30.42	33	2430		
2	Rectangular Grey, 60 mm				7.8 x 3.9 x 2.3		2840	30.42	63	4639		
3	Rectangular Grey, 60 mm				7.8 x 3.9 x 2.3		2810	30.42	81	5964		
4	Uniblock Red, 60 mm (2.4 thick)						3340	36.54	57	3494		
5					- /	GINE	RIATE					
6					-)	NEAD W	200					
7						DHE NAME CE THY LORD WHO	14.1	EB				
8					ASI ASI			HND				
9						-	-	X				
10					<	(A	INRE .					
11							-					
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



To:

Project: Nil			
Our Ref. No. CL/CED/ 6797	Dated:	07-01-22	Test Specification
Your Ref. No. Nil	Dated:	29/12/2021	()

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	30)/12/2	2021	Tested on:	05-0)1-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	ZBC				8.8 x 4.2 x 3.1		3340	36.96	55	3333		
2	Double Line				8.6 x 4.1 x 2.7		2575	35.26	47	2986		
3												
4												
5					/	GINE	RIATE					
6)	T READ IN	San De					
7					-	DIE NACE DE THY LORD VIND	14.4	EP-				
8					- 38			NO.				
9						2		7				
10					<	- LA	INRE?					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL
A carbon copy for
the report has
been retained in
the lab for record.

2496 Dr. M. Yousaf

To: Amir Qayyum (Assistant Construction Engineer) **The Citizens Foundation Lhr**

Project: The Citizens Foundation School at Awan Dhai Wala Lahore

Our Ref. No. CL/CED/ 6798	Dated	07-01-22	Test Specification
Your Ref. No. TCF/UET/	2021- Dated:	29/12/2021	(BS 3921**)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	29	-12-2	2021	Tested on:	06-0)1-22	in dry/wet condition				ONLINE REPORT	
Sr. No.	Mark*		•	Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks	
1	7UP				8.8 x 4.3 x 2.9		3125	37.84	23	1362			
2	7UP				8.9 x 4.2 x 3		3190	37.38	23	1378			
3	7UP				8.8 x 4.3 x 2.9		3090	37.84	20	1184			
4	7UP				8.8 x 4.3 x 2.8		3055	37.84	25	1480			
5	7UP				8.7 x 4.4 x 2.9	ARINE	3075	38.28	20	1170			
6					- >	E READ IN	ALL D						
7						DHE NAGAE <u>OE</u> THY LORID VING	144	EP					
8					- ISB								
9						2		V					
10					- <	-LA	INRE .						
11													
12													
13													
14													
15													
16													
Witness	ed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



2505 Dr. Umbreen

To: Engr. Muhammad Bilal Igbal (Project Manager) M. Siddique Sons Building Contractor, Lahore

Project: 113/4-M Quaid e Azam Industrial Estate, Lahore (3000 Psi)

Our Ref. No. CL/CED/ 6799	Dated:	07-01-22	Test Specification
Your Ref. No. Nil	Dated:	30-12-21	(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	3	0-12 [.]	-21	Tested on:	05-0	01-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	First Floor Slab (Stage-2)	20	12	21	6Diax12		14	28.28	81	6416		Non Engraved
2	First Floor Slab (Stage-2)	20	12	21	6Diax12		13	28.28	73	5782		Non Engraved
3	First Floor Slab (Stage-2)	20	12	21	6Diax12		13.8	28.28	45	3564		Non Engraved
4												
5				-	/	GINE	RIATE					
6				-	>	E READ W						
7						DHE NAME OF THY LORD VIND	- E					
8					188							
9				-		-						
10				-	<	- (A	INR E .					
11				-								
12				-								
13												
14												
15												
16												
Witness	ed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

ORIGINAL A carbon copy for the report has been retained in the lab for record.



2501 Dr. Umbreen

To: Mr. Umair Magsood (Sub Divisional Officer) **Buildings Sub Division, Assembly, Lahore**

Project: Construction of MPA Hostel (Phase-II) Lahore (Group No. 2)

Our Ref. No. CL/CED/ 6800	Dated:	07-01-22	Test Specification
Your Ref. No. 962	Dated:	21/12/2021	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	30)/12/2	2021	Tested on:	05-0	1-22	in dry/wet condition			ONLINE REPORT	
Sr. No.	Mark*	Cas DD	-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)		Water Absorpti on (%)	Remarks
1	First Floor Columns (1:1.5:3)	23	11	2021	6 x 6 x 6		8.8	36	106	6596		Non Engraved
2	First Floor Columns (1:1.5:3)	23	11	2021	6 x 6 x 6		8.6	36	100	6222		Non Engraved
3												
4												
5						GINE	RIATE					
6						I HEAD W						
7						DHE NHOLE OE THY LORD WHO		EB				
8					4.51			i) Na				
9						2	-					
10					<	-14	IDRE .					
11												
12												
13												
14												
15												
16												
Witness	Witnessed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

ORIGINAL A carbon copy for the report has been retained in the lab for record.



ORIGINAL
A carbon copy for
the report has
been retained in
the lab for record.

A

tł

2501 Dr. Umbreen

To: Mr. Umair Magsood (Sub Divisional Officer) **Buildings Sub Division Assembly, Lahore**

Project: Construction of MPA Hostel (Phase-II) Lahore (Group No. 2)

Our Ref. No. CL/CED/ 6801	Dated:	07-01-22	Test Specification
Your Ref. No. 958	Dated:	21/12/2021	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	30	/12/2	2021	Tested on:	05-0)1-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Lift Wall (1:1.5:3)	1	7	21	6 x 6 x 6		8.4	36	124	7716		Non Engraved
2	Lift Wall (1:1.5:3)	1	7	21	6 x 6 x 6		8.6	36	126	7840		Non Engraved
3												
4												
5						GINE	RINE					
6					>	T READ IN	Salt D					
7												
8					181							
9						2	- 2	7				
10					<	-14	INRE?					
11												
12												
13												
14												
15												
16												
Witnessed by:												

inesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



2501 Dr. Umbreen

To: Mr. Umair Magsood (Sub Divisional Officer) **Buildings Sub Division Assembly, Lahore**

Project: Construction of MPA Hostel (Phase-II) Lahore (Group No. 2)

Our Ref. No. CL/CED/ 6802	Dated:	07-01-22	Test Specification
Your Ref. No. 959	Dated:	21/12/2021	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	30)/12/2	2021	Tested on:	05-0	1-22	in dry/wet condition			ONLINE REPORT	
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Emergency Stairs (1:2:4)	8	9	21	6 x 6 x 6		7.8	36	39	2427		Non Engraved
2	Emergency Stairs (1:2:4)	8	9	21	6 x 6 x 6		7.8	36	41	2551		Non Engraved
3												
4												
5						ARTHE	RIATE					
6						I READ IN						
7						DHE NHOLE <u>OE</u> THY LORD WHO	14.9	EB				
8					4.81			H				
9						-	1	7				
10					<	-14	IORE .					
11												
12												
13												
14												
15												
16												
Witness	Witnessed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

ORIGINAL A carbon copy for the report has been retained in the lab for record.



ORIGINAL A carbon copy for the report has been retained in the lab for record.

2501 Dr. Umbreen

To: Mr. Umair Magsood (Sub Divisional Officer) **Buildings Sub Division Assembly, Lahore**

Project: Construction of MPA Hostel (Phase-II) Lahore (Group No. 2)

Our Ref. No. CL/CED/ 6803	Dated:	07-01-22	Test Specification
Your Ref. No. 960	Dated:	21/12/2021	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	30)/12/2	2021	Tested on:	05-0	1-22	in dry/wet condition			ONLINE REPORT	
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Upper Basement Slab (1:2:4)	10	10	21	6 x 6 x 6		8.6	36	124	7716		Non Engraved
2	Upper Basement Slab (1:2:4)	10	10	21	6 x 6 x 6		8.4	36	112	6969		Non Engraved
3												
4												
5						RINE	RIATE					
6						I READ IN						
7						DHE NHOLE <u>OE</u> THY LORD WHO	14.9	EB				
8					4.81			UNI 				
9							1					
10					<	-14	IORE .					
11												
12												
13												
14												
15												
16												
Witnessed by:												

illesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

2501 Dr. Umbreen

To: Mr. Umair Magsood (Sub Divisional Officer) **Buildings Sub Division Assembly, Lahore**

Project: Construction of MPA Hostel (Phase-II) Lahore (Group No. 2)

Our Ref. No. CL/CED/ 6804	Dated:	07-01-22	Test Specification
Your Ref. No. 961	Dated:	21/12/2021	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specime	ens received on:	30)/12/2	2021	Tested on:	05-0)1-22	in dry/wet	condition			ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Ground Floor Slab (1:2:4)	19	11	21	6 x 6 x 6		8.4	36	144	8960		Non Engraved
2	Ground Floor Slab (1:2:4)	19	11	21	6 x 6 x 6		8.4	36	116	7218		Non Engraved
3												
4												
5						RINE	RINE					
6)	T READ IN						
7						DHE NIKKE OF THY LORD WHO	- J					
8					- ISH	1						
9							-					
10					<	-LA	INK- ·					
11												
12												
13												
14												
15												
16												
Witness	Witnessed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



Our Ref. No. CL/CED/ 6805	Dated:	07-01-22	Test Specification
Your Ref. No. 1003/12/2021	Dated:	12-01-21	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	30)/12/2	2021	Tested on:	04-0)1-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	C-24	1	11	2021	6 x 6 x 6		8.8	36	106	6596		Non Engraved
2	C-24	1	11	2021	6 x 6 x 6		8.8	36	99	6160		Non Engraved
3	C-24	1	11	2021	6 x 6 x 6		9	36	102	6347		Non Engraved
4												
5					- /	GINE	RIATE					
6)	READ IN	PART					
7							- 42					
8					- Sa			No				
9						2	- 3					
10					<	-14	ORE .					
11												
12												
13												
14												
15												
16												
Vitness	ed by:					1	1	<u>.</u>	I	1	<u>. </u>	

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory



2504 Dr. Aqsa

To: Engr. M. Hamza Mansoor **STYLE Textile**

Project: Style SAP P-3			
Our Ref. No. CL/CED/ 6805	Dated:	07-01-22	Test Specification
Your Ref. No. 1029/12/2021	Dated:	16/12/2021	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	30	/12/2	021	Tested on:	04-0	1-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		Casting Date*		Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
1	C-30 (Column Cuttina Blda)	8	11	YYYY 21	(in) 6 x 6 x 6	(Kg/ gms) 	(Kg/ gms) 8.6	(Sq. in) 36	(Imp.Tons) 121	(psi) 7529		Non Engraved
2	C-30 (Column Cutting Bldg)	8	11	21	6 x 6 x 6		8.6	36	124	7716		Non Engraved
3	C-30 (Column Cuttina Blda)	8	11	21	6 x 6 x 6		8.6	36	110	6844		Non Engraved
4	C-30 (Raft ASE)	14	11	21	6 x 6 x 6		8	36	96	5973		Non Engraved
5	C-30 (Raft ASE)	14	11	21	6 x 6 x 6	RINE	8.6	36	125	7778		Non Engraved
6	C-30 (Raft ASE)	14	11	21	6 x 6 x 6	NEAD IN	8.8	36	116	7218		Non Engraved
7	C-35 (Column ASE)	16	11	21	6 x 6 x 6	DHE NHOLE OE THY LORD WHO	8.2	36	116	7218		Non Engraved
8	C-35 (Column ASE)	16	11	21	6 x 6 x 6 🤔		8.2	36	132	8213		Non Engraved
9	C-35 (Column ASE)	16	11	21	6 x 6 x 6	-	8.2	36	119	7404		Non Engraved
10					<	-14	IORE .					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



2504 Dr. Qasim

To: Engr. M. Hamza Mansoor **STYLE Textile**

Project: Style Manga.			
Our Ref. No. CL/CED/ 6807	Dated:	07-01-22	Test Specification
Your Ref. No. 1010/12/2021	Dated:	07-12-21	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on: 30/12/2021 Tested on: 03-01-22 in dry/wet condition					ONLINE REPORT						
Sr. No.	Mark*		•	Date* YYYY	Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
1	C-30 (Column)	10	11	21	(in) 6 x 6 x 6		(Kg/ gms) 8	(Sq. in) 36	(Imp.Tons) 66	(psi) 4107		Non Engraved
	. ,									-		-
2	C-30 (Column)	10	11	21	6 x 6 x 6		8.2	36	67	4169		Non Engraved
3	C-30 (Column)	10	11	21	6 x 6 x 6		8	36	73	4542		Non Engraved
4	C-20 (Beam)	10	11	21	6 x 6 x 6		8	36	57	3547		Non Engraved
5	C-20 (Beam)	10	11	21	6 x 6 x 6	GINE	RIA8	36	53	3298		Non Engraved
6	C-20 (Beam)	10	11	21	6 x 6 x 6	T READ W	8	36	53	3298		Non Engraved
7						DHE NHOLE OF THY LORD VIND	14.9	FB				
8					188							
9												
10					<	- (A	INRE.					
11												
12												
13												
14												
15												
16												
Witness	Witnessed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



2504 Dr. Aqsa

To: Engr. M. Hamza Mansoor **STYLE Textile**

Project: Style Raiwind.			
Our Ref. No. CL/CED/ 6808	Dated:	07-01-22	Test Specification
Your Ref. No. 1014/12/2021	Dated:	07-12-21	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:			30/12/2021 Tested of			04-0)1-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		Casting Date*		Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
				YYYY	. ,	(Kg/ gms)	(Kg/ gms)		(Imp.Tons)		011 (70)	
1	C-20 (Beam-ASE)	11	11	21	6 x 6 x 6		8	36	73	4542		Non Engraved
2	C-20 (Beam-ASE)	11	11	21	6 x 6 x 6		8	36	114	7093		Non Engraved
3	C-20 (Beam-ASE)	11	11	21	6 x 6 x 6		8	36	73	4542		Non Engraved
4	C-30 (493)	11	11	21	6 x 6 x 6		8	36	80	4978		Non Engraved
5	C-30 (493)	11	11	21	6 x 6 x 6	GINE	8.6	36	106	6596		Non Engraved
6	C-30 (493)	11	11	21	6 x 6 x 6	I HEAD IN	8.2	36	94	5849		Non Engraved
0						DHE NAME OF THY LORD WHO	-4	EC				
0					- SR			i Na				
0					}	2-	- 5					
10					<	- (A	ORE					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



2504 Dr. Aqsa

To:	Engr. M. Hamza Mansoor
	STYLE Textile

Project: Style SAI	P			
Our Ref. No. CL/C	ED/ 6809	Dated:	07-01-22	Test Specification
Your Ref. No.	0023/11/2021	Dated:	26/11/2021	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		30/12/2021		021	Tested on: 04-01-22)1-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		Casting Date*		Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
	C-24 (Footing -			ΥΥΥΥ	()		(Kg/ gms)		(Imp.Tons)			N
1	Kraftcon) C-24 (Footing -	25	10	21	6 x 6 x 6		8.8	36	115	7156		Non Engraved
2	Kraftcon)	25	10	21	6 x 6 x 6		8.4	36	111	6907		Non Engraved
3	C-24 (Footing - Kraftcon)	25	10	21	6 x 6 x 6		8.6	36	114	7093		Non Engraved
4	C-20 (Drain-ASE)	26	10	21	6 x 6 x 6		8.4	36	92	5724		Non Engraved
5	C-20 (Drain-ASE)	26	10	21	6 x 6 x 6	RINE	8.2	36	108	6720		Non Engraved
6	C-20 (Drain-ASE)	26	10	21	6 x 6 x 6	I READ IN	8.4	36	101	6284		Non Engraved
7	C-35 (Column-ASE)	28	10	21	6 x 6 x 6 🚞	DHE NAME <u>OE</u> THY LORD WHO	8.4	36	104	6471		Non Engraved
8	C-35 (Column-ASE)	28	10	21	6 x 6 x 6		8.2	36	121	7529		Non Engraved
9	C-35 (Column-ASE)	28	10	21	6 x 6 x 6		8.2	36	110	6844		Non Engraved
10					- <	-14	IORE .					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory