

ORIGINAL
A carbon copy for
the report has
been retained in
he lab for record.

3510 Dr. Aqsa

To: Mr. M. Imran Khan

Material Engineer ECSP, PIPAL House A-Block

Project: Reconstruction of Pipal House A-Block Lahore. (M/s Uni Build Associate Pvt. Ltd.)

Our Ref. No. CL	/CED/ 9356	Dated:	19/07/2022	Test Specification
Your Ref. No.	343/ECSP/PH/ME/20	Dated:	27/06/2022	(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	on: 29/06/2022 Tested on: 19/07/2022 in dry/wet condition						ONLINE REPORT				
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)		Water Absorpti on (%)	Remarks
1	5th Floor Stairs	31	5	2022	6Diax12		13.2	28.28	37	2931		Engraved
2	5th Floor Stairs	31	5	2022	6Diax12		13.2	28.28	37	2931		Engraved
3	5th Floor Stairs	31	5	2022	6Diax12		13	28.28	35	2772		Engraved
4												
5						AINE	RINC					
6												
7						THE NAME OF THY LORD WHO						
8					/ ASI	CREATES	<u><u> </u></u>	ZNIE I				
9						×	- 6	7				
10					- <		INRE .					
11												
12												
13												
14												
15												
16												
Witness	sed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



To: Mr. Ahmed Ejaz, Quantity Surveyor LINKER Developers (Pvt.) Ltd.

Project: Construction of ROLUSTECH - RT Tower, Gulberg III, Lahore.

Our Ref. No. CL/CED/ 9357	Dated:	19/07/2022	Test Specification
Your Ref. No. LD/RT/C-05	Dated:	04/07/2022	(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	05/07/2022 Tested on:			19/07	/2022	in dry/we	t condition			ONLINE REPORT	
Sr. No.	Mark*	Cas DD	-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Basement Slab (3000 Psi)	25	6	2022	6Diax12		13	28.28	47	3723		Non Engraved
2	Basement Slab (3000 Psi)	25	6	2022	6Diax12		12.4	28.28	45	3564		Non Engraved
3												
4												
5						ANE	RINC					
6					>	C REPAIR	X					
7						THE NAME CORD VIEW	1	HI.				
8					ASI -	CREATES	10000	HNO				
9							-					
10					- <	- 14	INRE .					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 3546 Dr. Aqsa



Project: Construction of Abdul Aleem Khan Dispensary Slab of Ground Floor Sheikhupura Road Kot Abdul Malik Lahore. Our Ref. No. CL/CED/ 9358 19/07/2022 Dated: **Test Specification** Your Ref. No. Nil Nil Dated:

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers



(ASTM C39)

ORIGINAL A carbon copy for

the report has been retained in

the lab for record.

3549 Dr. Aqsa

Specimens received on: 06/07/2022					Tested on:	19/07	/2022	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1		28	6	2022	6Diax12		13	28.28	11	871		Non Engraved
2		28	6	2022	6Diax12		13.2	28.28	31	2455		Non Engraved
3		28	6	2022	6Diax12		13	28.28	18	1426		Non Engraved
4												
5						AINE	RINO					
6)	Character and						
7						DHE NHOLE CONTROLOGIES LICERO VORD						
8					188	CAEATES	100					
9						×	-					
10					<		INRES					
11												
12												
13												
14												
15												
16												
Witness	Witnessed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Director/Dy. Director Concrete Laboratory



Dated:

02/07/2022

(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Nil

Specimens received on: 05/07/2022 Tested on: 19/07/2022 in dry/wet condition											ONLINE REPORT	
Sr. No.	Mark*	Cas DD	•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
I	Prim. Raft Conc. Ph- 2 (4000 Psi)	14	6	2022	6Diax12		13	28.28	68	5386		Non Engraved
2	Prim. Raft Conc. Ph 2 (4000 Psi)	14	6	2022	6Diax12		13.6	28.28	74	5861		Non Engraved
3	Prim. Raft Conc. Ph 2 (4000 Psi)	14	6	2022	6Diax12		13	28.28	68	5386		Non Engraved
4												
5						ANE	RINC					
6						C INCADING	No.					
7						THE NAME CORD WHE	-	H				
8					IS¥	CREATES	1	HNU				
9							-					
10					<	LA	INRE .					
11												
12												
13												
14												
15												
16												
Witness	sed by: Nil											

eu ny.

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

Your Ref. No.

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



Dated:

05/07/2022

(ASTM C39)

Your Ref. No. Nil

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	05/07/2022 Tested on: 19/07/2022 in dry/wet condition					ONLINE REPORT					
Sr. No.	Mark*	Cas	•	Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	G.F Column (4000 Psi)	2	6	2022	6Diax12		13	28.28	38	3010		Engraved
2	G.F Column (4000 Psi)	2	6	2022	6Diax12		13.2	28.28	65	5149		Non Engraved
3	G.F Column (4000 Psi)	2	6	2022	6Diax12		13	28.28	39	3089		Engraved
4												
5						ANE	RING					
6					>							
7						THE NAME CONTROL	4					
8					- USA	CREATES						
9							-					
10					- <	+//	INRE .					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil											

eu by.

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

		Univ	n and Reinforced C Civil Engineering De Versity of Engineering and Technol : 042-99029245 & 042-99029202	epartmen logy, Lahore.	ıt	,	ORIGINAL A carbon copy for the report has been retained in the lab for record.
To:	Drain of	Managar					3518 Dr. Aqsa
10.		t Manager s Property	v Management Pvt. Ltd.				
	Project	: Orchard	Mall, Bahria Orchard, Lahore				
	Our Re	f. No. CL/	CED/ 9361		Dated:	19/07/2022	Test Specification
	Your R	ef. No.	QLC-BO-BH2-2022-05-LTR-631-B		Dated:	30/06/2022	(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specime	ens received on:	01	/07/2	2022	Tested on:	19/07	/2022	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	4th Floor Slab (3000 Psi)	31	5	2022	6Diax12		13	28.28	42	3327		Non Engraved
2	4th Floor Slab (3000 Psi)	31	5	2022	6Diax12		13.8	28.28	42	3327		Non Engraved
3												
4												
5						ANE	RING					
6						C Lagran M				-		
7						DHE NAME CORD WHO		E				
8						CREATES	3	- 2				
9						×	-	5				
10					<	-14	LANG LANG			-		
11							I			-		
12										-		
13												
14												
15												
16												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

	Civil En	ering and Technology,	rtment	ý	ORIGINAL A carbon copy for the report has been retained in the lab for record.
То:	Project Manager Q-Links Property Management Pv		woone. 0007-040005		3519 Dr. Aqsa
	Project: Jasmine Grand Mall, Bah	ria Town, Lahore.			
	Our Ref. No. CL/CED/ 9362		Dated:	19/07/2022	Test Specification
	Your Ref. No. QLC-BO-BH2-2	022-05-LTR-630-A	Dated:	30/06/2022	(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	01	/07/2	2022	Tested on:	19/07	/2022	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate Ioad (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	5500 Psi	28	5	2022	6Diax12		13.2	28.28	56	4436		Engraved
2	5500 Psi	28	5	2022	6Diax12		13	28.28	53	4198		Engraved
3	3000 Psi	28	5	2022	6Diax12		13	28.28	32	2535		Engraved
4	3000 Psi	28	5	2022	6Diax12		13	28.28	34	2693		Engraved
5						ANE	RINE					
6												
7						THE NAME THY LORD WHO		H				
8					- se	CREATES	100	HN/				
9							-					
10					<	+ LA	INRE!					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil											

nesseu by. Mi

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory