

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3464 Dr. Umbreen

To: Mr. Muhammad Zeeshan

Sahuwari, Mughalpura, Lahore.

Project: House # 272/1, Z-Block Phase-3, DHA, Lahore.

Our Ref. No. CL/CED/ 9253 Dated:

Your Ref. No. Nil Dated: 20-06-22

Test Specification

28-06-22

(----)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-06-22 Tested on: 27-06-22 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(met.Tons)	(psi)	on (%)	
1	Porcelain Tile	-			0.5x0.5x0.5		2	0.25	0.25	2204		Cut Cube
2	Porcelain Tile				0.5x0.5x0.5		2	0.25	0.26	2292		Cut Cube
3	Porcelain Tile				0.5x0.5x0.5		2	0.25	0.3	2645		Cut Cube
4												
5			-		(CHETH!	RING A					
6						THE MARK	PARTY	<u></u>		-		
7						CHEATES	ر بالد الماري الماري	(A)		-		
8								100		-		
9						%	1.0			-		
10			-				DR.					
11										-		
12										-		
13										-		
14			-									
15												
16												
Witness	ed by: Nil			_								

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

 $\underline{\textbf{Note:}}$ Above results pertain to the unsealed samples supplied to the laboratory

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3472 Dr. Aqsa

Test Specification

(ASTM C39)

To: Mr. Ahmad Danyal, Civil Engr.

Xinhua Mall, Gulberg III, Lahore

Project: Construction of Studio Corporate Offices at Xinhua Mall, Gulberg III, Lahore.

Our Ref. No. CL/CED/ 9254 Dated: 28-06-22

Your Ref. No. SCO/UET/2022/01 Dated: 22-06-22

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 22-06-22 Tested on: 28-06-22 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Horizontal Member (Slab)	15	6	2022	6Diax12		13.2	28.28	46	3644		Non Engraved
2	Horizontal Member (Slab)	15	6	2022	6Diax12		13.2	28.28	53	4198		Non Engraved
3	Horizontal Member (Slab)	15	6	2022	6Diax12		13	28.28	48	3802		Non Engraved
4												
5					/	RIVE	RIATE					
6						NEAD W	205	X				
7						DHE NAME OF THY LIDRO WHO	- N	=				
8					- 68							
9		-				<u> </u>						
10					<	-LA	INRE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3490 Dr. Aqsa

To: Project Manager

Q-Links Property Management Pvt. Ltd.

Project: Construction of Orchard Mall, Bahria Orchard, Lahore.

Our Ref. No. CL/CED/ 9255 Dated: 28-06-22 <u>Test Specification</u>

Your Ref. No. QLC-UET-BH2-2022-06-LTR-002 Dated: 24-06-22 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 27-06-22 Tested on: 28-06-22 in dry/wet condition



Sr. No.	Mark*			Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	5000 Psi	23	5	2022	6Diax12		14	28.28	61	4832		Non Engraved
2	5000 Psi	23	5	2022	6Diax12		14	28.28	61	4832		Non Engraved
3												
4												
5					/	GINE	RINE					
6						READIN	200					
7						DHE NAME OF THY LIDRO WHO	- F	-				
8					SS			iNo				
9												
10					🤇	-LA	IORE					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3485 Dr. Aqsa

To: Mr. Ageel Aslam, Manager Projects

Fatima Memorial Hospital, Shadman, Lahore

Project: Construction of New Building at Fatima Memorial Hospital, Lahore

 Our Ref. No. CL/CED/
 9256
 Dated:
 28-06-22
 Test Specification

 Your Ref. No.
 FMH/RAF/con/20
 Dated:
 23-06-22
 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 24-06-22 Tested on: 28-06-22 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	4th Floor Slab (5000 Psi)	19	6	2022	6Diax12		14	28.28	40	3168		Non Engraved
2	4th Floor Slab (5000 Psi)	19	6	2022	6Diax12		14	28.28	45	3564		Non Engraved
3	4th Floor Slab (5000 Psi)	7	6	2022	6Diax12		14	28.28	44	3485		Non Engraved
4	4th Floor Slab (5000 Psi)	7	6	2022	6Diax12		14	28.28	39	3089		Non Engraved
5						REINE	RIATE					
6)	READ IN						
7						DE NAME OF THY LIDRO WHO	- F 1	=				
8					ea							
9						_						
10						-LA	ORE					
11												
12												
13												
14												
15												
16												

Witnessed by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3471 Dr. Aqsa

Test Specification

(ASTM C39)

To: HK Husnain Kareemain Residential and Commercial Builders

Plaza 14-A/5 PECHS Near Wapda Town, Lahore.

Project: Construction of Beacon House School, Sargodha Campus

Our Ref. No. CL/CED/ 9257

Your Ref. No. Nil Dated: 22-06-22

Dated:

28-06-22

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 22-06-22 Tested on: 28-06-22 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
	Mark	DD	ММ	YYYY	(in)		(Kg/ gms)		(Imp.Tons)		on (%)	Romanio
1	Column	6	6	2022	6Diax12		14.4	28.28	68	5386		Non Engraved
2	Column	6	6	2022	6Diax12		14.2	28.28	66	5228		Non Engraved
3	Footing	29	5	2022	6Diax12		14	28.28	45	3564		Non Engraved
4	Footing	29	5	2022	6Diax12		14	28.28	37	2931		Non Engraved
5	Footing	29	5	2022	6Diax12	CINE	14.6	28.28	60	4752		Non Engraved
6	Footing	29	5	2022	6Diax12	T READ W	14	28.28	69	5465		Non Engraved
7						DE MICE	- N	量				
8					- 68	ظلا		<u> </u>				
9						\		7				
10					(-LA	INK .					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3491 Dr. Aqsa

To: Sub Divisional Officer

Your Ref. No.

Building Sub Division, Kot Radha Kishan

118/KRK

Project: Construction of Building of Govt. Special Education Centre, Kot Radha Kishan Dist. Kasur. (ADP

No. 448) for the Year 2021-22

Our Ref. No. CL/CED/ 9258

Dated: Dated: 28-06-22

Test Specification

22-06-22 (BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 27-06-22 Tested on: 28-06-22 in dry/wet condition



r. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	(1:2:4)	28	5	2022	6x6x6		8	36	81	5040		Engraved
2	(1:2:4)	28	5	2022	6x6x6		8	36	77	4791		Engraved
3												
4												
5					/	GINE	RINE					
6						READIN	200					
7					A	DE NIGE OF THY LORD WHO	16					
8					- S			- ON				
9							1	7				
10						" -LA	IORE.					
11												
12												
13												
14												
15												
16												
15												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3491 Dr. Aqsa

To: Sub Divisional Officer

Building Sub Division, Kot Radha Kishan

Project: Construction of Tehsil Complex, Kot Radha Kishan Dist. Kasur. (ADP No. 5607 for the Year 2021-

22)

Our Ref. No. CL/CED/ 9259 Your Ref. No. 119/KRK Dated: 28-06-22

22-06-22

Dated:

Test Specification

(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 27-06-22 Tested on: 28-06-22 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	(1:2:4)	30	5	2022	6x6x6		8	36	93	5787		Engraved
2	(1:2:4)	30	5	2022	6x6x6		8.2	36	96	5973		Engraved
3												
4												
5					🔏	GINE	RINE					
6						READIN	200					
7						DHE NAME OF THY LIGHT WHO	₩. <u></u>	-				
8					SS							
9),—	- 6					
10					<	LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3488 Dr. Aqsa

Test Specification

To: Mr. Muhammad Rafique

District Muridke.

Project: Construction of Beacon House School, Hafizabad Secondary Branch.

Our Ref. No. CL/CED/ 9260 Dated:

Your Ref. No. Nil Dated: 27-06-22 (BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 27-06-22 Tested on: 28-06-22 in dry/wet condition



28-06-22

Sr. No.	Mark*			Date*	Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
		טט	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	G. (70)	
1		31	5	2022	6x6x6		9	36	118	7342		Engraved
2		31	5	2022	6x6x6		9	36	107	6658		Engraved
3		3	6	2022	6x6x6		9	36	111	6907		Engraved
4		3	6	2022	6x6x6		9	36	114	7093		Engraved
5						TETNE	RIATE					
6						READIN						
7						DHE NAME OF THY LIGHT WHILE	- T	EB				
8					es							
9												
10						-LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



Plain and Reinforced Concrete Laboratory

Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL**

A carbon copy for the report has been retained in the lab for record.

> 3435 Dr. Aqsa

Test Specification

To: Lt. Col. (R.) Muhammad Ibrahim, Estate Engr.

Sundar Industrial Estate

Project: Construction of RO Plant at Gate No. 3 SIE. (M/s Muhammad Aslam Partner & Company).

Our Ref. No. CL/CED/ 9261 Dated: 28-06-22

Your Ref. No. BOM/SIE/BCD/8126 Dated: 13-06-22 (BS 3921**)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14-06-22 Tested on: 28-06-22 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Water Absorpti	Remarks
on no.	mark	DD	ММ	YYYY	(in)		(Kg/ gms)		(Imp.Tons)		on (%)	rtomarko
1	Z 5				8.8 x 4.3 x 2.9	3815	3415	37.84	49	2901	11.71	
2	Z 5				8.7 x 4.3 x 3	3595	3185	37.41	45	2694	12.87	
3	Z 5				8.7 x 4.3 x 3	3610	3215	37.41	52	3114	12.29	
4	Z5				8.8 x 4.3 x 3	3750	3280	37.84	43	2545	14.33	
5	Z 5				8.7 x 4.3 x 3	3705	3300	37.41	44	2635	12.27	
6	Z 5				8.7 x 4.3 x 2.9	3635	3235	37.41	45	2694	12.36	
7						DHE NAKKE OF THY LIDIED WHE	<u> </u>	a —				
8					65	l series	1000					
9),		7				
10						LA	HORE					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



Plain and Reinforced Concrete Laboratory

Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL Carbon conv

A carbon copy for the report has been retained in the lab for record.

> 3469 Dr. Aqsa

(BS 3921**)

To: Sub Divisional Officer

Building Sub Division No. 2, Lahore

Project: Development Cultural Tourism Village & Allied Facilities at Harbanspura, Lahore (ADP No.

6765/2021-22)

Our Ref. No. CL/CED/ 9262 Dated: 28-06-22 <u>Test Specification</u>

Your Ref. No. 1166 2nd Dated: 17-06-22

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 22-06-22 Tested on: 28-06-22 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	7UP				8.9 x 4.2 x 2.9	3600	3170	37.38	36	2157	13.56	
2	7UP				8.8 x 4.2 x 3.1	3650	3310	36.96	48	2909	10.27	
3	7UP				9 x 4.1 x 2.9	3595	3265	36.9	40	2428	10.11	
4	7UP				8.8 x 4.1 x 3	3625	3265	36.08	35	2173	11.03	
5	7UP				8.8 x 4.1 x 3	3715	3275	36.08	31	1925	13.44	
6						T READ W						
7						DE NAME OF THY LORD WHO	- N	E -				
8								8 -				
9),—	-	7				
10						" LA	HORE					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.