

ORIGINAL
A carbon copy for
the report has
been retained in
he lab for record.

t

2923 Dr. M. Yousaf

To: Mr. Muhammad Usman (Project Manager) Guarantee Engineers (Pvt.) Ltd. Lahore

Project: Beaconhouse School System TNS 2.0 Gulberg-iii, Lahore (Lab No. BH-36)

Our Ref. No. CL	/CED/ 8238	Dated:	11-03-22	Test Specification
Your Ref. No.	GEPL/TNS2/04/2022	Dated:	09-03-22	(ASTM C39)

### **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	1	0-03	-22	Tested on:	11-0	)3-22	in dry/wet condition				
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	4000 Psi	7	2	2022	6Diax12		13.2	28.28	43	3406		Non Engraved
2	4000 Psi	7	2	2022	6Diax12		13.4	28.28	41	3248		Non Engraved
3	4000 Psi	7	2	2022	6Diax12		13.2	28.28	43	3406		Non Engraved
4												
5					- /	RINE	RIATE					
6					)	I NEAD W	Park I					
7						DHE NAME COE THY LORIQ WHO	14.1	EB				
8					- Sa			IND.				
9						-	-					
10					- <	(A	INK- ·					
11												
12												
13												
14												
15												
16												
Witnessed by: Mr. M. Ali Khan (CNIC # 33100-2629451-1)												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



• •	r Irrigation Project-Contract No.JIP/WKS (RD 0+000 to 52+000) Package-1 (Top SI			Canal
Our Ref. No. CL	/CED/ 8239	Dated:	11-03-22	Test Specification
Your Ref. No.	JIPIC/TECH/P-1/CRE/362	Dated:	01-03-22	(ASTM C39)



2871 Dr. Aqsa

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	3-03	-22	Tested on:	08-0	)3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	B-501-1	26	1	2022	6Diax12		12.4	28.28	79	6257		Non Engraved
2	B-501-2	26	1	2022	6Diax12		13	28.28	84	6653		Non Engraved
3	B-501-3	26	1	2022	6Diax12		13	28.28	90	7129		Non Engraved
4												
5					/	GINE	RIATE					
6					>	T READ IN	Sale D					
7						DIE NACE CE THY LORO WHO	199					
8					- 188			IN D				
9						2-	- 5	7				
10					<	-14	INRE ?					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



A carbon copy for
the report has
been retained in
the lab for record.

ORIGINAL

2871 Engr. Ubaid

To: Engr. Javed Asad (Chief Resident Engineer) Jalalpur Irrigation Consultants (JIP), Jalalpur Sharif

Project: Jalalpur Irrigation Project-Contract No.JIP/WKS/ICB/P1 Construction of Jalapur Irrigation Canal and ITS System (RD 0+000 to 52+000) Package-1 (Canal Lining Bed L/S RD 14+260 to 14+440)										
Our Ref. No. CL/CED/ 8240 Dated: 11-03-22										
Your Ref. No.	JIPIC/TECH/P-1/CRE/364	Dated:	01-03-22							

## COMPRESSION TEST REPORT

Test Specification (ASTM C39)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers
--

Specim	ens received on:	0	3-03	-22	Tested on:	10-0	)3-22	in dry/wet condition				
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	C-122-1	3	2	2022	6Diax12		12.4	28.28	41	3248		Non Engraved
2	C-122-2	3	2	2022	6Diax12		13	28.28	50	3960		Non Engraved
3	C-122-3	3	2	2022	6Diax12		12	28.28	37	2931		Non Engraved
4												
5					/	ARILE	RIATE					
6					>	READ W	RIAN					
7						DHE NAME CE THY LORD WHO	14.	EB				
8					/ 4.81			IND.				
9						-	-					
10						(A	INRE.					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil											

#### Nitnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



Jalalpur Irrigation Consultants (JIP), Jalalpur Sharif

, ,	Project: Jalalpur Irrigation Project-Contract No.JIP/WKS/ICB/P1 Construction of Jalapur Irrigation Canal and ITS System (RD 0+000 to 52+000) Package-1 (Parapet Wall pf Bridge RD 26+000)										
Our Ref. No. CL/CED/ 8241 Dated: 11-03-22											
Your Ref. No.	JIPIC/TECH/P-1/CRE/363	Dated:	01-03-22	(ASTM C39)							

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	3-03	-22	Tested on:	08-0	3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate Ioad (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	B-500-1	25	1	2022	6Diax12		13	28.28	91	7208		Non Engraved
2	B-500-2	25	1	2022	6Diax12		13	28.28	55	4356		Non Engraved
3	B-500-3	25	1	2022	6Diax12		12.4	28.28	74	5861		Non Engraved
4												
5					/	GINE	RIATE					
6					)	NEAD W						
7					-	DHE NAME OF THY LORD WHO	4	EB				
8					- ASI			IND				
9						2	- 5	<b>7</b>				
10					<	-14	IORE .					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



A carbon copy for the report has been retained in the lab for record.

ORIGINAL

2871 Dr. Aqsa

	Plain and Reinforced Concrete Laboratory Civil Engineering Department University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895	ORIGINAL A carbon copy for the report has been retained in the lab for record.
То:	Sub Divisional Officer Buildings Sub Division, Nankana Sahib	2821 Dr. M. Yousaf
	Project: Construction of 02-Nos Additional Class Rooms at Government Guru Nanak Graduate College for	

Boys at Nankana Sahib										
Our Ref. No. CL/CED/ 8242	Dated:	11-03-22	Test Specification							
Your Ref. No. Nil	Dated:	14-01-22	( )							

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	2	3-02	-22	Tested on:	11-0	)3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	SG				8.5 x 4.2 x 2.7	3225	2820	35.7	33	2071	14.36	
2	SG				8.5 x 4.2 x 2.8	3250	2865	35.7	37	2322	13.44	
3	SG				8.4 x 4.2 x 2.8	3210	2835	35.28	30	1905	13.23	
4	SG				8.5 x 4.3 x 2.8	3245	2820	36.55	32	1961	15.07	
5	м				8.7 x 4.3 x 2.9	3595	3165	37.41	42	2515	13.59	
6	м				8.6 x 4.2 x 3	3670	3225	36.12	37	2295	13.8	
7	М				8.6 x 4. <mark>2 x 2.9</mark>	3585	-3135	36.12	39	2419	14.35	
8	М				8.6 x 4 <mark>.</mark> 2 x 2.9	3535	3125	36.12	38	2357	13.12	
9						·	- 6					
10					<	-LA	INKE .					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption


3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.





346) 2021-22.		-	
Our Ref. No. CL/CED/ 8243	Dated:	11-03-22	Test Specification
Your Ref. No. 782/SDO/BSD/SKT	Dated:	16/2/2022	(BS 1881-116)



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	03	/03/2	022	Tested on:	08-0	3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(1:2:4)	10	1	2022	6x6x6		8.4	36	118	7342		Non Engraved
2	(1:2:4)	10	1	2022	6x6x6		8.2	36	126	7840		Non Engraved
3	(1:2:4)	10	1	2022	6x6x6		8.4	36	86	5351		Non Engraved
4												
5					/	GINE	RINE					
6					)	I HEAD IN						
7						DHE NAME OF THY LORD WHO	149	EB				
8					188		T	i Na				
9						-	1					
10					<	-LA	IDRE					
11							-					
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



2021-22).										
Our Ref. No. CL/	CED/ 8244	Dated:	11-03-22	Test Specification						
Your Ref. No.	822/SDO/BSD/NNS	Dated:	01-03-22	( BS 1881-116 )						



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	07	/03/2	022	Tested on:	08-0	)3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Slab (1:2:4)	31	1	2022	6x6x6		8.4	36	88	5476		Engraved
2	Slab (1:2:4)	31	1	2022	6x6x6		8.4	36	108	6720		Engraved
3	Slab (1:2:4)	31	1	2022	6x6x6		8.5	36	92	5724		Engraved
4												
5					/	ARTINE	RIATE					
6					>	NEAD IN	205 D					
7								F				
8					188							
9					I	-	1					
10					-	- (A	INR <del>E</del> .					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

	Plain and Reinforced Concrete Laboratory Civil Engineering Department University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895	ORIGINAL A carbon copy for the report has been retained in the lab for record.
_		2881 Dr. Aqsa
То:	Sub Divisional Officer Buildings Sub Division Nankana Sahib	
	Project: Establishment of Govt. Associate College for Boys Morekhunda, Nankana Sahib. (ADP No. 347 for	

Our Ref. No. (	-22). CL/CED/ 8245	Dated:	11-03-22	Test Specification
Your Ref. No.	790/SDO/BSD/SKT	Dated:	20-02-22	( BS 1881-116 )



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	04	/03/2	022	Tested on:	08-0	3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	(1:2:4)	28	1	2022	6x6x6		8	36	110	6844		Engraved
2	(1:2:4)	28	1	2022	6x6x6		8	36	77	4791		Engraved
3	(1:2:4)	28	1	2022	6x6x6		8	36	60	3733		Engraved
4												
5					/	GINE	RIATE					
6					)	I NEAD IN	(FIRE )					
7						DE NACE CE THY LORD VIND	4					
8					- SR			IND				
9					}	×						
10					<	-14	IDRE .					
11												
12												
13												
14												
15												
16												
Witness	ed by:	•			·							

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

the Vear 2021 22)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



M.E. A S Enterprises. (Consultant; AA Associates).

Project: Style Textile Mill Raiwind Road (65 Chak)

Our Ref. No. CL/CED/ 8246	Dated:	11-03-22	Test Specification
Your Ref. No. ASE/09	Dated:	04-03-22	(BS 1881-116)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	04	/03/2	2022	Tested on:	08-0	3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Lab # 660, C-20	3	2	2022	6x6x6		8	36	69	4293		Non Engraved
2	Lab # 660, C-20	3	2	2022	6x6x6		8.2	36	78	4853		Non Engraved
3	Lab # 660, C-20	3	2	2022	6x6x6		8	36	88	5476		Non Engraved
4	Lab # 661, C-20	3	2	2022	6x6x6		8	36	53	3298		Non Engraved
5	Lab # 661, C-20	3	2	2022	6x6x6 🧹	GINE	RIA8	36	81	5040		Non Engraved
6	Lab # 661, C-20	3	2	2022	6x6x6	T READ IN	8	36	85	5289		Non Engraved
7						DHE NAME COE THY LORD WHO	4					
8					- A		Contraction of the second	NND I				
9						×	-	<b>7</b>				
10					<	- (A	IDRE °					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

#### inesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



Innovative ® Construction Company. Lahore.

Project: Construction of ABL Branch at Jubilee Town, Lahore.

Our Ref. No. CL	/CED/ 8247	Dated:	03-11-22	Test Specification
Your Ref. No.	ICL/ABL/JT/0322/04	Dated:	04-03-22	(ASTM C39)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:			04/03/2022		Tested on:	08-0	3-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*	Cas DD	-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1		24	2	2022	6Diax12		12.4	28.28	43	3406		Non Engraved
2		24	2	2022	6Diax12		13	28.28	40	3168		Non Engraved
3		24	2	2022	6Diax12		12.6	28.28	54	4277		Non Engraved
4							-					
5						RINE	RIATE					
6						I READ IN						
7						DHE NAME OF THY LORD VIND	4					
8					LSR.							
9							1					
10					<	-LA	INR <del>E</del>					
11												
12												
13												
14												
15												
16												
Witness	Witnessed by:											

#### vitnessea by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



To: Mr. Nouman Rafique, Chief Technical Officer Sabcon Associates (Pvt) Ltd. Lahore.

Project: Construction of Commercial Building at 51A Gulberg-III, Lahore.

Our Ref. No. CL	/CED/ 8248	Dated:	11-03-22	Test Specification
Your Ref. No.	SABCON/2022/CTO/05	Dated:	07-03-22	(ASTM C39)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	07/03/2022		2022	Tested on:	10-0	3-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1		4	2	2022	6Diax12		13	28.28	47	3723		Non Engraved
2		4	2	2022	6Diax12		13	28.28	51	4040		Non Engraved
3												
4												
5					/	GINE	RIATE					
6					>	T NEAD IN	(Filter					
7					11		-4					
8					4.81			NN Ni				
9							1					
10					<	-14	IORE .					
11												
12												
13												
14												
15												
16												
Witness	Witnessed by:											

#### inesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

2894 Engr. Ubaid

#### **Director/Dy. Director Concrete Laboratory**



Project: Construction of 4-Nos Additional Class Room	at First Floor in Govt. Gra	aduate College for V	Vomen
Raiwind Lahore. Our Ref. No. CL/CED/ 8249	Dated:	11-03-22	Test Specification
Your Ref. No. 407/8th	Dated:	03-03-22	(ASTM C39)



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		07/03/2022		022	Tested on:	10-0	3-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(1:2:4)	6	2	2022	6Diax12		13.2	28.28	46	3644		Non Engraved
2	(1:2:4)	6	2	2022	6Diax12		13.4	28.28	55	4356		Non Engraved
3	(1:2:4)	6	2	2022	6Diax12		13	28.28	71	5624		Non Engraved
4												
5					-	EINE	RIATE					
6					-	READ IN						
7						DHE NAME CETHY CORD VAND	4	F				
8					188							
9							1					
10					<	-LA	INRE .					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



A carbon copy for the report has been retained in the lab for record.

> 2905 Engr. Ubaid

ORIGINAL

To: Engr. Abdul Qadeer Khan LANDMARK CONSULTANTS, Gulberg-II, Lahore.

Project: Parkview Apartments			
Our Ref. No. CL/CED/ 8250	Dated:	11-03-22	Test Specification
Your Ref. No. CIV/172/03032022	Dated:	Nil	(ASTM C39)

## COMPRESSION TEST REPORT

Specim	ens received on:	07/03/2022			Tested on:	10-0	3-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1		23	2	2022	6Diax12		14	28.28	61	4832		Engraved
2		23	2	2022	6Diax12		13.8	28.28	33	2614		Engraved
3												
4												
5					/	GINE	RIATE					
6					)	READ W	RIAN					
7						DHE NAME COE THY LORIO WHO		EB				
8					SB 			i Ma				
9												
10						(A	INR <del>E</del> .					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

#### vitnessea by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 2899 Dr. Aqsa

To: Mr. Musaddig Igbal, CM at Extention of Colony Building Project For Master Textile Mills Limited.

Project: Waste Water Treatment Plant.

Our Ref. No. CL/CED/ 8251	Dated:	11-03-22	Test Specification
Your Ref. No. Nil	Dated:	07-03-22	(BS 1881-116)

## COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	07	/03/2	022	Tested on:	08-0	3-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)		Water Absorpti on (%)	Remarks
1	3000 Psi	27	2	2022	6x6x6	(itg/ giiis) 	(Rg/ gills) 9	36	42	2613		Non Engraved
2	3000 Psi	27	2	2022	6x6x6		8	36	59	3671		Non Engraved
3	3000 Psi	27	2	2022	6x6x6		9	36	56	3484		Non Engraved
4												
5						ARTHE	RIATE					
6					)	MEAD IN	No.					
7					11	DHE NAME OF THY CORD VIND	4	EP				
8					88							
9						2	-					
10					<	-LA	INRE .					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 2901 Dr. Aqsa

To: **Resident Engineer** 

**Engineering Services Consultants.** 

Project: Establishment of Center of Excellence Boys at Chakwal. (Secondary Section).

Our Ref. No. CL	/CED/ 8252	Dated:	03-11-22	Test Specification
Your Ref. No.	RE/ESC/COE/2022-29	Dated:	05-03-22	(ASTM C39)

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received o	n:	07	07/03/2022 Tested on:			08-0	3-22	in dry/we	t condition		ONLINE REPORT	
Sr. No.	Mark*			•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	GF Slab Grid 0), (1-12)	(C-	7	2	2022	6Diax12		12.4	28.28	47	3723		Non Engraved
2	GF Slab Grid 0). (1-12)	(C-	7	2	2022	6Diax12		13.8	28.28	65	5149		Non Engraved
3	GF Slab Grid 0). (1-12)	(C-	7	2	2022	6Diax12		13	28.28	60	4752		Non Engraved
4													
5						/	GINE	RIATE					
6						- )	NEAD W						
7							DHE NAME OE THY LORD WHO	14.9	EB				
8						188			I Ma				
9							-	1					
10						<	- (A	IORE .					
11													
12													
13													
14													
15													
16													
Witness	Vitnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



2902 Dr. Aqsa

To:	Engr. Zia ul Hassan Khan											
	Resident Engine	Resident Engineer, Chiniot										
	Project: Construction of 2 Nos Academic Blocks at Chiniot Campus of Government College University,											
	Faisalabad. (Contractor; M/s Alcon Associates).											
	Our Ref. No. CL	/CED/ 8253	Dated:	11-03-22	Test Specification							
	Your Ref. No.	DCS/RE/UET/GCUF/2022/040	Dated:	05-03-22	(BS 1881-116)							

# **COMPRESSION TEST REPORT**



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	07/03/2022		022	Tested on:	n: 08-03-22		in dry/wet condition			ONLINE REPORT	
Sr. No.	Mark*		•	Date*	Size	Wet Weight		Area of X-Section		Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 ( 76)	
1	Block-II, Grid-J/3~7	6	2	2022	6x6x6		8.8	36	127	7902		Non Engraved
2	Block-II, Grid-J/3~7	6	2	2022	6x6x6		8.6	36	126	7840		Non Engraved
3	Block-II, Grid-J/3~7	6	2	2022	6x6x6		8.8	36	97	6036		Non Engraved
4	Block-I, LGF Slab Grid- B~1 X 1~3	26	2	2022	6x6x6		8.4	36	112	6969		Non Engraved
5	Block-I, LGF Slab Grid- B~1 X 1~3	26	2	2022	6x6x6 🧹	BILLE	8.4	36	90	5600		Non Engraved
6	Block-I, LGF Slab Grid- B~1 X 1~3	26	2	2022	6x6x6	DIE NAME	8.6	36	146	9084		Non Engraved
7						LORD WHO CREATES	ر بهت <del>به ک</del> ی طنق،	<b>*</b>				
8												
9						10		×				
10						A	IORE					
11		-										
12												
13												
14												
15												
16												
Witnessed by:												

#### Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 2904 Dr. Aqsa

#### To: Muhammad Saleem, GM

Professional Construction Services (Pvt.) Ltd.

Project: Construction of TCF School at Chack # 507-1 Burewala, Vehari.

Our Ref. No. CL	/CED/ 8254	Dated:	11-03-22	Test Specification
Your Ref. No.	PCS/22/Eng-22	Dated:	07-03-22	( BS 1881-116 )

#### COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	07	/03/2	2022	Tested on: 08-03-22 in dry/wet condition							
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)		Water Absorpti on (%)	Remarks
1	GF Slab (1:2:4)	26	1	2022	6x6x6		8	36	63	3920		Non Engraved
2												
3												
4												
5					/	HINE	RIATE					
6					- )	READ IN	A DE					
7							-E					
8												
9						<u></u>						
10					<	(A	INR <del>E</del> .					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

#### illiesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 2904 Dr. Aqsa

#### To: Muhammad Saleem, GM

Professional Construction Services (Pvt.) Ltd.

Project: Construction of TCF School at Chack # 507-1 Burewala, Vehari.

Our Ref. No. CL	/CED/ 8255	Dated:	03-11-22	Test Specification
Your Ref. No.	PCS/22/Eng-22A	Dated:	07-03-22	( BS 1881-116 )

#### COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	07	/03/2	2022	Tested on:	08-0	)3-22	in dry/we	t condition			
Sr. No.	Mark*			Date* YYYY	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	GF Slab (1:2:4)	26	1	2022	6x6x6		8.2	36	69	4293		Non Engraved
2												
3												
4												
5					/	RINE	RIATE					
6					- )	READIN	2 DE					
7							-E					
8												
9						2						
10					<	-LA	INRE					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

#### illiesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/


1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



Dated:

(ASTM C39)

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 03/03/202				022	Tested on:	11-0	3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate Ioad (Imp.Tons)		Water Absorpti on (%)	Remarks
1	Lab # 42 (4000 Psi)	31	1	2022	6Diax12		13.4	28.28	63	4990		Non Engraved
2	Lab # 42 (4000 Psi)	31	1	2022	6Diax12		13.2	28.28	63	4990		Non Engraved
3	Lab # 42 (4000 Psi)	31	1	2022	6Diax12		13	28.28	61	4832		Non Engraved
4	Lab # 41 (4000 Psi)	31	1	2022	6Diax12		13.2	28.28	68	5386		Non Engraved
5	Lab # 41 (4000 Psi)	31	1	2022	6Diax12	RINE	13.2	28.28	91	7208		Non Engraved
6	Lab # 41 (4000 Psi)	31	1	2022	6Diax12	I READ IN	13.4	28.28	84	6653		Non Engraved
7						DHE NAME OF THY LORD WHO	149	EB				
8					- Sa			UNI I				
9						-						
10					<	- (A	ER L					
11							-					
12												
13												
14												
15												
16												
Witnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



To:

ain	and	<b>Reinforced Concrete Laboratory</b>
	Civil	Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 2908 Dr. Yousaf

M. Nadeem Zafar Ullah Incharge (Civil) For Managing Director, SNGPL, 21-Kashmir Road, Lahore.

Project: Construction of Domestic Meter Inspection Shop at Faisalabad.

Our Ref. No. CL/CED/ 8257	Dated:	11-03-22	Test Specification
Your Ref. No. CC/DMIS/FSD	Dated:	07-03-22	(BS 1881-116)

## COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	08	/03/2	2022	Tested on:	11-(	)3-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*			Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1		17	1	2022	6x6x6		9	36	148	9209		Engraved
2		17	1	2022	6x6x6		8.8	36	140	8711		Engraved
3												
4												
5						ARTHE	RING					
6					)	MEAD IN	Salt D					
7					11	DHE NAME OF THY CORD WHO		E .				
8					188							
9						2						
10					- <	-LA	INRE .					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL
A carbon copy for
the report has
been retained in
he lab for record.

2910 Dr. Yousaf

To: Engr. Abdul Qadeer Khan LANDMARK CONSULTANTS (Pvt) Ltd. Gulberg-II, Lahore.

Project: Parkview Apartments.											
Our Ref. No. CL/CED/ 8258	Dated:	11-03-22	Test Specification								
Your Ref. No. CIV/172/03032022	Dated:	Nil	( ASTM C39 )								

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	08	/03/2	022	Tested on:	11-0	3-22	in dry/wet condition			ONLINE REPORT	
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)		Water Absorpti on (%)	Remarks
1		27	2	2022	6Diax12		13.8	28.28	73	5782		Non Engraved
2		27	2	2022	6Diax12		14	28.28	49	3881		Non Engraved
3		27	2	2022	6Diax12		13.4	28.28	43	3406		Non Engraved
4												
5					/	HINE	RINA					
6					)	READ IN	PAUS D					
7						DHE NAME OF THY CORD WHO		EP-				
8					188							
9						2		<b>7</b>				
10					- <	-LA	IORE .					
11												
12												
13												
14												
15												
16												
Witnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



# **Plain and Reinforced Concrete Laboratory Civil Engineering Department**

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 2911 Dr. Yousaf

To: **Muhammad Imran Khan** 

Material Engineer ECSP, MPA HOSTEL, Phase-II, Lahore.

Project: Engineering Consultancy Services for Construction of MPA's Hostel Lahore, Phase-II.

Our Ref. No. CL/	/CED/ 8259	Dated:	11-03-22	Test Specification
Your Ref. No.	340/ECSP/MPA/ME/18	Dated:	24/02/2022	( BS 1881-116 )

## COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	08	/03/2	2022	Tested on:	11-0	3-22	in dry/wet condition				
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	2nd Floor Col. (Group No.2)	27	1	2022	6x6x6		8.4	36	84	5227		Engraved
2	2nd Floor Col. (Group No.2)	27	1	2022	6x6x6		8.4	36	76	4729		Engraved
3	2nd Floor Col. (Group No.2)	27	1	2022	6x6x6		8.2	36	118	7342		Engraved
4												
5					/	ARINE	RIATE					
6					)	NEAD N	XUS D					
7						DHE NAME OF THY LORD WHO	4					
8			-		/SB		T	i Ma				
9			-		I	-	ł					
10					<	-LA	INRE					
11												
12												
13												
14												
15												
16												
Witnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



# **Plain and Reinforced Concrete Laboratory Civil Engineering Department**

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 2911 Dr. Yousaf

To: **Muhammad Imran Khan** 

Material Engineer ECSP, MPA HOSTEL, Phase-II, Lahore.

Project: Engineering consultancy services for construction of MPA's Hostel Lahore, Phase-II.

Our Ref. No. CL	/CED/ 8260	Dated:	11-03-22	<b>Test Specification</b>
Your Ref. No.	340/ECSP/MPA/ME/19	Dated:	06-03-22	( BS 1881-116 )

### COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	08	/03/2	2022	Tested on:	11-0	3-22	in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Lift Wall 2nd Floor (Group No.2)	7	2	2022	6x6x6		8.2	36	126	7840		Non Engraved
2	Lift Wall 2nd Floor (Group No.2)	7	2	2022	6x6x6		8.2	36	124	7716		Non Engraved
3	Lift Wall 2nd Floor (Group No.2)	7	2	2022	6x6x6		8.2	36	87	5413		Non Engraved
4												
5					/	ARTNE	RIATE					
6					>	NEAD IN	ALL ST D					
7					411	DHE NAME OF THY CORD WHO	-4	E				
8					188							
9							1					
10					<	-LA	INKE					
11												
12												
13												
14												
15												
16												
Witnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



2912 Dr. Yousaf

ORIGINAL

To: M. Ijaz Faroog

Usman Ibrahim Construction, DHA, Lahore.

Project: AL-FATAH E-MALL, E-125 Main Boulevard Gulberg-III.

Our Ref. No. CL/CED/ 8261	Dated:	11-03-22	Test Specification
Your Ref. No. Nil	Dated:	08-03-22	(ASTM C39)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	mens received on: 08/03/2022 Tested on: 11-03-22 in dry/wet condition					ONLINE REPORT						
Sr. No.	Mark*	Cas DD	•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1		22	2	2022	6Diax12		13	28.28	31	2455		Non Engraved
2		22	2	2022	6Diax12		13.4	28.28	48	3802		Non Engraved
3		22	2	2022	6Diax12		13.2	28.28	25	1980		Non Engraved
4												
5					/	GINE	RIATE					
6					- >	T READ IN	Parts IN	<b>X</b>				
7						CE THY LORD WHO						
8												
9						×						
10					<	-4	IONE ?					
11												
12												
13												
14												
15												
16												
Witnessed by:												

#### illesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 2915 Dr. Yousaf

То:	: Engr. Muhammad Fiaz, Sub Divisional Officer (Works Wing). The Punjab Employees Social Security Institution (Head Office), 3/A Gulberg-V, Lahore.									
	Project: Construction of Social Security Health Facility at Taunsa Sharif. (M/s Al-Tawakkal Construction Company).									
	Our Ref. No. CL/CED/ 8262 Dated: 11-03-22 <u>Test Specific</u>									
	Your Ref. No. SS.DC/454	Dated:	28-02-22	(BS 1881-116)						

## COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	09	/03/2	2022	Tested on:	11-0	)3-22	in dry/wet condition			ONLINE REPORT	
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)		Water Absorpti on (%)	Remarks
1		7	2	2022	6x6x6		8	36	57	3547		Engraved
2		7	2	2022	6x6x6		8	36	63	3920		Engraved
3												
4												
5					/	HINE	RING					
6					)	READ IN	PAUS D					
7						DEE NAME OF THY CORD VIND	- 4	FP				
8					188			IND				
9						2		<b>7</b>				
10					- <	-LA	INRE .					
11												
12												
13												
14												
15												
16												
Witnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory

	Plain and Reinforced Cone Civil Engineering Depar University of Engineering and Technology, Landline: 042-99029245 & 042-99029202	rtment	5	ORIGINAL A carbon copy for the report has been retained in the lab for record.
				2916 Dr. Yousaf
To:	Sh. Muhammad Tariq Engineer REC, For the Help Care Society (TAC)			
	Project: Construction of Extension Block (The Help Care So (Contractor; M/S Muhammad Ashfaq & Sons Pvt. Ltd.) Our Ref. No. CL/CED/ 8263	ociety) TAC School Jo Dated:	ohar Town, Lahore. 11-03-22	Test Specification

Dated:

05-03-22

Your Ref. No. **JTC EXT-8** 

#### **COMPRESSION TEST REPORT**



(ASTM C39)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	pecimens received on: 09-03-22 Tested on: 11-03-22 in dry/wet condition				ONLINE REPORT							
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)		Water Absorpti on (%)	Remarks
1	GF Columns	26	2	2022	6Diax12		13	28.28	63	4990		Non Engraved
2	GF Columns	26	2	2022	6Diax12		13.2	28.28	65	5149		Non Engraved
3	GF Columns	26	2	2022	6Diax12		13	28.28	63	4990		Non Engraved
4												
5						RINE	RIATE					
6					-	READ IN						
7						DHE NIGHE OF THY CORD VIND		F				
8					188							
9												
10					<	-LA	INRE .					
11												
12												
13												
14												
15												
16												
Witnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory

- Particular		Plain and Reinforced Co Civil Engineering De University of Engineering and Technolo Landline: 042-99029245 & 042-99029202	partment	5	ORIGINAL A carbon copy for the report has been retained in the lab for record.
					2917 Dr. Yousaf
То:		. (R) Ubaid ur Rehman V) PEC Bldg Proj			
	Project	: Construction of PEC Regional Office Lahore.			
	Our Re	f. No. CL/CED/ 8264	Dated:	11-03-22	Test Specification

Our Ref. No. CL/	CED/ 8264	Dated:	11-03-22	Test Specification
Your Ref. No.	901/NLC-TD(JV)/PEC/556	Dated:	07-03-22	(ASTM C39)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	09	/03/2	2022	Tested on:	11-0	3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	8th to 9th Floor Part-2 (1599)	5	2	2022	6Diax12		12.8	28.28	66	5228		Non Engraved
2	8th to 9th Floor Part-2 (1605)	5	2	2022	6Diax12		13	28.28	66	5228		Non Engraved
3	8th to 9th Floor Part-2 (1608)	5	2	2022	6Diax12		13	28.28	58	4594		Non Engraved
4												
5						RINE	RIATE					
6					)	NEAD IN	ALS D					
7						DHE NAME OF THY LORD WHO						
8					- Sa							
9						-	ł					
10					<	-LA	INK-					
11							-					
12												
13												
14												
15												
16												
Witness	ed by:											

#### vittiesseu by.

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory

A LINE AND		Plain and Reinforced Co Civil Engineering Deg University of Engineering and Technolo Landline: 042-99029245 & 042-99029202	partment	5	ORIGINAL A carbon copy for the report has been retained in the lab for record.
					2917 Dr. Yousaf
To:		. (R) Ubaid ur Rehman IV) PEC Bldg Proj			
	Projec	t: Construction of PEC Regional Office Lahore.			
	Our Re	ef. No. CL/CED/ 8265	Dated:	11-03-22	Test Specification

Our Ref. No. CL/	CED/ 8265	Dated:	11-03-22	Test Specification
Your Ref. No.	901/NLC-TD(JV)/PEC/557	Dated:	07-03-22	(ASTM C39)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	09	/03/2	2022	Tested on:	11-0	3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	Left Wall 8th to 9th Floor (1610)	8	2	2022	6Diax12		13	28.28	70	5545		Non Engraved
2	Left Wall 8th to 9th Floor (1614)	8	2	2022	6Diax12		13	28.28	60	4752		Non Engraved
3	Left Wall 8th to 9th Floor (1616)	8	2	2022	6Diax12		12.8	28.28	73	5782		Non Engraved
4												
5						GINE	RIATE					
6					>	T HEAD IN						
7						DHE NHOLE OF THY LORD VIND	17	FB				
8					188							
9						-	ł					
10						- (A	RH					
11							-					
12												
13												
14												
15												
16												
Witness	sed by:											

#### vittiesseu by.

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory

		Universit	Ind Reinforced Civil Engineering I by of Engineering and Techn -99029245 & 042-99029202	Departmen nology, Lahore	nt	5	ORIGINAL A carbon copy for the report has been retained in the lab for record.
							2924 Dr. Yousaf
To:		Kaleem Ullah ent Engineer, Az	ZEA Sialkot Residency				
	Muham		of Flyover at Shahabpura Cho vt. Contractor). 8266	owk Defence Ro	ad Sialkot in Dated:	District Sialkot. (M/s 11-03-22	Test Specification



(BS 1881-116)

09-03-22

Dated:

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

AZEA/SLK/SF/22/22

Specim	ens received on:	10	/03/2	2022	Tested on:	11-0	3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Absorpti	Remarks
		DD	MM	ΥΥΥΥ	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Girder # 02	2	2	2022	6x6x6		8.4	36	98	6098		Non Engraved
2	Girder # 02	2	2	2022	6x6x6		8.4	36	107	6658		Non Engraved
3	Girder # 02	2	2	2022	6x6x6		8.4	36	114	7093		Non Engraved
4	Deck Slab #19	4	2	2022	6x6x6		8.4	36	88	5476		Non Engraved
5	Deck Slab #19	4	2	2022	6x6x6 🧹	RINE	8.2	36	108	6720		Non Engraved
6	Deck Slab #19	4	2	2022	6x6x6	T READ IN	8.2	36	80	4978		Non Engraved
7	R.W. (Section=2-2) R/s 1st Step	7	2	2022	6x6x6	DHE NIKKE COETHY LORD WHO	8.4	36	90	5600		Non Engraved
8	R.W. (Section=2-2) R/s 1st Step	7	2	2022	6x6x6		8.4	36	90	5600		Non Engraved
9	R.W. (Section=2-2) R/s 1st Step	7	2	2022	6x6x6	-	8.6	36	84	5227		Non Engraved
10					- <	- (A	RE					
11												
12												
13												
14												
15												
16												
Witness	Witnessed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

Your Ref. No.

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



•		•			
Our Ref. No. CL/	/CED/ 8267		Dated:	11-03-22	Test Specification
Your Ref. No.	UET/RCC/091/22		Dated:	10-03-22	( BS 1881-116 )

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 10/03/2022 Tested on: 11-03-22 in dry/wet condition						ONLINE REPORT						
Sr. No.	Mark*		•	Date*	Size	Wet Weight		Area of X-Section		Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (70)	
1	Foundation (1:2:4)	8	2	2022	6x6x6		8.6	36	71	4418		Non Engraved
2	Foundation (1:2:4)	8	2	2022	6x6x6		8.4	36	94	5849		Non Engraved
3	Foundation (1:2:4)	8	2	2022	6x6x6		8.8	36	84	5227		Non Engraved
4	Pile Cap (1: 1.5: 3)	9	2	2022	6x6x6		8.4	36	82	5102		Non Engraved
5	Pile Cap (1: 1.5: 3)	9	2	2022	6x6x6 🧹	RINE	8.6	36	92	5724		Non Engraved
6	Pile Cap (1: 1.5: 3)	9	2	2022	6x6x6	I READ IN	8.4	36	129	8027		Non Engraved
7	Column (G-11- 12/ENG)	7	2	2022	6x6x6	DHE NHOLE OF THY LORD VIND	8.6	36	114	7093		Non Engraved
8	Column (G-11- 12/ENG)	7	2	2022	6x6x6		8.4	36	122	7591		Non Engraved
9	Column (G-11- 12/ENG)	7	2	2022	6x6x6	-	8.6	36	100	6222		Non Engraved
10					<	(A	INR <del>E</del>					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



the report has been retained in the lab for record.

ORIGINAL

2887 Engr. Ubaid

To: Municipal Officer (I&S).

Municipal Committee Toba Tek Singh.

Project: Improvement of General Bus Stand Toba Tek Singh.

Our Ref. No. CL/CED/ 8268	Dated:	11-03-22	Test Specification
Your Ref. No. 882/MC/TTS	Dated:	19/02/2022	( )

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	7-03·	-22	Tested on:	10-0	)3-22	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	Rectangular, Grey, 80mm				7.9 x 3.9 x 3.1		3845	30.81	116	8434		
2	Rectangular, Grey, 80mm				7.9 x 3.9 x 3.1		3895	30.81	118	8579		
3	Rectangular, Red, 80mm				7.9 x 3.9 x 3.1		3585	30.81	93	6761		
4	Rectangular, Red, 80mm				7.9 x 3.9 x 3.1		3560	30.81	100	7270		
5					- /	HINE	RIATE					
6					- )	NEAD IN	AUX D					
7						CORD VIND	- J					
8												
9						2-						
10					- <	LA	INRE .					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



Our Ref. No. CL/CED/ 8269	Dated:	11-03-22	Test Specification
Your Ref. No. 264/K	Dated:	24/02/2022	( )

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		0	7-03	7-03-22 Tested on:		10-03-22		in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	Rectangular, Grey, 60mm				7.8 x 3.8 x 2.3		2555	29.64	86	6499		
2	Rectangular, Grey, 60mm				7.8 x 3.8 x 2.3		2660	29.64	93	7028		
3	Rectangular, Grey, 60mm				7.8 x 3.8 x 2.3		2555	29.64	98	7406		
4	Rectangular, Grey, 60mm				7.8 x 3.8 x 2.3		2625	29.64	72	5441		
5		-				GINE	RIATE					
6		-			>	T READ W						
7						DHE NHOLE OF THY LORD VIND	149	EP				
8					188							
9		-				-						
10		-			<	- (A	ER L					
11												
12												
13												
14												
15												
16												
Witnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 2885 Engr. Ubaid

To: **District Officer** 

District Council Toba Tek Singh.

Project: Improvement of Road/Construction of Soling, Resoling, Tuff Tile Rajana.

Our Ref. No. CL/	CED/ 8270	Dated:	11-03-22	Test Specification
Your Ref. No.	369/DO(I&S)/DC/TTS	Dated:	14/12/2021	( )

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		0	7-03	-22	Tested on:	10-03-22		in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*		-	Date* YYYY	Size (in)	Wet Weight	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Rectangular, Grey, 60mm				(III) 7.8 x 3.9 x 2.3	(rtg/ gills) 	(Rg/ gills) 2860	30.42	(imp. rons) 110	(psi) 8100		
2	Rectangular, Grey, 60mm				7.8 x 3.9 x 2.3		2880	30.42	121	8910		
3	Rectangular, Grey, 60mm				7.8 x 3.9 x 2.3		2535	30.42	71	5228		
4	Rectangular, Grey, 60mm				7.8 x 3.9 x 2.3		2940	30.42	138	10162		
5	Rectangular, Red, 60mm				7.8 x 3.9 x 2.3	GINE	2630	30.42	80	5891		
6	Rectangular, Red, 60mm				7.8 x 3.9 x 2.3	READ W	2660	30.42	64	4713		
7					11	DHE NARDE COE THY LORD WHE	-4					
8					88			IND -				
9						2		<b>X</b>				
10					<	-4	IORE .					
11												
12												
13												
14												
15												
16												
Witnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory







Chief Resident	Engineer, Package-1 (M/s Hajvary Construct	tion Services).		
•	uction/Improvement & Rehabilitation of at G aid e Azam Interchange Left Side.	rade from Warra Ch	ungi Stop Service Ro	ad
Our Ref. No. CL	/CED/ 8271	Dated:	11-03-22	Test Specification
Your Ref. No.	4042/13/FAM/Tough-Paver-206	Dated:	14/02/2022	()



( ---- )

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		0	3-03	-22	Tested on:	10-03-22		in dry/wet condition			ONLINE REPORT	
Sr. No.	Mark*		-	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Water Absorpti on (%)	Remarks
	Rectangular, Grey,	עט	MIM	YYYY	,	(Kg/ gms)	(Kg/ gms)		(Imp.Tons)			
1	80mm				7.9 x 3.9 x 3		3405	30.81	41	2981		
2	Rectangular, Grey, 80mm				7.9 x 3.9 x 3		3470	30.81	48	3490		
3	Rectangular, Red, 80mm				7.9 x 3.9 x 3		3635	30.81	44	3199		
4	Rectangular, Red, 60mm				7.9 x 3.9 x 2.3		2585	30.81	78	5671		
5	Rectangular, Grey, 60mm				7.9 x 3.9 x 2.3	RINE	3055	30.81	124	9015		
6	Rectangular, Grey, 60mm				7.9 x 3.9 x 2.3	NEAD IN	2990	30.81	110	7997		
7						DHE NAME OF THY CORD VAND		F				
8					188							
9						-						
10					<	-LA	INRE .					
11							-					
12												
13												
14												
15												
16												
Witnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory