

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

3267 Dr. Rizwan Riaz

To: Muhammad Sohail Anjum, Project Manager

MS Tower Developers, J4 Lahore.

Project: Construction of MS Tower at Plot 450,451 Johar Town, Lahore.

 Our Ref. No. CL/CED/
 8811
 Dated:
 18-05-22
 Test Specification

 Your Ref. No.
 MST/UET/2022/C-027
 Dated:
 16-05-22
 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-05-22 Tested on: 18-05-22 in dry/wet condition





Sr. No.	Sr. No. Mark*		ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	3000 Psi (58)	14	4	2022	6Diax12		13	28.28	45	3564		Non Engraved
2	3000 Psi (61)	14	4	2022	6Diax12		13	28.28	49	3881		Non Engraved
3												
4												
5					🔏	GINE	RINE					
6						READIN	200					
7						DHE NAME OF THY LIGHT WHO	JE	#				
8					so							
9						<u></u>	- 2					
10						LA	IORE					
11												
12												
13												
14												
15												
16												
\A/:4:0 0 0 0					-		-	-		•		

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

3267 Dr. Rizwan Riaz

To: Muhammad Sohail Anjum, Project Manager

MS Tower Developers, J4 Lahore.

Project: Construction of MS Tower at Plot 450,451 Johar Town, Lahore.

 Our Ref. No. CL/CED/
 8812
 Dated:
 18-05-22
 Test Specification

 Your Ref. No.
 MST/UET/2022/C-028
 Dated:
 16-05-22
 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-05-22 Tested on: 18-05-22 in dry/wet condition





Sr. No.	Mark*	Casting Date*			Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	3000 Psi (67)	17	4	2022	6Diax12		13.8	28.28	43	3406		Non Engraved
2	3000 Psi (71)	17	4	2022	6Diax12		14.8	28.28	39	3089		Non Engraved
3												
4												
5					/	GENE	RINE					
6						READIN	200					
7						DHE NAME OF THY LIGHT WHO	JE	-				
8					es							
9												
10						LA	IORE					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL**

A carbon copy for the report has been retained in the lab for record.

3269 Dr. Rizwan Riaz

To: Muhammad Sohail Anjum, Project Manager

MS Tower Developers, J4 Lahore.

Project: Construction of MS Tower at Plot 450,451 Johar Town, Lahore.

Our Ref. No. CL/CED/ 8813 Dated: 18-05-22 **Test Specification** (ASTM C39)

Your Ref. No. MST/UET/2022/C-026 Dated: 16-05-22

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-05-22 Tested on: 18-05-22 in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	3000 Psi (62)	2	4	2022	6Diax12		13.2	28.28	45	3564		Non Engraved
2	3000 Psi (52)	2	4	2022	6Diax12		13.8	28.28	49	3881		Non Engraved
3												
4												
5					/	GINE	RINE					
6						READIN	200					
7						DHE NAME OF THY LIDRO WHO	JE					
8					es							
9												
10					🤇	-LA	IORE					
11												
12												
13												
14												
15												
16												
\A/:4:0000								<u> </u>			<u> </u>	

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

3269 Dr. Rizwan Riaz

To: Muhammad Sohail Anjum, Project Manager

MS Tower Developers, J4 Lahore.

Project: Construction of MS Tower at Plot 450,451 Johar Town, Lahore.

Our Ref. No. CL/CED/ 8814 Dated: 18-05-22 <u>Test Specification</u>

Your Ref. No. MST/UET/2022/C-025 Dated: 16-05-22 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-05-22 Tested on: 18-05-22 in dry/wet condition





Sr. No.	Sr. No. Mark*		ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks						
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)							
1	3000 Psi (41)	1	4	2022	6Diax12		13.2	28.28	39	3089		Non Engraved						
2	3000 Psi (42)	1	4	2022	6Diax12		13.4	28.28	43	3406		Non Engraved						
3																		
4																		
5					/	MEINE	RINE											
6						READIN	200											
7						DE THY LORD WHO	JE	#										
8					es													
9																		
10						-LA	IORE											
11																		
12																		
13																		
14																		
15																		
16																		
\A/:4							With a coord by:											

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL**

A carbon copy for the report has been retained in the lab for record.

3269 Dr. Rizwan Riaz

To: Muhammad Sohail Anjum, Project Manager

MS Tower Developers, J4 Lahore.

Project: Construction of MS Tower at Plot 450,451 Johar Town, Lahore.

Our Ref. No. CL/CED/ 8815 Dated: 18-05-22 **Test Specification** (ASTM C39)

Your Ref. No. MST/UET/2022/C-024 Dated: 16-05-22

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-05-22 Tested on: 18-05-22 in dry/wet condition





Sr. No.	Mark*		Casting Date*		Size (in)	Wet Weight	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	3000 Psi (29)	30	3	2022	6Diax12		13	28.28	27	(psi) 2139		Non Engraved
2	3000 Psi (33)	30	3	2022	6Diax12		13.4	28.28	39	3089		Non Engraved
3												
4												
5					🔏	RINE	RING					
6						MEAD IN	200					
7						DHE NAME OF THY LORD WHO	الله	-				
8					- 08			in.				
9							1					
10					<	-LA	IORE					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

3269 Dr. Rizwan Riaz

To: Muhammad Sohail Anjum, Project Manager

MS Tower Developers, J4 Lahore.

Project: Construction of MS Tower at Plot 450,451 Johar Town, Lahore.

Our Ref. No. CL/CED/ 8816 Dated: 18-05-22 <u>Test Specification</u>

Your Ref. No. MST/UET/2022/C-023 Dated: 16-05-22 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-05-22 Tested on: 18-05-22 in dry/wet condition





Sr. No.	Mark*	Casting Date*			Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	3000 Psi (26)	28	3	2022	6Diax12		13	28.28	31	2455		Non Engraved
2	3000 Psi (35)	28	3	2022	6Diax12		13.4	28.28	33	2614		Non Engraved
3												
4												
5					/	GINE	RINE					
6						READIN	200					
7						DHE NAME OF THY LIDRO WHO	- E - C - C - C - C - C - C - C - C - C	-				
8					es							
9						<u></u>						
10			-		<	-LA	IORE.					
11			I									
12			-									
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

3269 Dr. Rizwan Riaz

To: Muhammad Sohail Anjum, Project Manager

MS Tower Developers, J4 Lahore.

Project: Construction of MS Tower at Plot 450,451 Johar Town, Lahore.

Our Ref. No. CL/CED/ 8817 Dated: 18-05-22 <u>Test Specification</u>

Your Ref. No. MST/UET/2022/C-022 Dated: 16-05-22 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-05-22 Tested on: 18-05-22 in dry/wet condition





		1				1	1	1	1	1		
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)		(Imp.Tons)	(psi)	on (%)	
1	3000 Psi (16)	27	3	2022	6Diax12		13.4	28.28	43	3406		Non Engraved
2	3000 Psi (18)	27	3	2022	6Diax12		13.2	28.28	43	3406		Non Engraved
3												
4												
5					/	GENE	RING					
6						READW	Salar C	X				
7						DHE NAME OF THY LIDRO WHO	- T	#				
8					63 EE	ظلل	2 31	<u> </u>				
9),—						
10					<	LA	IORE.					
11												
12												
13												
14												
15												
16												
\A/:4:0 0 0 0					•	-		-	-			

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

3269 Dr. Rizwan Riaz

To: Muhammad Sohail Anjum, Project Manager

MS Tower Developers, J4 Lahore.

Project: Construction of MS Tower at Plot 450,451 Johar Town, Lahore.

 Our Ref. No. CL/CED/
 8818
 Dated:
 18-05-22
 Test Specification

 Your Ref. No.
 MST/UET/2022/C-021
 Dated:
 16-05-22
 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-05-22 Tested on: 18-05-22 in dry/wet condition





Sr. No. Mark*		Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	3000 Psi (8)	26	3	2022	6Diax12		13	28.28	49	3881		Non Engraved
2	3000 Psi (11)	26	3	2022	6Diax12		13.2	28.28	33	2614		Non Engraved
3	3000 Psi (13)	26	3	2022	6Diax12		13.4	28.28	37	2931		Non Engraved
4												
5					/	GINE	RINE					
6						TREADIN	San C	X				
7						DE NAME OF THY LORD WHO	- N	至-				
8					- 60	رشيا						
9							9	7				
10					(-UA	IOR'S					
11												
12												
13												
14												
15												
16												
\A/:4:0 0 0 0												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.