

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

4309 Dr. Umbreen

(----)

To: Mr. Aqeel Haider

Taj Gasoline Habibabad

Project: Construction of Taj Gasoline Oil Depot Habibabad

Our Ref. No. CL/CED/ 468 Dated: 28/11/2022 <u>Test Specification</u>

Your Ref. No. Nil Dated: 25/11/2022

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 25/11/2022 Tested on: 28/11/2022 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Rectangular, Grey, 80mm				7.8 x 3.8 x 3.1		3725	29.64	96	7255		
2	Rectangular, Grey, 80mm				7.8 x 3.8 x 3.1		3650	29.64	83	6273		
3	Rectangular, Grey, 80mm				7.8 x 3.8 x 3.1		3645	29.64	77	5819		
4												
5						CINE	RING					
6						READ IN	200					
7						DHE NAME OF THY LIGHT WHO	100	EB				
8					es							
9						-	1					
10					🤇	"-LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 4312 Dr. Umbreen

To: Mr. Aamir Bashir, Project Manager

Our Ref. No. CL/CED/ 469

Velosi Integrity and Safety Pakistan (Pvt.) Ltd.

Project: Resident Supervision of Regional Campuses for Allama Iqbal Open University located at Sahiwal.

Dated:

28/11/2022

Your Ref. No. VISPL-L-C22-321 Dated: 25/11/2022

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 25/11/2022 Tested on: 28/11/2022 in dry/wet condition



Test Specification

(BS 1881-116)



Sr. No.	Mark*	Castir		Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Raft Foundation (1:1.5:3) 3750 Psi	15	10	2022	6x6x6		8.4	36	96	5973		Non Engraved
2	Raft Foundation (1:1.5:3) 3750 Psi	15	10	2022	6x6x6		8.4	36	124	7716		Non Engraved
3	Raft Foundation (1:1.5:3) 3750 Psi	15	10	2022	6x6x6		8.4	36	94	5849		Non Engraved
4												
5						CINE	RINE					
6						READIN		X				
7						DHE NIGGE OF THY LIDRO WHO	-E	==				
8					S							
9							1					
10						"-LA	IDRE					
11					-		-					
12												
13												
14												
15												
16												
1871			<u> </u>			<u> </u>						

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

4313 Dr. Umbreen

To: Mr. Muneeb Ali Hamza

Rang Mahal, Lahore.

Project: Construction of Taimoor Trading

Our Ref. No. CL/CED/ 470-1 of 2

Your Ref. No. Nil

Dated: 28/11/2022

Dated:

Test Specification

Nil (BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 25/11/2022 Tested on: 28/11/2022 in dry/wet condition





Sr. No.	Mark*			Date*	Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	IVIIVI	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	(,	
1		15	11	2022	6x6x6		8.2	36	37	2302		Engraved
2												
3												
4												
5					/	GINE	RIATE					
6						READIN						
7						DHE NAME OF THY LIDRO WHO	- E	-				
8					es			INO				
9												
10						º-∠A	ORE.					
11							-					
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

4313 Dr. Umbreen

To: Mr. Muneeb Ali Hamza Rang Mahal, Lahore.

Project: Construction of Taimoor Trading.

Our Ref. No. CL/CED/ 470-2 of 2

Your Ref. No. Nil

Dated:

Dated:

28/11/2022

Nil

Test Specification

(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 25/11/2022 Tested on: 28/11/2022 in dry/wet condition





Sr. No.	Mark*			Date*	Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (70)	
1		15	11	2022	6Diax12		13.8	28.28	59	4673		Engraved
2												
3												
4												
5					/	GINE	RINE					
6						READIN		X				
7						DE THY LORD WHO	- E / F	-				
8					SS							
9						-	-					
10					<	-LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

4308 Dr. Umbreen

To: Mr. Usman Meer

SINACO Engineers (Pvt.) Ltd.

Project: Construction of National Foods Galaxy Project at FIEDMC Sahianwala, Faisalabad.

 Our Ref. No. CL/CED/
 471
 Dated:
 28/11/2022
 Test Specification

 Your Ref. No.
 00277-2022
 Dated:
 24/11/2022
 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 25/11/2022 Tested on: 28/11/2022 in dry/wet condition





Sr. No.	Sr. No. Mark*			Date*	Size	Wet Weight	Dry Weight	Area of X-Section	1000	Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	OII (/6)	
1	Admin Block (3000 Psi)	25	10	2022	6Diax12		13.6	28.28	61	4832		Non Engraved
2	Admin Block (3000 Psi)	25	10	2022	6Diax12		13.4	28.28	71	5624		Non Engraved
3	Admin Block (3000 Psi)	25	10	2022	6Diax12		13.6	28.28	65	5149		Non Engraved
4	Production (4000 Psi)	26	10	2022	6Diax12		13.2	28.28	43	3406		Non Engraved
5	Production (4000 Psi)	26	10	2022	6Diax12	CTME	13.2	28.28	41	3248		Non Engraved
6	Production (4000 Psi)	26	10	2022	6Diax12	READIN	13.4	28.28	45	3564		Non Engraved
7	Car Park Shed (4000 Psi)	11	11	2022	6Diax12	DHE NAME OF THY LIDRO WHO	13.6	28.28	71	5624		Non Engraved
8	Car Park Shed (4000 Psi)	11	11	2022	6Diax12		13.6	28.28	73	5782		Non Engraved
9	Car Park Shed (4000 Psi)	11	11	2022	6Diax12		13.6	28.28	67	5307		Non Engraved
10	Admin Block (3000 Psi)	12	11	2022	6Diax12	-LA	13.4	28.28	43	3406		Non Engraved
11	Admin Block (3000 Psi)	12	11	2022	6Diax12		13.4	28.28	47	3723		Non Engraved
12	Admin Block (3000 Psi)	12	11	2022	6Diax12		13.4	28.28	47	3723		Non Engraved
13												
14												
15												
16										-		

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 4311 Dr. Umbreen

To: Mr. Muhammad Adnan, Project Manager

ICON Valley Phase-II

Project: Construction of ICON Signature 3rd Floor Lift or 4th Floor Columns

 Our Ref. No. CL/CED/
 472
 Dated:
 28/11/2022
 Test Specification

 Your Ref. No.
 IV-18
 Dated:
 20/11/2022
 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 25/11/2022 Tested on: 28/11/2022 in dry/wet condition





Sr. No.	Mark*			Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	4000 Psi	19	10	2022	6Diax12		13.6	28.28	83	6574		Non Engraved
2	4000 Psi	19	10	2022	6Diax12		13.8	28.28	86	6812		Non Engraved
3	4000 Psi	19	10	2022	6Diax12		13.8	28.28	83	6574		Non Engraved
4												
5					/	GINE	RINE					
6			-			READW	700	X				
7			-			DHE NAME OF THY LIDRO WHO	1919	=				
8			ł		os			IND.				
9			-									
10			-			-LA	IORE					
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 4288 Dr. Umbreen

To: Sub Divisional Officer

Buildings Sub Division No.20, Lahore

Project: Construction of Office Building of Chief Inspectorate of Mines Punjab, (ADP No. 6741 for year 2021-

2022)

 Our Ref. No. CL/CED/
 473
 Dated:
 28/11/2022
 Test Specification

 Your Ref. No.
 423/20th
 Dated:
 17/10/2022
 (----)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 21/11/2022 Tested on: 28/11/2022 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Machine Made Double Line				8.8 x 4.3 x 3	3785	3220	37.84	61	3611	17.55	
2	Machine Made Double Line				8.9 x 4.3 x 2.9	3700	3235	38.27	49	2868	14.37	
3	Machine Made Double Line				8.8 x 4.4 x 3	3800	3280	38.72	49	2835	15.85	
4												
5					-	CTME	RIATE					
6						READIN						
7						DHE NIGGE OF THY LIDRO WHO	- N	EF .				
8								IND				
9							-					
10						"-LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.