

Project: Construction of MS Tower at Plot 450, 451 Johar Town Lahore

Our Ref. No. CL/	CED/ 9965	Dated:	03/10/2022	Test Specification
Your Ref. No.	MST/UET/2022/C-055	Dated:	26/09/2022	(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	27	/09/2	2022	Tested on:	03/10)/2022	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Ka/ ams)	Area of X-Section (Sg. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	82 (3000 Psi)	27	8	2022	6Diax12		13	28.28	52	4119		Non Engraved
2	86 (3000 Psi)	27	8	2022	6Diax12		13.2	28.28	57	4515		Non Engraved
3	88 (3000 Psi)	27	8	2022	6Diax12		13.4	28.28	52	4119		Non Engraved
4												
5					-	ANE	RING					
6						C Incaria	No.					
7					i	THE NAME CORD VIVID		HEP.				
8					188	CREATES	100	HNZ				
9						·	6					
10					<	IA	INRE .					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



Project: Construction of MS Tower at Plot 450, 451 Johar Town Lahore

Our Ref. No. CL/	CED/ 9966	Dated:	03/10/2022	Test Specification
Your Ref. No.	MST/UET/2022/C-056	Dated:	26/09/2022	(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tile	es/Pavers
--	-----------

Specim	ens received on:	27	/09/2	2022	Tested on:	03/10	/2022	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date*	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	121 (3000 Psi)	20	9	2022	6Diax12		13.2	28.28	32	2535		Non Engraved
2	122 (3000 Psi)	20	9	2022	6Diax12		13.4	28.28	36	2851		Non Engraved
3	125 (3000 Psi)	20	9	2022	6Diax12		13.8	28.28	36	2851		Non Engraved
4												
5						ATHE	RING					
6						Caracian State						
7						THE NAME						
8					- 32	CAEATES	100					
9							-					
10					<	/A	INRES					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

vitnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Director/Dy. Director Concrete Laboratory



Project: Construction of MS Tower at Plot 450, 451 Johar Town Lahore

Our Ref. No. CL	(CED/ 9967	Dated:	03/10/2022	Test Specification
Your Ref. No.	MST/UET/2022/C-057	Dated:	26/09/2022	(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	27	/09/2	2022	Tested on:	03/10)/2022	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	97 (3000 Psi)	1	9	2022	6Diax12		13.4	28.28	37	2931		Non Engraved
2	98 (3000 Psi)	1	9	2022	6Diax12		13.2	28.28	48	3802		Non Engraved
3	99 (3000 Psi)	1	9	2022	6Diax12		13.8	28.28	28	2218		Non Engraved
4												
5						ANE	RING					
6					>	C Incaria	No.					
7						DHE NAME CORD VIVIO		HEP.				
8					IS.	CREATES	3	HNZ				
9						×						
10					<		INRE .					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL
A carbon copy for
the report has
been retained in
he lab for record.

t

3985 Dr. Aqsa

To: Mr. Muhammad Asif, Site Administrator Bismillah Developers, Main Ferozepur Road, Mustafabad (Laliani), Lahore.

Project: Marriage Hall Slab.			
Our Ref. No. CL/CED/ 9968	Dated:	03/10/2022	Test Specification
Your Ref. No. Nil	Dated:	03/10/2022	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	03	8/10/2	2022	Tested on:	03/10	0/2022	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas	Casting Date* Size		Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti on (%)	Remarks	
		סט		YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp. I ons)	(psi)	. ()	
1	3000 Psi	1	9	2022	6x6x6		8.6	36	58	3609		Engraved
2	3000 Psi	1	9	2022	6x6x6		8.4	36	57	3547		Engraved
3	3000 Psi	1	9	2022	6x6x6		8.4	36	55	3422		Engraved
4												
5						GINE	RINC					
6						Therease and						
7						THE NAME THY LORD WHO						
8					- Se	CREATES	000	-				
9						3	- 6	7				
10					- <	-14	INRE!					
11												
12												
13												
14												
15												
16												
Witness	sed by: Nil										•	

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL
A carbon copy for
the report has
been retained in
the lab for record.

3982 Dr. Aqsa

To: Engr. Abdul Karim, Resident Engineer Allied Engineering Consultants (Pvt.) Ltd.

Project: Establishment of Mother & Child Block in Sir Ganga Ram Hospital Lahore (Group No.1)

Our Ref. No. CL/C	ED/ 9969	Dated:	03/10/2022	Test Specification
Your Ref. No.	AEC/MBC/2022/222	Dated:	22/09/2022	()

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		03	/10/2	022	Tested on:	03/10	/2022	in dry/we	t condition			je slage
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti on (%)	Remarks
1	Rectangular, Grey,				7.8 x 3.9 x 3.1	(rtg/ giiis) 	(Rg/ gms) 3745	30.42	113	(psi) 8321		
2	Rectangular, Grey, 80mm				7.8 x 3.9 x 3.1		3775	30.42	99	7290		
3	Rectangular, Grey, 80mm				7.8 x 3.9 x 3.1		3770	30.42	113	8321		
4	Rectangular, Grey, 80mm				7.8 x 3.9 x 3.1		3695	30.42	98	7216		
5	Rectangular, Grey, 80mm				7.8 x 3.9 x 3.1	ANE	3720	30.42	116	8542		
6	Rectangular, Grey, 80mm				7.8 x 3.9 x 3.1	Contract of	3700	30.42	103	7584		
7						THE NAME THY LORD WHO						
8					188	CHEATES	100					
9						×		7				
10					- <	/A	INRE .					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 3941 Dr. Aqsa

Engr. Sohail Za	far, Senior Engineer			
University of Ec	lucation, Lahore, Engineering Cell. (M/S	S 7 Star Trading Company	y)	
Project: Constr	uction of New Room for Water Filtration	n Plant Near S&T Building	g at University of Edu	cation
Lahore (Townsl	hip Campus)			
Our Ref. No. CL	./CED/ 9970	Dated:	03/10/2022	Test Specification
Your Ref. No.	UE/Engg/SE/22/1353	Dated:	21/09/2022	(BS 3921**)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	26	5/09/2	2022	Tested on:	03/10	/2022	in dry/we	t condition		C	1620895
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Water Absorpti	Remarks
		DD	MM	ΥΥΥΥ	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Sword				8.7 x 4.3 x 2.9		3295	37.41	46	2754		
2	Sword				8.7 x 4.3 x 2.8		3270	37.41	46	2754		
3	Sword				8.8 x 4.3 x 3		3450	37.84	48	2841		
4	Sword				8.8 x 4.3 x 2.9		3335	37.84	48	2841		
5	Sword				8.9 x 4.3 x 3	AINE	3330	38.27	41	2400		
6					- >							
7						THE NAME CORD VITE	-	H				
8					US N	CREATES	3	+ Wa				
9						5	-					
10					<		I REL					
11							I					
12												
13												
14												
15												
16												
Witness	ad by:											

witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 3970 Dr. Aqsa

To: Mr. Aamir Shahzad Alvi, PM Usman Ibrahim Construction, CCA-124, Phase IV DHA, Lahore

Project: Construction of High-Q Mall and Offices at 3-A, Gulberg II, Lahore

Our Ref. No. CL	'CED/ 9971	Dated:	03/10/2022	Test Specification
Your Ref. No.	QC/HQ/CIVIL/23	Dated:	29/09/2022	(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:		29	/09/2	2022	Tested on:	03/10	0/2022	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*	Cas DD	ting MM	Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Ka/ ams)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	6000 Psi	26	8	2022	6Diax12		14.4	28.28	79	6257		Non Engraved
2	6000 Psi	26	8	2022	6Diax12		13.2	28.28	61	4832		Non Engraved
3	6000 Psi	26	8	2022	6Diax12		13.6	28.28	68	5386		Non Engraved
4	6000 Psi	31	8	2022	6Diax12		13.4	28.28	58	4594		Non Engraved
5	6000 Psi	31	8	2022	6Diax12	ARE	13.4	28.28	45	3564		Non Engraved
6	6000 Psi	31	8	2022	6Diax12		13.6	28.28	48	3802		Non Engraved
7	6000 Psi	1	9	2022	6Diax12	THE NAME THY LORD WHO	13.6	28.28	60	4752		Non Engraved
8	6000 Psi	1	9	2022	6Diax12	CREATES	13.6	28.28	58	4594		Non Engraved
9	6000 Psi	1	9	2022	6Diax12	1	13.2	28.28	55	4356		Non Engraved
10					<	-14	INRE!					
11												
12												
13												
14												
15												
16												
Witnessed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory