

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3906 Dr. Mazhar

To: Sub Divisional Officer

Your Ref. No.

**Buildings Sub Division No. 9, Lahore** 

170/9th

Project: Master Planning of Qurban Lines Lahore (Phase-1). Construction of BS (18-19) Apartments at

**Qurban Lines Lahore** 

Our Ref. No. CL/CED/ 9867

Dated: 21/9/2022

Test Specification
(BS 1881-116)

Dated: 11-08-22

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20/9/2022 Tested on: 21/9/2022 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Concrete cube ratio (1:1.5:3)	14	8	2022	6x6x6		8.6	36	114	7093		Non Engraved
2	Concrete cube ratio (1:1.5:3)	14	8	2022	6x6x6		8.6	36	96	5973		Non Engraved
3	Concrete cube ratio (1:1.5:3)	14	8	2022	6x6x6		8.6	36	94	5849		Non Engraved
4												
5						TETNE	RIATE					
6						NEAD IN	200	<b>K</b>				
7						DE NIGE OF THY LIGHD WHO	- E 2	-				
8					8 H			INO				
9						\	7					
10						-LA	INRE					
11												
12												
13												
14												
15												
16												
16												

#### Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3906 Dr. Mazhar

To: Sub Divisional Officer

**Buildings Sub Division No. 15, Lahore** 

Project: Construction of Court Rooms for Judicial Officers at Model Town Lahore Group No. 1

 Our Ref. No. CL/CED/
 9868
 Dated:
 21/9/2022
 Test Specification

 Your Ref. No.
 No. 2640
 Dated:
 14/9/2022
 (BS 1881-116)

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20/9/2022 Tested on: 21/9/2022 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	1:1-1/2:3 (Columns + Lift)	13	8	2022	6x6x6		8.4	36	86	5351		Non Engraved
2	1:1-1/2:3 (Columns + Lift)	13	8	2022	6x6x6		8.4	36	118	7342		Non Engraved
3	1:1-1/2:3 (Columns + Lift)	13	8	2022	6x6x6		8.6	36	83	5164		Non Engraved
4												
5						TETNE	RIAVE					
6						READIN	200					
7						DHE NAME OF THY LIDRO WHO	- T	EF -				
8							E SI	INO.				
9						-	-					
10					🤇	"-LA	IORE.					
11												
12												
13												
14												
15												
16												

#### Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

> 3897 Dr. Mazhar

To: Sub Divisional Officer

**Buildings Sub Division No. 20, Lahore** 

Project: Construction of Women Development Office Complex Sabzazar Lahore (ADP No. 2482 for the Year

2021-22)

 Our Ref. No. CL/CED/
 9869
 Dated:
 21/9/2022
 Test Specification

 Your Ref. No.
 359/20th
 Dated:
 19/8/2022
 (BS 1881-116)

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19/9/2022 Tested on: 21/9/2022 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	R.C.C Lift Well F/F (1: 1-1/2: 3)	27	7	2022	6x6x6		8.8	36	75	4667		Non Engraved
2	R.C.C Lift Well F/F (1: 1-1/2: 3)	27	7	2022	6x6x6		8.6	36	71	4418		Non Engraved
3												
4												
5						TETHE	RIATE					
6						READIN	200	<b>X</b>				
7						DHE NIGGE OF THY LIGHT WHO	- E / -	T.F				
8					SE			- AN				
9							-					
10					<	"-LA	IORE.					
11												
12												
13												
14												
15												
16												
Witness	and by:				•		•			·		

Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3900 Dr. Mazhar

To: Resident Engineer

**Engineering Services Consultants** 

Project: Re-Construction/widening of Road from Hafizabad to Sukheke Mandi L = 29.24 KM (Sec. K.M. 0.00

to 7.40 & 23.70 to 29.24 L = 13.14 KMS) in District Hafizabad

Our Ref. No. CL/CED/ 9870

21/9/2022

**Test Specification** 

Your Ref. No. RE/ESC/ADP/HFZ-104

Dated: 16/9/2022

Dated:

(BS 1881-116)

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19/9/2022 Tested on: 21/9/2022 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Rigid Pavement (1:1.5:3)	23	8	2022	6x6x6		9	36	102	6347		Non Engraved
2	Rigid Pavement (1:1.5:3)	23	8	2022	6x6x6		9	36	90	5600		Non Engraved
3	Rigid Pavement (1:1.5:3)	23	8	2022	6x6x6		9	36	81	5040		Non Engraved
4												
5					/	GINE	RING					
6						READW	200	<b>X</b>				
7						DHE NAME OF THY LORD WHO	₩. <u></u>	<b>#</b>				
8					es	ظيا		<b>8</b> -				
9						<b>7</b>		<b>7</b>				
10					<	LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

> 3907 Dr. Mazhar

**Test Specification** 

( ASTM C39 )

To: Engr. Hassan Mahmood

Resident Engineer, G3 Engineering Consultants (Pvt.) Ltd

Project: Construction of Newlife Residency Appartments at 273/1 Q Block Phase-II DHA, Lahore.

(Contractor: M/s Ghousia Engineering & Construction (Pvt.) Ltd. Lahore.)

Our Ref. No. CL/CED/ 9871 Dated:

Your Ref. No. G3/DHA-NLD/RE/99 Dated: 19/9/2022

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20/9/2022 Tested on: 21/9/2022 in dry/wet condition



21/9/2022

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	FF Column/Lift Wall (5000 Psi)	23	8	2022	6Diax12		13.6	28.28	53	4198		Non Engraved
2	FF Column/Lift Wall (5000 Psi)	23	8	2022	6Diax12		13	28.28	53	4198		Non Engraved
3	FF Column/Lift Wall (5000 Psi)	23	8	2022	6Diax12		14	28.28	49	3881		Non Engraved
4												
5					-	CEINE	RING					
6						READIN	200	<b>X</b>				
7						DHE NIME OF THY LIDRO WHO	- E	量				
8					- A							
9						<u></u>						
10						· LA	ORE.					
11					I		-					
12												
13												
14												
15												
16												
Witness	and hu	<u> </u>	<u> </u>									

Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3887 Dr. Aqsa

To: Mr. Muhammad Shahbaz

For and Behalf of Imperium Hospitality (Pvt) Ltd

Project: Nil

 Our Ref. No. CL/CED/
 9872
 Dated:
 21/9/2022
 Test Specification

 Your Ref. No.
 IHPL/Con/891
 Dated:
 31/8/2022
 (ASTM C39)

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15/9/2022 Tested on: 21/9/2022 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	4000 Psi	13	8	2022	6Diax12		14.2	28.28	75	5941		Non Engraved
2	4000 Psi	13	8	2022	6Diax12		14	28.28	70	5545		Non Engraved
3	4000 Psi	13	8	2022	6Diax12		14	28.28	67	5307		Non Engraved
4												
5					/	GINE	RING					
6						READIN	200					
7						DHE NAME OF THY LIDRO WHO	16. <u></u>					
8								- CAN				
9							1					
10						"-LA	ORE .					
11							-					
12												
13												
14												
15												
16												

Witnessed by: Engr. Rafi Ullah Bajwa & Engr. Ali Hasnain Khan (K.B)

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>
1. \* as engraved on the specimens (if any)

- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3887 Dr. Aqsa

To: Mr. Muhammad Shahbaz

For and Behalf of Imperium Hospitality (Pvt) Ltd

Project: Nil

 Our Ref. No. CL/CED/
 9873
 Dated:
 21/9/2022
 Test Specification

 Your Ref. No.
 IHPL/Con/890
 Dated:
 31/8/2022
 (ASTM C39)

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15/9/2022 Tested on: 21/9/2022 in dry/wet condition



Sr. No.	Mark*			Date*	Size	Wet Weight		Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	5000 Psi	12	8	2022	6Diax12		14.4	28.28	96	7604		Non Engraved
2	5000 Psi	12	8	2022	6Diax12		13.8	28.28	89	7050		Non Engraved
3	5000 Psi	12	8	2022	6Diax12		13.6	28.28	81	6416		Non Engraved
4												
5					/	GINE	RIATE					
6						READIN	200	<b>X</b>				
7						DHE NAME OF THY LIGHT WHO	JE	#				
8					es	رشيا		<b>8</b> -				
9								<b>7</b>				
10					<	"-LA	IORE					
11												
12												
13												
14												
15												
16												

Witnessed by: Engr. Rafi Ullah Bajwa & Engr. Ali Hasnain Khan (K.B)

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 3905 Dr. Mazhar

To: Engr. Zaheer ud Din Babar

Deputy General Manager Projects, for Habib Rafiq Engineering (Pvt.) Ltd

Project: Construction of Sky Gardens Tower, Lahore.

Our Ref. No. CL/CED/ 9874 Dated: 21/9/2022 <u>Test Specification</u>

Your Ref. No. HRLE/SKG/2022/064 Dated: 20/9/2022 (ASTM C39)

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20/9/2022 Tested on: 21/9/2022 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	RCC Raft 8th Pour (6000 Psi)	25	8	2022	6Diax12		14	28.28	100	7921		Non Engraved
2	RCC Raft 8th Pour (6000 Psi)	25	8	2022	6Diax12		13.8	28.28	100	7921		Non Engraved
3	RCC Raft 8th Pour (6000 Psi)	25	8	2022	6Diax12		14	28.28	98	7762		Non Engraved
4												
5					/	GINE	RINE					
6						NEAD W	200					
7						OF THY LIQKO WHO	-E	-				
8					SS							
9						<b>X</b>						
10						· LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

> 3874 Dr. Umbreen

**Test Specification** 

To: M/S Vertical Heights

Phase 6, DHA, Lahore.

Project: Vertical Heights Plot # 68B-2 Gulberg-III Lahore

Our Ref. No. CL/CED/ 9875-1 of 2

Your Ref. No. Nil Dated: 14/9/2022 (ASTM C39)

Dated:

21/9/2022

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14/9/2022 Tested on: 19-09-22 in dry/wet condition



		Cas	tina	Date*	Size	Wet	Dry	Area of	Ultimate	Ultimate	vvalei	
Sr. No.	Mark*					Weight	Weight	X-Section	load	Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Raft (4000 Psi)	3	7	2022	6Diax12		13.4	28.28	63	4990		Non Engraved
2	Raft (4000 Psi)	3	7	2022	6Diax12		13.6	28.28	77	6099		Non Engraved
3	Raft (4000 Psi)	3	7	2022	6Diax12		14	28.28	61	4832		Non Engraved
4	Raft (4000 Psi)	3	7	2022	6Diax12		13.2	28.28	81	6416		Non Engraved
5	Raft (4000 Psi)	3	7	2022	6Diax12	GINE	13.4	28.28	69	5465		Non Engraved
6	Raft (4000 Psi)	3	7	2022	6Diax12	READIN	13.4	28.28	83	6574		Non Engraved
7	Retaining Walls (4000 Psi)	1	8	2022	6Diax12	DHE NAME OF THY LIDRO WHO	- 14	28.28	67	5307		Non Engraved
8	Retaining Walls (4000 Psi)	1	8	2022	6Diax12		13.4	28.28	71	5624		Non Engraved
9	Retaining Walls (4000 Psi)	1	8	2022	6Diax12		13.4	28.28	81	6416		Non Engraved
10	Retaining Walls (4000 Psi)	1	8	2022	6Diax12	-LA	13.8	28.28	75	5941		Non Engraved
11	Retaining Walls (4000 Psi)	1	8	2022	6Diax12		13.8	28.28	63	4990		Non Engraved
12	Retaining Walls (4000 Psi)	1	8	2022	6Diax12		14	28.28	67	5307		Non Engraved
13	Columns (5000 Psi)	16	8	2022	6Diax12		14	28.28	67	5307		Non Engraved
14	Columns (5000 Psi)	16	8	2022	6Diax12		13.2	28.28	71	5624		Non Engraved
15	Columns (5000 Psi)	16	8	2022	6Diax12		13.4	28.28	94	7446		Non Engraved
16	Columns (5000 Psi)	16	8	2022	6Diax12		13.8	28.28	88	6970		Non Engraved

Witnessed by: Mr. Riaz ul Hassan, CNIC # 36402-9593943-9

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

3874 Dr. Umbreen

**Test Specification** 

To: M/S Vertical Heights

Phase 6, DHA, Lahore.

Project: Vertical Heights Plot # 68B-2 Gulberg-III Lahore

Our Ref. No. CL/CED/ 9875-2 of 2

Your Ref. No. Nil Dated: 14/9/2022 (ASTM C39)

Dated:

21/9/2022

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14/9/2022 Tested on: 19-09-22 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
17	Columns (5000 Psi)	16	8	2022	6Diax12		14	28.28	94	7446		Non Engraved
18	Columns (5000 Psi)	16	8	2022	6Diax12		13	28.28	86	6812		Non Engraved
19												
20												
21						THE	RIAVE					
22					>	TREADW		X				
23						DE NAME OF THY LORD WHO	- N	<b>=</b>				
24					es			<b>8</b> -				
25							-	<b>7</b>				
26						-UA	IORE.					
27												
28												
29												
30												
31												
32												

Witnessed by: Mr. Riaz ul Hassan, CNIC # 36402-9593943-9

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.