

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5120 Dr. Umbreen

Test Specification

(ASTM C39)

To: Engr. Shahid Iqbal

Our Ref. No. CL/CED/ 1811

Manager Construction, Trans-Continental Freight Pvt. Ltd

Project: Construction of TAQ House- Gulberg at Plot No. 6F, Main Market, Gulberg-II, Lahore

Your Ref. No. THG/032/UET Dated: 14/3/2023

Dated:

26/4/2023

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14/04/2023 Tested on: 26/4/2023 in dry/wet condition



Sr. No.	Mark*	Casting Date*			Size	Wet Weight		Area of X-Section		Ultimate Stress	Water Absorpti on (%)	Remarks
		DD MM YYYY			(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (70)	
1	Cylinder Sample No. 168 (3000 Psi)	29	1	2023	6Diax12		14	28.28	75	5941		Non Engraved
2	Cylinder Sample No. 169 (3000 Psi)	29	1	2023	6Diax12		13.6	28.28	69	5465		Non Engraved
3	Cylinder Sample No. 170 (3000 Psi)	29	1	2023	6Diax12		14.2	28.28	83	6574		Non Engraved
4												
5					/	RINE	RINA					
6						NEAD W	200	X				
7						DE NICE OF THY LORD WHO	- E 7 -	-				
8												
9						-						
10					🤇	· LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5120 Dr. Umbreen

Test Specification

(ASTM C39)

To: Engr. Shahid Iqbal

Our Ref. No. CL/CED/ 1812

Manager Construction, Trans-Continental Freight Pvt. Ltd

Project: Construction of TAQ House- Gulberg at Plot No. 6F, Main Market, Gulberg-II, Lahore

Your Ref. No. THG/033/UET Dated: 14/3/2023

Dated:

26/4/2023

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14/04/2023 Tested on: 26/4/2023 in dry/wet condition



Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti Remar	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Cylinder Sample No. 174 (5000 Psi)	29	1	2023	6Diax12		13	28.28	73	5782		Non Engraved
2	Cylinder Sample No. 175 (5000 Psi)	29	1	2023	6Diax12		12.8	28.28	77	6099		Non Engraved
3	Cylinder Sample No. 176 (5000 Psi)	29	1	2023	6Diax12		13.2	28.28	73	5782		Non Engraved
4												
5						GINE	RING					
6						READW	Sala D	X				
7						DE NAME OF THY LIDRO WHO	ر الله الله الله الله الله الله الله الله	=				
8						ظلا		<u> </u>				
9						,		7				
10					🤇	LA	IORE					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5120 Dr. Umbreen

Test Specification

(ASTM C39)

To: Engr. Shahid Iqbal

Our Ref. No. CL/CED/ 1813

Manager Construction, Trans-Continental Freight Pvt. Ltd

Project: Construction of TAQ House- Gulberg at Plot No. 6F, Main Market, Gulberg-II, Lahore

Your Ref. No. THG/034/UET Dated: 14/3/2023

Dated:

26/4/2023

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14/04/2023 Tested on: 26/4/2023 in dry/wet condition



Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti Re	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Cylinder Sample No. 180 (3000 Psi)	14	2	2023	6Diax12		13.8	28.28	81	6416		Non Engraved
2	Cylinder Sample No. 181 (3000 Psi)	14	2	2023	6Diax12		14	28.28	73	5782		Non Engraved
3	Cylinder Sample No. 182 (3000 Psi)	14	2	2023	6Diax12		13.8	28.28	69	5465		Non Engraved
4												
5					/	GINE	RINE					
6						READW	200	X				
7						DE NICLE OF THY LIQKO WHO	- E 7 -					
8					es							
9						> =						
10					<	· LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5120 Dr. Umbreen

Test Specification

(ASTM C39)

To: Engr. Shahid Iqbal

Our Ref. No. CL/CED/ 1814

Manager Construction, Trans-Continental Freight Pvt. Ltd

Project: Construction of TAQ House- Gulberg at Plot No. 6F, Main Market, Gulberg-II, Lahore

Your Ref. No. THG/035/UET Dated: 14/3/2023

Dated:

26/4/2023

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14/04/2023 Tested on: 26/4/2023 in dry/wet condition



Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Cylinder Sample No. 186 (3000 Psi)	16	2	2023	6Diax12		13.4	28.28	77	6099		Non Engraved
2	Cylinder Sample No. 187 (3000 Psi)	16	2	2023	6Diax12		13.6	28.28	81	6416		Non Engraved
3	Cylinder Sample No. 188 (3000 Psi)	16	2	2023	6Diax12		14	28.28	81	6416		Non Engraved
4												
5						CINE	RING					
6						READ IN	200					
7						DE THY LIDRO WHO	- S	=				
8					ea							
9												
10						· LA	HORE.					
11							-					
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.