

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

5806 Dr. M. Mazhar

**Test Specification** 

( ASTM C39 )

To: Mr. Farhan Ramzan

Site Supervisor, Premier Services.

Our Ref. No. CL/CED/ 2791

Project: MSC Boundary Wall Re-Construction at Zong MSC, Kot Lakhpat Lahore.

Your Ref. No. Nil Dated: 29-08-23

Dated:

30-08-23

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 29-08-23 Tested on: 30-08-23 in dry/wet condition



Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
	DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
(3000 Psi)	22	8	2023	6Diax12		13.2	28.28	34	2693		Non Engraved
(3000 Psi)	22	8	2023	6Diax12		13.6	28.28	40	3168		Non Engraved
(3000 Psi)	22	8	2023	6Diax12		13.4	28.28	36	2851		Non Engraved
	(3000 Psi) (3000 Psi) (3000 Psi)	(3000 Psi) 22 (3000 Psi) 22 (3000 Psi) 22	DD MM (3000 Psi)   22   8   (3000 Psi)   22   8   (3000 Psi)   22   8	DD MM YYYY   (3000 Psi)   22   8   2023   (3000 Psi)   22   8   2023   (3000 Psi)   22   8   2023	DD MM YYYY	DD MM YYYY	DD   MM YYYY   (in)   (Kg/ gms) (Kg/ gms)	DD   MM YYYY   (in)   (Kg/ gms)   (Kg/ gms)   (Sq. in)	DD   MM   YYYY   (in)   (Kg/ gms) (Kg/ gms) (Sq. in) (Imp.Tons)	DD MM YYYY	DD MM YYYY

Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

5798 Dr. M. Mazhar

To: Mr. Muhammad Saleem

Our Ref. No. CL/CED/ 2792

GM, Professional Construction Services (Pvt) Ltd

Project: Construction of Faculty Apartment-8 at LUMS Lahore (1st Floor Slab)

Your Ref. No. PCS/23/Eng-124 Dated: 28/8/2023 (ASTM C39)

Dated:

30/8/2023

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 28/8/2023 Tested on: 30/8/2023 in dry/wet condition



**Test Specification** 

Sr. No.	Mark*			Date*	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	P-2 (1:2:4)	25	7	2023	6Diax12		14.2	28.28	79	6257		Non Engraved
2	P-2 (1:2:4)	25	7	2023	6Diax12		13.8	28.28	74	5861		Non Engraved
3	P-2 (1:2:4)	25	7	2023	6Diax12		14	28.28	72	5703		Non Engraved
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												

#### Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

5788 Dr. M. Mazhar

To: Mr. Muhammad Siddique

Head QA/QC, AL-A'ZAMIYYA BLOCK PHASE I

Project: Nil

Your Ref. No.

Our Ref. No. CL/CED/ 2793

Alz./CT/UET/005

Dated: 30/8/2023

Test Specification
( ASTM C39 )

Dated: 25/8/2023

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 25/8/2023 Tested on: 30/8/2023 in dry/wet condition



Sr. No.	Mark*	Casting Da		Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)		(Imp.Tons)		on (%)	
1	4000 Psi	12	8	2023	6Diax12		13	28.28	38	3010		Non Engraved
2	4000 Psi	12	8	2023	6Diax12		13	28.28	32	2535		Non Engraved
3	4000 Psi	12	8	2023	6Diax12		13	28.28	40	3168		Non Engraved
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

5792 Dr. M. Mazhar

To: MEEZAN DEVELOPERS

Main Boulevard Jubilee Town, Lahore.

**Project: Construction of Jamia tur Rasheed Lahore Campus** 

i roject. Construction of Sanna tar Rasheed Lanore Sannpas

 Our Ref. No. CL/CED/
 2794
 Dated:
 30/8/2023
 Test Specification

 Your Ref. No.
 Nil
 Dated:
 28/8/2023
 (ASTM C39)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 28/8/2023 Tested on: 30/8/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	s-w	27	7	2023	6Diax12		13.2	28.28	64	5069		Engraved
2	s-w	27	7	2023	6Diax12		13.4	28.28	79	6257		Engraved
3												
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												

#### Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

5805 Dr. M. Mazhar

To: Mr. M. Faisal Bhatti,

Construction Manager, For Ittefaq Building Solutions (Pvt) Ltd

Project: Construction of Mr. Imran Qamar Residence Cantt, Lahore (Ground Floor Columns)

Our Ref. No. CL/CED/ 2795 Dated: 30/8/2023

Your Ref. No. Nil Dated: 28/8/2023

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 29/8/2023 Tested on: 30/8/2023 in dry/wet condition



**Test Specification** 

(BS 1881-116)

Sr. No.	Mark*			Date*	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	4500 Psi	19	8	2023	6x6x6		8.2	36	60	3733		Non Engraved
2	4500 Psi	19	8	2023	6x6x6		8.8	36	58	3609		Non Engraved
3	4500 Psi	19	8	2023	6x6x6		8.4	36	72	4480		Non Engraved
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												

#### Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

5804 Dr. M. Mazhar

To: Mr. Asif Javed

Resident Engineer, New Vision Engineering Consultant

Project: Strengthening Infrastructure and Academic Programs of Government College Women University

Sialkot. Construction of Faculty Natural Sciences Block (First Floor) Group-01

Our Ref. No. CL/CED/ 2796 Dated: 30/8/2023 <u>Test Specification</u>

Your Ref. No. NVEC/GCWUS/T-08 Dated: 06-07-23 (BS 1881-116)

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 29/8/2023 Tested on: 30/8/2023 in dry/wet condition



Sr. No.	Mark*	Cas		Date*	Size (in)	Wet Weight	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	Area# 01 Columns	8	6	2023	6x6x6		8.6	36	103	6409		Non Engraved
2	Area# 01 Columns	8	6	2023	6x6x6		8.2	36	83	5164		Non Engraved
3	Area# 01 Columns	8	6	2023	6x6x6		8.6	36	109	6782		Non Engraved
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												

#### Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

5804 Dr. M. Mazhar

To: Mr. Asif Javed

Resident Engineer, New Vision Engineering Consultant

Project: Strengthening Infrastructure and Academic Programs of Government College Women University

Sialkot. Construction of Faculty Natural Sciences Block (First Floor) Group-01

Our Ref. No. CL/CED/ 2797 Dated: 30/8/2023 <u>Test Specification</u>

Your Ref. No. NVEC/GCWUS/T-07a Dated: 27/6/2023 (BS 1881-116)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 29/8/2023 Tested on: 30/8/2023 in dry/wet condition



Sr. No.	Mark*	Cas		Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	Area# 02 Columns	30	5	2023	6x6x6		8.6	36	97	6036		Non Engraved
2	Area# 02 Columns	30	5	2023	6x6x6		8.4	36	95	5911		Non Engraved
3	Area# 02 Columns	30	5	2023	6x6x6		8.8	36	89	5538		Non Engraved
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

5804 Dr. M. Mazhar

To: Mr. Asif Javed

Resident Engineer, New Vision Engineering Consultant

Project: Strengthening Infrastructure and Academic Programs of Government College Women University

Sialkot. Construction of Faculty Natural Sciences Block (First Floor) Group-01

Our Ref. No. CL/CED/ 2798 Dated: 30/8/2023 <u>Test Specification</u>

Your Ref. No. NVEC/GCWUS/T-05 Dated: 26/6/2023 (BS 1881-116)

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 29/8/2023 Tested on: 30/8/2023 in dry/wet condition



Sr. No.	Mark*	Cas		Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	Area# 03 Columns	26	5	2023	6x6x6		8.6	36	97	6036		Non Engraved
2	Area# 03 Columns	26	5	2023	6x6x6		8.6	36	89	5538		Non Engraved
3	Area# 03 Columns	26	5	2023	6x6x6		9	36	103	6409		Non Engraved
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

5804 Dr. M. Mazhar

To: Mr. Asif Javed

Resident Engineer, New Vision Engineering Consultant

Project: Strengthening Infrastructure and Academic Programs of Government College Women University

Sialkot. Construction of Faculty Natural Sciences Block (First Floor) Group-01

Our Ref. No. CL/CED/ 2799 Dated: 30/8/2023 <u>Test Specification</u>

Your Ref. No. NVEC/GCWUS/T-07 Dated: 04-07-23 (BS 1881-116)

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 29/8/2023 Tested on: 30/8/2023 in dry/wet condition



Sr. No.	Mark*			Date*	Size	Wet Weight		Area of X-Section	load		Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (70)	
1	Area# 03 Slab	7	6	2023	6x6x6		8.6	36	89	5538		Non Engraved
2	Area# 03 Slab	7	6	2023	6x6x6		8	36	95	5911		Non Engraved
3	Area# 03 Slab	7	6	2023	6x6x6		8.6	36	87	5413		Non Engraved
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5801 Dr. Aqsa

> > ( ---- )

To: Mr. Muhammad Asif

**Project Manager, Imperium Developers** 

Project: Sixty6, Gulberg-III Lahore

Our Ref. No. CL/CED/ 2800 Dated: 30/8/2023 <u>Test Specification</u>

Your Ref. No. IMP/66/16/02 Dated: 28/8/2023

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 28/8/2023 Tested on: 30/8/2023 in dry/wet condition



Sr. No.	Mark*			Date*	Size	Wet Weight		Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Concrete Block				11.9 x 4 x 8		13.4	47.6	54	2541		
2												
3												
4												
5					/	GINE	RIATE					
6						READIN	200					
7						DHE NIGGE OF THY LIDRO WHO	1999	<b>E</b> -				
8					S							
9												
10						"-LA	HORE.					
11												
12												
13												
14												
15												
16												

Witnessed by: Mr. Husnain Imran, CNIC 35202-6634387-3

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5801 Dr. Aqsa

> > ( ---- )

To: Mr. Muhammad Asif

**Project Manager, Imperium Developers** 

Project: Sixty6, Gulberg-III Lahore

Our Ref. No. CL/CED/ 2801 Dated: 30/8/2023 <u>Test Specification</u>

Your Ref. No. IMP/66/16/03 Dated: 28/8/2023

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 28/8/2023 Tested on: 30/8/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Concrete Block				11.9 x 6 x 8		22	71.4	94	2949		
2												
3												
4												
5					/	GINE	RING					
6						READIN	200					
7						DE NICE OF THY LORD WHO	- E / T					
8					SS			- CAN				
9							- 6					
10					<	LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by: Mr. Husnain Imran, CNIC 35202-6634387-3

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.