

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** A carbon copy for the report has been retained in the lab for record.

> 6375 Dr. Mazhar

To: **Meezan Developers** 

Plaza # 97 Block B, 2nd Floor, Main Boulevard Jubilee Town, Lahore.

Project: Construction of Jamia tur Rasheed Lahore Campus.

Our Ref. No. CL/CED/ 3764 Dated: 20/12/2023 **Test Specification** 

Your Ref. No. Dated: 13/12/2023 ( ASTM C39 )

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13/12/2023 Tested on: 20/12/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	C-5 + C-5	9	11	2023	6Diax12		13	28.28	60	4752		Engraved
2	C-5 + C-5	9	11	2023	6Diax12		13.8	28.28	72	5703		Engraved
3												
4												
5												
6												
7												
8												
9												
10												
11												
12				-								
13				-								
14												
15												
16												
Witness	sed by:										•	

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL
A carbon copy for the report has been retained in

the lab for record.

6375
Dr. Mazhar

To: Meezan Developers

Plaza # 97 Block B, 2nd Floor, Main Boulevard Jubilee Town, Lahore

Project: Construction of Jamia tur Rasheed Lahore Campus

Our Ref. No. CL/CED/ 3765 Dated: 20/12/2023 <u>Test Specification</u>

Your Ref. No. Nil Dated: 13/12/2023 (ASTM C39)

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13/12/2023 Tested on: 20/12/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	C-5 + C-5	7	11	2023	6Diax12		13.6	28.28	81	6416		Engraved
2	C-5 + C-5	7	11	2023	6Diax12		13.8	28.28	80	6337		Engraved
3												
4												
5												
6							-			I	I	
7					-		1			I	I	
8												
9												
10												
11							-			I	I	
12										I	I	
13												
14												
15												
16												

#### Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** A carbon copy for the report has

been retained in the lab for record.

> 6358 Dr. Mazhar

To: Mr. Talha Javaid

**Project Manager, CONSTRUCT ®** 

Project: Construction of 18 Green Apartment Complex, DHA Phase V1, Lahore (Basement Slab in Front of

Our Ref. No. CL/CED/ 3766 Dated: 20/12/2023 **Test Specification** 

Your Ref. No. Dated: 08-12-23 ( ASTM C39 )

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

8/12/2023 Tested on: Specimens received on: 20/12/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	3000 Psi	9	11	2023	6Diax12		13	28.28	58	4594		Non Engraved
2	3000 Psi	9	11	2023	6Diax12		13.2	28.28	60	4752		Engraved
3	3000 Psi	9	11	2023	6Diax12		13.2	28.28	56	4436		Engraved
4	3000 Psi	9	11	2023	6Diax12		13	28.28	52	4119		Engraved
5	3000 Psi	9	11	2023	6Diax12		13	28.28	54	4277		Engraved
6	3000 Psi	9	11	2023	6Diax12		13	28.28	54	4277		Engraved
7												
8												
9												
10												
11												
12				-								
13												
14												
15												
16												
Witness	sed by:				-							

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** A carbon copy for the report has

been retained in the lab for record.

> 6392 Dr. Mazhar

To: Engr. Hassan Mahmood

Resident Engineer, G3 Engineering Consultants (Pvt) Ltd

Project: Construction of DHA NEWLIFE RESIDENCY APARTMENTS at 273/1 Q Block Phase-II DHA, Lahore

(Pouring of Block-B Footing # FB-7 & F4 from Grid P/12-14 and P/11)

Our Ref. No. CL/CED/ 3767 Dated: 20/12/2023 **Test Specification** 

Your Ref. No. G3/DHA-NLD/RE/207 Dated: 12-12-23 ( ASTM C39 )

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

15/12/2023 Tested on: Specimens received on: 20/12/2023 in dry/wet condition



Sr. No.	Mark*			Date*	Size	Wet Weight		Area of X-Section		Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	OII ( 70)	
1	Footing	15	11	2023	6Diax12		13.4	28.28	79	6257		Non Engraved
2	Footing	15	11	2023	6Diax12		13.4	28.28	81	6416		Non Engraved
3	Footing	15	11	2023	6Diax12		13.4	28.28	68	5386		Non Engraved
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												
Witness	end by:											

#### Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL
A carbon copy for the report has been retained in

the lab for record.

6408 Dr. Mazhar

**Test Specification** 

To: CW Manager

ARCON, Office # 703, 7th Floor, Khudadad Heights, E-11, Islamabad

Project: RAFT, COLUMN, DG & SOLAR

Our Ref. No. CL/CED/ 3768 Dated: 20/12/2023

Your Ref. No. Nil Dated: Nil (BS 1881-116)

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19/12/2023 Tested on: 20/12/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Site ID ISQ014 (1:1.5:3 & 1:4:8)	17	11	2023	6x6x6		8	36	83	5164		Non Engraved
2	Site ID ISQ014 (1:1.5:3 & 1:4:8)	17	11	2023	6x6x6		8	36	95	5911		Non Engraved
3												
4												
5												
6												
7										-		
8												
9							-			I		
10												
11							-			I		
12							-			I		
13										I		
14										I		
15										-		
16										-		
Witness	ed by:			•	-					•		

#### Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL
A carbon copy for the report has been retained in

the lab for record.

6408 Dr. Mazhar

To: CW Manager

ARCON, Office # 703, 7th Floor, Khudadad Heights, E-11, Islamabad

Project: RAFT, COLUMN, DG & SOLAR

Our Ref. No. CL/CED/ 3769 Dated: 20/12/2023 <u>Test Specification</u>

Your Ref. No. Nil Dated: Nil (BS 1881-116)

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19/12/2023 Tested on: 20/12/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Site ID N-3186 (1:1.5:3 & 1:4:8)	12	11	2023	6x6x6		8	36	111	6907		Non Engraved
2	Site ID N-3186 (1:1.5:3 & 1:4:8)	12	11	2023	6x6x6		8	36	107	6658		Non Engraved
3					-							
4												
5												
6												
7										-		
8												
9							-			I		
10												
11							-			I		
12												
13												
14										I		
15												
16							-			I		
Witness	ed by:			•	-					•		

#### Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** A carbon copy for the report has been retained in

the lab for record.

6408 Dr. Mazhar

To: **CW Manager** 

ARCON, Office # 703, 7th Floor, Khudadad Heights, E-11, Islamabad

Project: RAFT, COLUMN, DG & SOLAR

Our Ref. No. CL/CED/ 3770 Dated: 20/12/2023 **Test Specification** 

Your Ref. No. Dated: Nil (BS 1881-116)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

19/12/2023 Tested on: Specimens received on: 20/12/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Site ID 85 (1:1.5:3 & 1:4:8)	13	11	2023	6x6x6		8	36	85	5289		Non Engraved
2	Site ID 85 (1:1.5:3 & 1:4:8)	13	11	2023	6x6x6		8.2	36	87	5413		Non Engraved
3					-		I					
4							-					
5												
6							-					
7					-		I					
8							-					
9							-					
10												
11							-					
12												
13												
14												
15												
16												
Witness	sed by:				-							

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** A carbon copy for the report has been retained in the lab for record.

> 6408 Dr. Mazhar

To: **CW Manager** 

ARCON, Office # 703, 7th Floor, Khudadad Heights, E-11, Islamabad

Project: RAFT, COLUMN, DG & SOLAR

Our Ref. No. CL/CED/ 3771 Dated: 20/12/2023 **Test Specification** 

Your Ref. No. Dated: Nil (BS 1881-116)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

19/12/2023 Tested on: Specimens received on: 20/12/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	N-3132 (1:1.5:3 & 1:4:8)	3	11	2023	6x6x6		7.8	36	116	7218		Non Engraved
2	N-3132 (1:1.5:3 & 1:4:8)	3	11	2023	6x6x6		8.2	36	105	6533		Non Engraved
3				I								
4				1			-					
5				1			-					
6				1			-					
7				1	-		I					
8				1			-					
9				-								
10												
11							-					
12				-								
13				1								
14				ŀ								
15				1								
16				1								
Witness	sed by:				•							

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL** A carbon copy for the report has been retained in

the lab for record.

6408 Dr. Mazhar

**Test Specification** 

To: **CW Manager** 

ARCON, Office # 703, 7th Floor, Khudadad Heights, E-11, Islamabad

Project: RAFT, COLUMN, DG & SOLAR

Our Ref. No. CL/CED/ 3772 Dated: 20/12/2023

Your Ref. No. Dated: Nil (BS 1881-116)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

19/12/2023 Tested on: Specimens received on: 20/12/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	N-3315 (1:1.5:3 & 1:4:8) N-3315 (1:1.5:3 &	6	11	2023	6x6x6		8	36	111	6907		Non Engraved
2	N-3315 (1:1.5:3 & 1:4:8)	6	11	2023	6x6x6		8.4	36	111	6907		Non Engraved
3												
4							-			I		
5							-			I		
6										-		
7												
8							-			I		
9							-			I		
10							-			I		
11					-		-			I		
12												
13												
14												
15												
16												
Witness	sed by:				-							

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL
A carbon copy for the report has been retained in

the lab for record.

6408 Dr. Mazhar

To: CW Manager

ARCON, Office # 703, 7th Floor, Khudadad Heights, E-11, Islamabad

Project: RAFT, COLUMN, DG & SOLAR

Our Ref. No. CL/CED/ 3773 Dated: 20/12/2023

Your Ref. No. Nil Dated: Nil (BS 1881-116)

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19/12/2023 Tested on: 20/12/2023 in dry/wet condition



**Test Specification** 

Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	N-3154 (1:1.5:3 & 1:4:8) N-3154 (1:1.5:3 &	5	11	2023	6x6x6		7.8	36	101	6284		Non Engraved
2	N-3154 (1:1.5:3 & 1:4:8)	5	11	2023	6x6x6		7.8	36	85	5289		Non Engraved
3												
4												
5												
6					-		-				-	
7										-		
8				-								
9												
10												
11							-					
12												
13												
14												
15											-	
16												
Witness	end hv:											

#### Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL
A carbon copy for the report has been retained in

the lab for record.

6408 Dr. Mazhar

To: CW Manager

ARCON, Office # 703, 7th Floor, Khudadad Heights, E-11, Islamabad

Project: RAFT, COLUMN, DG & SOLAR

Our Ref. No. CL/CED/ 3774 Dated: 20/12/2023 <u>Test Specification</u>

Your Ref. No. Nil Dated: Nil (BS 1881-116)

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 19/12/2023 Tested on: 20/12/2023 in dry/wet condition



Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
	DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
N-3174 (1:1.5:3 & 1:4:8)	31	10	2023	6x6x6		8.2	36	127	7902	-	Non Engraved
N-3174 (1:1.5:3 & 1:4:8)	31	10	2023	6x6x6		7.6	36	91	5662		Non Engraved
										-	
										-	
	N-3174 (1:1.5:3 & 1:4:8) N-3174 (1:1.5:3 & 1:4:8)	Mark* DD  N-3174 (1:1.5:3 & 31 1:4:8) N-3174 (1:1.5:3 & 31	Mark*  DD MM  N-3174 (1:1.5:3 & 31 10  1:4:8)  N-3174 (1:1.5:3 & 31 10	N-3174 (1:1.5:3 & 11	Mark* DD MM YYYY (in)  N-3174 (1:1.5:3 & 31 10 2023 6x6x6  1:4:8) N-3174 (1:1.5:3 & 31 10 2023 6x6x6	Mark*         Casting Date*         Size         Weight           N-3174 (1:1.5:3 & 1:4:8)         31 10 2023 6x6x6            N-3174 (1:1.5:3 & 1:4:8)         31 10 2023 6x6x6	N-3174 (1:1.5:3 & 1:4:8)	Mark*    DD   MM   YYYY   (in)   (Kg/ gms)   (Kg/ gms)   (Sq. in)	Mark*         Casting Date*         Size         Weight (Kg/gms)         X-Section (Ioad (Imp.Tons))           N-3174 (1:1.5:3 & 1:4:8)         31 10 2023 6x6x6          8.2 36 127           N-3174 (1:1.5:3 & 1:4:8)         31 10 2023 6x6x6          7.6 36 91	Mark*         Casting Date*         Size         Weight (Kg/gms)         X-Section (Sq. in) (Imp.Tons)         Stress (psi)           N-3174 (1:1.5:3 & 1:4:8)         31 10 2023 6x6x6         8.2 36 127 7902           N-3174 (1:1.5:3 & 31 10 2023 6x6x6         7.6 36 91 5662	Mark*         Casting Date*         Size         Weight (Kg/gms)         Weight (Kg/gms)         X-Section (Inad (Imp.Tons))         Stress Absorption (%)           N-3174 (1:1.5:3 & 1:4:8)         31 10 2023 6x6x6          8.2 36 127 7902            N-3174 (1:1.5:3 & 1:4:8)         31 10 2023 6x6x6          7.6 36 91 5662

#### Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL
A carbon copy for the report has been retained in

the lab for record.

6387 Dr. Mazhar

To: Professional Construction Services Pvt Ltd Lahore

Johar Town, Lahore.

Project: Construction of TCF Secondary School Chanwali Basti Qasba Gujrat

Our Ref. No. CL/CED/ 3775 Dated: 20/12/2023 <u>Test Specification</u>

Your Ref. No. PCS/23/Eng/242 Dated: 14/12/2023 (ASTM C39)

### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 14/12/2023 Tested on: 20/12/2023 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Ground Floor Slab	30	10	2023	6Diax12		12	28.28	52	4119		Non Engraved
2	Ground Floor Slab	30	10	2023	6Diax12		12.8	28.28	50	3960	1	Non Engraved
3										-		-
4												
5												
6												
7										-		-
8												
9												
10												
11												
12												
13												
14												
15												
16												

#### Witnessed by:

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.