



To: **JR Private Limited** 

**Cavalry Ground Ext. Lahore Cantt.** 

Project: Construction of Warehouse & Cold Store at Faisalabad Fiedmc.

Our Ref. No. CL/CED/ 2322	Dated:	12-07-23	Test Specification
Your Ref. No. Nil	Dated:	10-07-23	(ASTM C39)

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	1	0-07	-23	Tested on:	12-0	07-23	in dry/we	t condition		Ö	jesneg
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Footings (3750 Psi)	13	6	2023	6Diax12		13.8	28.28	73	5782		Non Engraved
2	Footings (3750 Psi)	13	6	2023	6Diax12		14	28.28	67	5307		Non Engraved
3	Footings (3750 Psi)	14	6	2023	6Diax12		13.8	28.28	61	4832		Non Engraved
4	Footings (3750 Psi)	14	6	2023	6Diax12		13.8	28.28	75	5941		Non Engraved
5	Footings (3750 Psi)	15	6	2023	6Diax12		14	28.28	71	5624		Non Engraved
6	Footings (3750 Psi)	15	6	2023	6Diax12		13.8	28.28	69	5465		Non Engraved
7	Wall (3750 Psi)	19	6	2023	6Diax12		13.8	28.28	75	5941		Non Engraved
8	Wall (3750 Psi)	19	6	2023	6Diax12		13.6	28.28	75	5941		Non Engraved
9	Wall (3750 Psi)	21	6	2023	6Diax12		13.6	28.28	83	6574		Non Engraved
10	Wall (3750 Psi)	21	6	2023	6Diax12		13.6	28.28	77	6099		Non Engraved
11	Wall (3750 Psi)	21	6	2023	6Diax12		13.8	28.28	90	7129		Non Engraved
12												
13												
14												
15												
16												
Nitness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

ORIGINAL A carbon copy for the report has been retained in the lab for record.

5508 & 5517 Dr. M. Mazhar





Plain and Reinforced Concrete Laboratory **Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895



To: Mr. Muhammad Abdul Rehman

Izmir Housing Society, Canal Bank Road, House No.93, Block-J, Lahore.

Project: Research Titled "Development of 3DCP and Mix Design"

Our Ref. No. CL/C	CED/ 2323	Dated:	12-07-23
Your Ref. No.	Nil	Dated:	11-07-23

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	1	1-07	-23	Tested on:	12-0	)7-23	in dry/we	t condition		Ö	je stan si
Sr. No.	Mark*		-	Date*	Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (70)	
1		2	7	2023	6x6x6		8	36	63	3920		Non Engraved
2		2	7	2023	6x6x6		8	36	69	4293		Non Engraved
3		2	7	2023	6x6x6		8	36	57	3547		Non Engraved
4												
5												
6												
7												
8												
9												
10												
11												
12												
13												
14												
15												
16												
Witness	sed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



5519 Dr. M. Mazhar

	-azara
응	
	<b>*</b>
$\mathbf{h}_{i}$	
пð	31 <u>80</u> 7
⊡¢.	3129)

Test Specification (BS 1881-116)



Dr. Aqsa

### To: Engr. Haseeb Afzal

Project Manager, HMB Developers Pvt Ltd

Project: Construction of Commercial Tower, Finance Trade Centre Lahore

Our Ref. No. CL	/CED/ 2324	Dated:	12-07-23	Test Specification
Your Ref. No.	HMBDPL/S.O/05/23/51th (Lhr)	Dated:	12-07-23	(ASTM C39)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	12	2/07/2	2023	Tested on:	12-0	)7-23	in dry/we	t condition		Ë	jesteg
Sr. No.	Mark*		•	Date* YYYY	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	C-09 (6000 Psi)	10	6	2023	6Diax12		14.2	28.28	76	6020		Non Engraved
2	C-09 (6000 Psi)	10	6	2023	6Diax12		13.8	28.28	75	5941		Non Engraved
3	C-09 (6000 Psi)	10	6	2023	6Diax12		14	28.28	82	6495		Non Engraved
4												
5						HINE	RINE					
6						I READ W						
7						DHE NAME OFTHY CORD WHO		F				
8					188			IND				
9							- 6					
10					<	-LA	INNE .					
11												
12												
13												
14												
15												
16												
Witness	ed by: CNIC 3520	1-893	3168	5-1								

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



# Plain and Reinforced Concrete Laboratory

**Civil Engineering Department** 

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

5511 Dr. M. Mazhar

- To: Engr. Muhammad Umar
  - **E&dc Associates**

Project: Construction of House Officers Hostel at CKMC, Kharian Cantt.

Our Ref. No. CL	/CED/ 2325	Dated:	12-07-23	Test Specification
Your Ref. No.	E&dc-080/12	Dated:	10-07-23	(ASTM C39)

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	11	/07/2	2023	Tested on:	12-0	)7-23	in dry/we	t condition		Ö	jestes
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	FF Col. Add. Girls Hostel (3000 Psi)	18	5	2023	6Diax12		13.4	28.28	69	5465		Non Engraved
2	FF Col. Add. Girls Hostel (3000 Psi)	18	5	2023	6Diax12		13	28.28	57	4515		Non Engraved
3	FF Col. Add. Girls Hostel (3000 Psi)	18	5	2023	6Diax12		13.2	28.28	47	3723		Engraved
4	FF slab Add. Girls Hostel (3000 Psi)	25	6	2023	6Diax12		13.4	28.28	39	3089		Engraved
5	FF slab Add. Girls Hostel (3000 Psi)	25	6	2023	6Diax12	RINE	RIA4	28.28	43	3406		Engraved
6	FF slab Add. Girls Hostel (3000 Psi)	25	6	2023	6Diax12	I READ IN	14	28.28	57	4515		Engraved
7						DHE NAKSE OF THY LORID WHO	143	EB				
8					/ ASI			H				
9							1	<b>X</b>				
10					<	-14	ORE					
11												
12												
13												
14												
15												
16												
Witness	sed by:								·			

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

ORIGINAL A carbon copy for the report has been retained in the lab for record.



To: Mr. Muhammad Irfan Material Engineer, Banu Mukhtar Contracting Pvt. Ltd.

Project: Burj-1 by Ajwa Builders (Main Building Ground Floor)

Our Ref. No. CL/	CED/ 2326	Dated:	12-07-23	Test Specification
Your Ref. No.	DOC-BMC/AJWA/083	Dated:	03-07-23	(ASTM C39)

### COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	7/	/07/2	023	Tested on:	12-0	)7-23	in dry/we	t condition		r. D	
Sr. No.	Mark*	Cas	•	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate Ioad (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	Col. #04 Grids# E/8,9 & H/8,9	3	6	2023	6Diax12		14	28.28	94	7446		Non Engraved
2	Col. #04 Grids# E/8,9 & H/8,9	3	6	2023	6Diax12		14.2	28.28	86	6812		Non Engraved
3	Col. #04 Grids# E/8,9 & H/8,9	3	6	2023	6Diax12		13.8	28.28	112	8871		Non Engraved
4												
5					/	RINE	RINE					
6					>	I READ IN						
7						DHE NHOLE OF THY LORD WHO		EB				
8												
9							1					
10					<	-LA	INNE .					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory



Material Engineer, Banu Mukhtar Contracting Pvt. Ltd.

Project: Burj-1 by Ajwa Builders (Main Building Ground Floor)

Our Ref. No. CL/	CED/ 2327	Dated:	12-07-23	Test Specification
Your Ref. No.	DOC-BMC/AJWA/084	Dated:	05-07-23	(ASTM C39)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:			7/07/2023 Tested on:			12-07-23 in dr		in dry/we	n dry/wet condition				
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate Ioad	Ultimate Stress	Absorpti	Remarks	
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)		
1	Col. #02 Grids# F/8, G/8	5	6	2023	6Diax12		13.8	28.28	90	7129		Non Engraved	
2	Col. #02 Grids# F/8, G/8	5	6	2023	6Diax12		14	28.28	83	6574		Non Engraved	
3	Col. #02 Grids# F/8, G/8	5	6	2023	6Diax12		13.8	28.28	71	5624		Non Engraved	
4													
5					/	GINE	RIATE						
6					- )	READIN	PHILE D						
7							4						
8													
9						-	- 5	<b></b>					
10					- <	-LA	INRE .						
11													
12													
13													
14													
15													
16													
Witness	sed by:												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

 $\underline{\textbf{Note:}}$  Above results pertain to the unsealed samples supplied to the laboratory



To: **Meezan Developers** 

Main Boulevard Jubilee Town, Lahore.

Project: Construction of Jami tur Rasheed Lahore Campus

Our Ref. No. CL/0	CED/ 2328	Dated:	12-07-23	Test Specification
Your Ref. No.	Nil	Dated:	10-07-23	(ASTM C39)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	10	/07/2	2023	Tested on:	12-0	)7-23	in dry/wet condition			Ċ	jester
Sr. No.	Mark*		-	Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	C-5	14	5	2023	6Diax12		13.4	28.28	57	4515		Engraved
2	C-5	14	5	2023	6Diax12		12.4	28.28	47	3723		Engraved
3												
4												
5						ARTNE	RINE					
6					- )	READIN	CAUSED					
7						CORD WHE	-E					
8												
9						10-						
10					<	-LA	IORE ?					
11												
12												
13												
14												
15												
16												
Witnessed by:												

### vitnessea by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory





To: Meezan Developers	
-----------------------	--

Main Boulevard Jubilee Town, Lahore.

Project: Construction of Jami tur Rasheed Lahore Campus

Our Ref. No. CL/C	ED/ 2329	Dated:	12-07-23	Test Specification
Your Ref. No.	Nil	Dated:	10-07-23	(ASTM C39)

### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	10	/07/2	2023	Tested on:	12-0	)7-23	in dry/wet condition			Ċ	jester j
Sr. No.	Mark*	Cas DD	-	Date*	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	C-1	13	5	2023	6Diax12		13.4	28.28	53	4198		Engraved
2	C-1	13	5	2023	6Diax12		13.4	28.28	45	3564		Engraved
3												
4							-					
5						AHIE	RIATE					
6					>	READIN	No.					
7						DHE NAME OF THY LORD WHO	-4	F				
8					88							
9						2	-					
10					- <	-LA	IONE .					
11												
12												
13												
14												
15												
16												
Witness	ed by:											

### vitnessea by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory





Resident Engineer		
Project: Detailed Design and Resident Supervision of located at Sargodha	f Regional Campuses for Allama Iq	bal Open University
Our Ref. No. CL/CED/ 2330	Dated: 12-0	07-23 <u>Test Specification</u>
Your Ref. No. VISP/RC/SRG-10	Dated: 06-0	)7-23 (BS 1881-116)

## COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	11	/07/2	2023	Tested on:	12-0	)7-23	in dry/wet condition		Ë	jezan g	
Sr. No.	Mark*		•	Date*	Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (70)	
1	(3750 Psi)	8	6	2023	6x6x6		8.6	36	90	5600		Engraved
2	(3750 Psi)	8	6	2023	6x6x6		8.6	36	70	4356		Engraved
3	(3750 Psi)	10	6	2023	6x6x6		8.4	36	65	4044		Engraved
4	(3750 Psi)	10	6	2023	6x6x6		8.6	36	65	4044		Engraved
5						RINE	RIATE					
6					>	E READ IN						
7						DHE NAKSE OF THY LORIO WHO	14.4	EB				
8					/ ASI			I Ma				
9						-	-					
10					<	(A	INK- ·					
11												
12												
13												
14												
15												
16												
Witness	sed by:											

### illiesseu by

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. \* as engraved on the specimens (if any)

2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory