

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5002 Dr. Aqsa

Test Specification

(ASTM C39)

To: Engr. Syed M Sajjad Hashmi (Head QA/QC)

Vision Developers (Pvt.) Ltd.

Project: Masjid Al Rafay Basement Flooring at Park View City, Lahore.

Our Ref. No. CL/CED/ 1567 Dated:

Your Ref. No. 11 Dated: 07-03-23

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 27/03/2023 Tested on: 28-03-23 in dry/wet condition



28-03-23

Sr. No.	Mark*	Mark*		Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Basement Flooring	11	2	2023	6Diax12		13	28.28	30	2376		Non Engraved
2	Basement Flooring	11	2	2023	6Diax12		13	28.28	30	2376		Non Engraved
3												
4												
5					/	GINE	RINE					
6						READIN	200					
7						DHE NAME OF THY LIDRO WHO	- E	-				
8					SS							
9							- 6					
10					<	"-LA	HORE.					
11												
12												
13												
14												
15												
16												

Witnessed by: Mr. M. Waqas, Lab Tech Vision Developers

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5019 Dr. Aqsa

To: The Resident Engineer

Acrow Consulting Pvt. Ltd. Lahore.

Project: Construction of Building B-45 MM Alam Road Gulberg-III. (UGWT Walls)

 Our Ref. No. CL/CED/
 1568
 Dated:
 28-03-23
 Test Specification

 Your Ref. No.
 AC/B-45/06
 Dated:
 26-03-23
 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 28-03-23 Tested on: 28-03-23 in dry/wet condition





Sr. No.	Mark*			Date*	Size	Wet Weight		Area of X-Section	load		Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	011 (70)	
1	TM-6, Tank (6000 Psi)	27	2	2023	6Diax12		14	28.28	60	4752		Non Engraved
2	TM-5, Tank (6000 Psi)	27	2	2023	6Diax12		14.2	28.28	67	5307		Non Engraved
3	TM-1, Tank (6000 Psi)	27	2	2023	6Diax12		14	28.28	76	6020		Non Engraved
4												
5						CINE	RINA					
6						READ IN	200					
7						DHE NAME OF THY LIDRO WHO	1999	E -				
8					SS							
9							70					
10						"-LA	HORE					
11												
12												
13												
14												
15												
16												

Witnessed by: Mr. Uzair, CNIC # 16102-6784638-9

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5007 Dr. Umbreen

To: Cantonment Executive Officer

Sargodha Cantt. Office of the Cantonment Board, Sargodha

Project: Providing / Laying of Sewerage Lines at Ward No. 01 Sargodha Cantt (Phase-I)

Our Ref. No. CL/CED/ 1569 Dated: 28-03-23

Your Ref. No. CBS/Cantt/01/88 Dated: 02-03-23

Test Specification

(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 27-03-23 Tested on: 28-03-23 in dry/wet condition





Sr. No.	Mark*			Date*	Size	Wet Weight		Area of X-Section	load	Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)		(Imp.Tons)	(psi)	J. (70)	
1	E. Cost (M), 14.26	1	2	2023	6Diax12		13.6	28.28	69	5465		Non Engraved
2	E. Cost (M), 14.26	1	2	2023	6Diax12		13.2	28.28	112	8871		Non Engraved
3												
4												
5					/	GINE	RIATE					
6						READIN	200					
7						DHE NAME OF THY LORD WHO	₩					
8						رشيا		8 –				
9),	-	7				
10					🤇	LA	HORE					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5007 Dr. Umbreen

To: Cantonment Executive Officer

Sargodha Cantt. Office of the Cantonment Board, Sargodha

Project: Providing / Laying of Sewerage Lines / Drains Ward No. 10 Sargodha Cantt (Phase-I)

Our Ref. No. CL/CED/ 1570 Dated: 28-03-23

Your Ref. No. CBS/Cantt/01/96 Dated: 02-03-23

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 27-03-23 Tested on: 28-03-23 in dry/wet condition



Test Specification

(ASTM C39)



Sr. No.	Mark*			Date*	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	E. Cost (M), 15.45	1	2	2023	6Diax12		13.2	28.28	81	6416		Non Engraved
2	E. Cost (M), 15.45	1	2	2023	6Diax12		13.4	28.28	83	6574		Non Engraved
3												
4												
5					/	GINE	RINE					
6					>	T READ IN	200	X				
7						DE THY LORD WHO	₩. <u></u>	=				
8					es	رقتال		8 -				
9							-					
10						-UA	IOR'S					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5007 Dr. Umbreen

To: Cantonment Executive Officer

Our Ref. No. CL/CED/ 1571

Sargodha Cantt. Office of the Cantonment Board, Sargodha

Project: Providing / Laying of Sewerage Lines / Drain at Ward No. 06 Sargodha Cantt.

Your Ref. No. CBS/Cantt/01/87 Dated: 02-03-23

Dated:

28-03-23

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 27-03-23 Tested on: 28-03-23 in dry/wet condition



Test Specification

(ASTM C39)



Sr. No.	Mark*			Date*	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	E. Cost (M), 2.48	1	2	2023	6Diax12		13.2	28.28	81	6416		Non Engraved
2	E. Cost (M), 2.48	1	2	2023	6Diax12		13.2	28.28	100	7921		Non Engraved
3												
4												
5					/	GINE	RIATE					
6						NEAD IN	200					
7						DHE NAME OF THY LIDRO WHO	1812	E -				
8					on			IND.				
9						<u></u>	72					
10						· LA	HORE.					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5007 Dr. Umbreen

To: Cantonment Executive Officer

Our Ref. No. CL/CED/ 1572

Sargodha Cantt. Office of the Cantonment Board, Sargodha

Project: Providing / Laying of Sewerage / Drain at Ward No. 06, 07, 08, 09 and 10 Sargodha Cantt.

Dated:

28-03-23

Your Ref. No. CBS/Cantt/01/79 Dated: 02-03-23

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 27-03-23 Tested on: 28-03-23 in dry/wet condition



Test Specification

(ASTM C39)



Sr. No.	Mark*	Casting Date*				Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	E. Cost (M), 6.37	1	2	2023	6Diax12		13.2	28.28	79	6257		Non Engraved
2	E. Cost (M), 6.37	1	2	2023	6Diax12		13.4	28.28	75	5941		Non Engraved
3												
4												
5					/	RIVE	RINE					
6						READ N	200					
7						DHE NAME OF THY LIGHTO WHIC	- (F)	-				
8					on			INO				
9												
10						-LA	IORE					
11												
12												
13												
14												
15												
16												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 5006 Dr. Umbreen

Test Specification

To: Mr. Abdul Qadir Ali

Fateh Garh, Lahore Cantt.

Project: 42A/C1 Gulberg III

Our Ref. No. CL/CED/ 1573 Dated: 28-03-23

Your Ref. No. Nil Dated: Nil (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 27-03-23 Tested on: 28-03-23 in dry/wet condition





Sr. No.	Mark*			Date*	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	2nd Floor Slab (3000 Psi)	23	2	2023	6Diax12		13.6	28.28	51	4040		Engraved
2	2nd Floor Slab (3000 Psi)	23	2	2023	6Diax12		14	28.28	43	3406		Engraved
3												
4												
5			ł		/	GINE	RINE					
6			ł			READW					-	
7			ł			DHE NIGGE OF THY LIDRO WHO	1999	EB -			-	
8					S			- No				
9			ł								-	
10			ł			"-LA	HORE.				-	
11			ł								-	
12			ł								-	
13												
14			I									
15			I									
16			-									

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 4995 Dr. Umbreen

To: Mr. Abdubakar Jamil, Site Engineer

ENAARA Developers, 92-B/2, Gulberg III, Lahore

Project: Nil

Your Ref. No.

Our Ref. No. CL/CED/ 1574

Dated: 28-03-23

Test Specification
(ASTM C39)

Dated: 22-03-23

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 22-03-23 Tested on: 28-03-23 in dry/wet condition



•						<u> </u>						UNLINE REPORT
Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	4000 Psi	24	2	2023	6Diax12		13	28.28	61	4832		Non Engraved
2	4000 Psi	24	2	2023	6Diax12		13.4	28.28	55	4356		Non Engraved
3	4000 Psi	24	2	2023	6Diax12		13.2	28.28	63	4990		Non Engraved
4	4000 Psi	24	2	2023	6Diax12		13	28.28	49	3881		Non Engraved
5	4000 Psi	24	2	2023	6Diax12	GINE	13.2	28.28	55	4356		Non Engraved
6						NEAD IN	200	X				
7						DE NIGE OF THY LORD WHO	- E	류				
8					- 88							
9), <u> </u>		7				
10					<	-LA	HORE.					
11												
12					I							
13												
14												
15												
16												
\A/''4						· · · · · · · · · · · · · · · · · · ·	· · · · · · · · · · · · · · · · · · ·					·

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 4987 Dr. Umbreen

To: Sub Divisional Officer

Your Ref. No.

Buildings Sub Division No. 12, Lahore

144

Project: Establishment of Govt. Technical Training Institute for Women, Sabzazar District Lahore.

Our Ref. No. CL/CED/ 1575

Dated: 28-03-23

15-03-23

Dated:

Test Specification
(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 20-03-23 Tested on: 28-03-23 in dry/wet condition

ONLINE REPORT

Sr. No.	Mark*			Date*	Size (in)	Wet Weight	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)			Water Absorpti on (%)	Remarks
1	Third Floor Slab (1:2:4)	16	2	2023	6x6x6		8.6	36	116	7218		Non Engraved
2	Third Floor Slab	16	2	2023	6x6x6		8.8	36	114	7093		Non Engraved
3	(1:2:4) Third Floor Slab (1:2:4)	16	2	2023	6x6x6		8.8	36	112	6969		Non Engraved
4							-					
5			-		/	RIVE	RING					
6						READIN		X				
7						DE NAME OF THY LORD WHO	- N	F				
8					es		No. of London	3 -				
9							-	7				
10			-		🤇	"-LA	IORE.					
11												
12			ł									
13			ł									
14			ł									
15												
16			-									

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.