

Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

6982 Dr. Aqsa

To: Mr. M. Ashraf Javed

Project Incharge, Ijaz Cotton Pvt. Ltd.

Project: Ijaz Cotton Pvt. Ltd. Nabi Baksh 34 km Ferozepur Road Lahore.

Our Ref. No. CL/C	CED/ 4630	Dated:	09-04-24	Test Specification
Your Ref. No.	TM - Ground Floor Columns	Dated:	02-04-24	(ASTM C39)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	3-04	-24	Tested on:	09-0	4-24	in dry/wet	t condition		Ē	je ster
Sr. No.	Mark*	Cas DD	-	Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(5000 Psi)	21	3	2024	6Diax12		13.2	28.28	54	4277		Engraved
2	(5000 Psi)	21	3	2024	6Diax12		14	28.28	58	4594		Engraved
3	(5000 Psi)	21	3	2024	6Diax12		13.8	28.28	54	4277		Engraved
4												
5					1	HINE	RIN S					
6					-	READIN						
7						OF THY UCRD WHO OREATES	ریج۔ انڈکی خلق ر					
8					1							
9						200		~				
10					<	-LA	IDRL.					
11												
12												
13												
14												
15												
16												
Witnessed by:												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

6982 Dr. Aqsa

To: Mr. M. Ashraf Javed

Project Incharge, Ijaz Cotton Pvt. Ltd.

Project: Ijaz Cotton Pvt. Ltd. Nabi Baksh 34 km Ferozepur Road Lahore.

Our Ref. No. CL/	CED/ 4631	Dated:	09-04-24	Test Specification
Your Ref. No.	TM - Ground Floor Columns	Dated:	02-04-24	(ASTM C39)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	3-04	-24	Tested on:	09-0)4-24	in dry/we	t condition		Ē	je ster
Sr. No.	Mark*	Cas DD	-	Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(5000 Psi)	20	3	2024	6Diax12		13.6	28.28	45	3564		Engraved
2	(5000 Psi)	20	3	2024	6Diax12		14	28.28	58	4594		Engraved
3	(5000 Psi)	20	3	2024	6Diax12		14	28.28	56	4436		Engraved
4												
5						THE	RING A					
6						READIN	2071					
7						OF THY HORD WHO OREATES	زیجی ان کی خلق ر					
8					- 88			5				
9								>				
10						-IA	IDR <u>E.</u>			-		
11												
12												
13												
14												
15												
16												
Witnessed by:												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

6982 Dr. Aqsa

To: Mr. M. Ashraf Javed

Project Incharge, Ijaz Cotton Pvt. Ltd.

Project: Ijaz Cotton Pvt. Ltd. Nabi Baksh 34 km Ferozepur Road Lahore.

Our Ref. No. CL/0	CED/ 4632	Dated:	09-04-24	Test Specification
Your Ref. No.	TM - Ground Floor Columns	Dated:	02-04-24	(ASTM C39)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	3-04	-24	Tested on:	09-0)4-24	in dry/we	t condition		Ü	je steri
Sr. No.	Mark*	Cas DD	-	Date*	Size (in)	Wet Weight	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate Ioad (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(5000 Psi)	18	3	2024	6Diax12	(rtg/ giiis) 	(Rg/ gills) 14	28.28	58	(psi) 4594		Engraved
2	(5000 Psi)	18	3	2024	6Diax12		14.2	28.28	60	4752		Engraved
3	(5000 Psi)	18	3	2024	6Diax12		14.2	28.28	64	5069		Engraved
4												
5						NHNE	RING					
6					-	READIN	2071					
7						OF THY HORD WHO OREATES	زیجی ان کی خلق ر					
8					1							
9						200		~				
10					<	/ A	IORL.					
11												
12												
13												
14												
15												
16												
Witnessed by:												

witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 <u>ORIGINAL</u> A carbon copy for the report has been retained in the lab for record.

> 6968 Dr. Aqsa

To: Hussain Construction Company

4th Floor, 244-C, DHA Phase-8, Broadway, Lahore.

Project: Construction of Slab Concrete (Mess & Hostle) of Ground Floor at CMH Medical and Dental College, Lahore.

Our Ref. No. CL/CED/ 4633	Dated:	09-04-24	Test Specification
Your Ref. No. Nil	Dated:	01-04-24	(ASTM C39)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	1-04	-24	Tested on:	09-0)4-24	in dry/wet condition			Ü	jeskeg
Sr. No.	Mark*	Cas DD	_	Date* YYYY	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)		Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	1:2:4 (3000 Psi)	28	2	2024	6Diax12		14	28.28	36	2851		Engraved
2	1:2:4 (3000 Psi)	28	2	2024	6Diax12		14	28.28	60	4752		Engraved
3	1:2:4 (3000 Psi)	28	2	2024	6Diax12		13.6	28.28	65	5149		Engraved
4												
5					-	WHINE	RING				-	
6						READIN	2000					
7						OF THY GORD WHO CREATES	ر بک اند کی خلق ر	I FCH				
8					S.R. 1			i Na			-	
9					-						-	
10					-		IDR				-	
11												
12												
13												
14												
15												
16												
Witnessed by:												

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients) 2. The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)



Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

7002 Dr. Aqsa

To: **Director Projects**

Innovative Construction Company

Project: Shoring Works at Kingdom Arena, RUDA, Lahore.

Our Ref. No. CL/CED/ 4634

Your Ref. No. ICL/KA/Piling/0424/01

COMPRESSION TEST REPORT



Test Specification

(ASTM C39)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	8-04	-24	Tested on:	09-0)4-24	in dry/wet condition			Ē		
Sr. No.	Mark*	Cas	-	Date*	Size (in)	Wet Weight (Ka/ ams)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate load (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks	
1		9	3	2024	6Diax12		14	28.28	51	4040		Non Engraved	
2		9	3	2024	6Diax12		14.2	28.28	58	4594		Non Engraved	
3		9	3	2024	6Diax12		14.4	28.28	57	4515		Non Engraved	
4		10	3	2024	6Diax12		13.6	28.28	50	3960		Non Engraved	
5		10	3	2024	6Diax12	NHNE	RI/14	28.28	61	4832		Non Engraved	
6		10	3	2024	6Diax12	READ IN	13.8	28.28	60	4752		Non Engraved	
7		11	3	2024	6Diax12	OF THY HORD WHO OREATES	14 ع ان کی خلق ر	28.28	80	6337		Non Engraved	
8		11	3	2024	6Diax12		15	28.28	74	5861		Non Engraved	
9		11	3	2024	6Diax12	20-	13.6	28.28	64	5069		Non Engraved	
10					<	(A	IORE.						
11													
12													
13													
14													
15													
16													
Witnessed by:													

Dated:

Dated:

09-04-24

07-04-24

witnessea by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1.The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)

2. The test results are recommended to be interpreted in the light of above factors by the engineer.



To:

Plain and Reinforced Concrete Laboratory Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL A carbon copy for the report has been retained in the lab for record.

> 6991 Dr. Aqsa

:	Mr. M. Usman R Resident Engine	auf eer, NESPAK (Pvt.) Ltd. Highways and Tra	nsportation Engineering I	Division.
	Project: Rehabil Projects)	itation of Road, Streets & Boundary Wall	Graveyard Kot Kamboh, A	A.I Zone Lahore. (MCL
	Our Ref. No. CL	/CED/ 4635	Dated:	09-04-24
	Your Ref. No.	4084/103/MUR/104/1824	Dated:	22-03-24

COMPRESSION TEST REPORT



Test Specification (BS 1881-116)

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specim	ens received on:	0	4-04	-24	Tested on:	09-0)4-24	in dry/we	t condition			ONLINE REPORT
Sr. No.	Mark*		-	Date*	Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate Ioad (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1		22	2	2024	6x6x6		9	36	87	5413		Non Engraved
2		22	2	2024	6x6x6		8.6	36	55	3422		Non Engraved
3		22	2	2024	6x6x6		9	36	44	2738		Non Engraved
4						/						
5					-	NHNE	RING					
6					-	READIN	2071					
7						OF THY 	ز <u>ع</u> ک اندکی خلق ر					
8					S.R.			5				
9					-		101	~				
10							IORE.					
11												
12												
13												
14												
15												
16												
Witnessed by: Nil												

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)

2. The test results are recommended to be interpreted in the light of above factors by the engineer.



Civil Engineering Department

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

7000 Dr. Aqsa

To: Mr. Muazzam Shaukat Muhammad Younis Construction Company

Project: House # 184-D, DHA Phase-8, Ex-Park View

Our Ref. No. CL/CED/ 4636	Dated:	09-04-24	Test Specification
Your Ref. No. Nil	Dated:	08-04-24	(BS 1881-116)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on:			8-04	-24	Tested on:	09-04-24		in dry/wet condition				ONLINE REPORT
Sr. No.	Mark*	Casting Date*			Size (in)	Wet Weight (Kg/ gms)	Dry Weight (Kg/ gms)	Area of X-Section (Sq. in)	Ultimate Ioad (Imp.Tons)	Ultimate Stress (psi)	Water Absorpti on (%)	Remarks
1	(4000 Psi)	24	3	2024	6x6x6		8.4	36	66	4107		Non Engraved
2	(4000 Psi)	24	3	2024	6x6x6		9	36	62	3858		Non Engraved
3	(4000 Psi)	24	3	2024	6x6x6		8.8	36	65	4044		Non Engraved
4							-			-		
5						THE	RING			-		
6)	READ IN	2000					
7						OF THY CORD WHO CREATES	ر بک اند کی خلق ر					
8					S.R. 1					-		
9								~				
10					<		IOR					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil											

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

1. * as engraved on the specimens (if any)

2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption

3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprensive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)

2. The test results are recommended to be interpreted in the light of above factors by the engineer.

