



Plain and Reinforced Concrete Laboratory

Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL
A carbon copy for the report has been retained in the lab for record.

8372
Dr. Aqsa

To: Sub Divisional Officer
Building Sub Division No.10, Lahore.

Project: CONSTRUCTION OF ANTI-RIOT HEADQUARTERS AT HARBANSPURA, LAHORE.

Our Ref. No. CL/CED/ 6756

Dated: 17-12-24

Test Specification

Your Ref. No. 4772/10th

Dated: 11-09-23

(----)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-12-24 Tested on: 17-12-24 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorption (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	S	---	---	---	8.8 x 4.4 x 2.9	3835	3355	38.72	44	2545	14.31	---
2	S	---	---	---	8.8 x 4.4 x 2.9	3695	3250	38.72	48	2777	13.69	---
3	S	---	---	---	8.9 x 4.4 x 3	3725	3280	39.16	49	2803	13.57	---
4	---	---	---	---	---	---	---	---	---	---	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---
6	---	---	---	---	---	---	---	---	---	---	---	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by:

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports1/>

- * as engraved on the specimens (if any)
- ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory

Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

8372
Dr. Aqsa

To: Sub Divisional Officer
Building Sub Division No.10, Lahore.

Project: CONSTRUCTION OF ANTI-RIOT HEADQUARTERS AT HARBANSPURA, LAHORE.

Our Ref. No. CL/CED/ 6757

Dated: 17-12-24

Test Specification

Your Ref. No. 5662/10th

Dated: 06-06-24

(----)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-12-24 Tested on: 17-12-24 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorption (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	S	---	---	---	8.8 x 4.4 x 2.9	3515	3090	38.72	51	2950	13.75	---
2	S	---	---	---	8.9 x 4.4 x 3	3695	3245	39.16	48	2746	13.87	---
3	S	---	---	---	8.9 x 4.4 x 2.9	3690	3230	39.16	47	2688	14.24	---
4	---	---	---	---	---	---	---	---	---	---	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---
6	---	---	---	---	---	---	---	---	---	---	---	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by:

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports1/>

- * as engraved on the specimens (if any)
- ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory

Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

8372
Dr. Aqsa

To: Sub Divisional Officer
Buildings Sub Division No.16, Lahore.

Project: CONSTRUCTION OF SMART POLICE STATION HARBANSPURA, LAHORE.

Our Ref. No. CL/CED/ 6758

Dated: 17-12-24

Test Specification

Your Ref. No. 352

Dated: 17-02-24

(----)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-12-24 Tested on: 17-12-24 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorption (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	RB	---	---	---	8.9 x 4.3 x 3	3695	3240	38.27	49	2868	14.04	---
2	RB	---	---	---	8.9 x 4.4 x 2.9	3585	3170	39.16	42	2402	13.09	---
3	RB	---	---	---	8.8 x 4.4 x 2.9	3630	3200	38.72	49	2835	13.44	---
4	---	---	---	---	---	---	---	---	---	---	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---
6	---	---	---	---	---	---	---	---	---	---	---	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by:

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports1/>

- * as engraved on the specimens (if any)
- ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory

Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

8372
Dr. Aqsa

To: Sub Divisional Officer
Buildings Sub Division No.16, Lahore.

Project: CONSTRUCTION OF SMART POLICE STATION BATAPUR, LAHORE.

Our Ref. No. CL/CED/ 6759

Dated: 17-12-24

Test Specification

Your Ref. No. 361

Dated: 19-02-24

(----)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-12-24 Tested on: 17-12-24 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorption (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	RB	---	---	---	8.9 x 4.4 x 2.9	3745	3275	39.16	45	2574	14.35	---
2	RB	---	---	---	9 x 4.4 x 3	3715	3250	39.6	45	2545	14.31	---
3	RB	---	---	---	8.9 x 4.4 x 2.9	3690	3220	39.16	49	2803	14.6	---
4	---	---	---	---	---	---	---	---	---	---	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---
6	---	---	---	---	---	---	---	---	---	---	---	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by:

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports1/>

- * as engraved on the specimens (if any)
- ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory

Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

8430
Dr. Aqsa

To: Mr. Muhammad Imran
Senior Project Manager, IDAP

Project: Nil

Our Ref. No. CL/CED/ 6760

Dated: 17-12-24

Test Specification

Your Ref. No. SPM(NETZERO)/IDAP/2024/20919

Dated: 13-12-24

(ASTM C39)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13-12-24 Tested on: 17-12-24 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorption (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	---	5	12	2024	6Diax12	---	13	28.28	51	4040	---	Non Engraved
2	---	5	12	2024	6Diax12	---	13.2	28.28	42	3327	---	Non Engraved
3	---	5	12	2024	6Diax12	---	13	28.28	57	4515	---	Non Engraved
4	---	---	---	---	---	---	---	---	---	---	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---
6	---	---	---	---	---	---	---	---	---	---	---	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by: Nil

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports1/>

- * as engraved on the specimens (if any)
- ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory

Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

8439
Dr. Aqsa

To: Mr. Farrukh
Sr. Manager Projects, Premier Trading Services (Pvt) Ltd.

Project: Construction of a Warehouse at Harbanspura.

Our Ref. No. CL/CED/ 6761

Dated: 17-12-24

Test Specification

Your Ref. No. Nil

Dated: Nil

(ASTM C39)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 16-12-24 Tested on: 17-12-24 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorption (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	---	4	10	2024	6Diax12	---	13.4	28.28	85	6733	---	Non Engraved
2	---	4	10	2024	6Diax12	---	14	28.28	83	6574	---	Non Engraved
3	---	---	---	---	---	---	---	---	---	---	---	---
4	---	---	---	---	---	---	---	---	---	---	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---
6	---	---	---	---	---	---	---	---	---	---	---	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by: Nil

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports1/>

- * as engraved on the specimens (if any)
- ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory

Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

8406
Dr. Aqsa

To: Mr. HUZAIFA JAVED
Lt Commander PN, GE (Navy) Lahore.

Project: CA NO. ENC-N-33/2025 - CONSTRUCTION OF ADMIN BLOCK AT PN WAR COLLEGE WALTON LAHORE.

Our Ref. No. CL/CED/ 6762

Dated: 17-12-24

Test Specification

Your Ref. No. 6024/181/23/E-6

Dated: 06-12-24

(----)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 11-12-24 Tested on: 17-12-24 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorption (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	7UP	---	---	---	8.6 x 4.1 x 2.9	3605	3310	35.26	44	2795	8.91	---
2	7UP	---	---	---	8.9 x 4.1 x 2.8	3620	3340	36.49	43	2640	8.38	---
3	7UP	---	---	---	8.9 x 4.2 x 3	3650	3385	37.38	44	2637	7.83	---
4	ZBC	---	---	---	9 x 4.2 x 3	3730	3430	37.8	44	2607	8.75	---
5	ZBC	---	---	---	9 x 4.2 x 3	3785	3500	37.8	43	2548	8.14	---
6	ZBC	---	---	---	8.9 x 4.2 x 3	3615	3340	37.38	47	2816	8.23	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by:

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports1/>

- * as engraved on the specimens (if any)
- ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- **** ACI318-08 requires mean of two sample (6"x12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory



Plain and Reinforced Concrete Laboratory

Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

8442
Dr. Aqsa

To: Engr. Haseeb Afzal
Project Manager, HMB Developers Pvt. Ltd

Project: Construction of Commercial Tower, Finance Trade Centre Lahore (9th Floor Slab Pour 2 A' ~ G'/1~4')

Our Ref. No. CL/CED/ 6763

Dated: 17-12-24

Test Specification

Your Ref. No. HMBDPL/S.O/12/24/150(LHR)

Dated: 17-12-24

(ASTM C39)

COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 17-12-24 Tested on: 17-12-24 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorption (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	CT-170 (3500 Psi)	14	11	2024	6Diax12	---	14.4	28.28	63	4990	---	Non Engraved
2	CT-170 (3500 Psi)	14	11	2024	6Diax12	---	14	28.28	61	4832	---	Non Engraved
3	CT-170 (3500 Psi)	14	11	2024	6Diax12	---	14.4	28.28	56	4436	---	Non Engraved
4	---	---	---	---	---	---	---	---	---	---	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---
6	---	---	---	---	---	---	---	---	---	---	---	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by: Mr. Ghulam Nabi, CNIC 35201-1248412-1

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports/>

- * as engraved on the specimens (if any)
- ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

Note: Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory