

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 6561 Dr. Umbreen

To: Engr. Haseeb Afzal

Project Manager, HMB Developers (Pvt) Ltd.

Project: Commercial Tower, Finance Trade Centre, Lahore. (B1 Shear Wall C~D/1~2)

Our Ref. No. CL/CED/ 3989 Dated: 18-01-24 <u>Test Specification</u>

Your Ref. No. HMBDPL/S.O/01/24/90th (LHR) Dated: 18-01-24

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-01-24 Tested on: 18-01-24 in dry/wet condition



(ASTM C39)



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	CT-70 (6000 Psi)	12	12	2023	6Diax12		14	28.28	95	7525		Non Engraved
2	CT-70 (6000 Psi)	12	12	2023	6Diax12		13.6	28.28	89	7050		Non Engraved
3	CT-70 (6000 Psi)	12	12	2023	6Diax12		13.6	28.28	74	5861		Non Engraved
4			-									
5			-			WEINE	RING					
6			-			READ IN	207				-	
7			1		- A	OF THY GREATES	ر تیب اند کی خلق ر	193		-	1	
8			-									
9								~				
10						-UA	IORE.					
11			-									
12			-				-					
13												
14												
15							-				-	
16							-				-	

Witnessed by: Mr. Haris Shah Syed

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL**

A carbon copy for the report has been retained in the lab for record.

6559 Dr. M. Burhan

To: Mr. Zeeshan Sadique

Equal Marketing Pvt. Ltd.

Project: Construction of a Plaza at Plot No. CA-35, 36 & 37, Down Town, Fazaia Housing Society, Lahore.

Our Ref. No. CL/CED/ 3990 Dated: 18-01-24 **Test Specification**

Your Ref. No. Dated: Nil (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 18-01-24 Tested on: 18-01-24 in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	R.C.C Wall (1:2:4), (3000 Psi)	20	12	2023	6Diax12		14	28.28	46	3644		Non Engraved
2	R.C.C Wall (1:2:4), (3000 Psi)	20	12	2023	6Diax12		13.4	28.28	48	3802		Non Engraved
3	Column (1:2:2), (4500 Psi)	20	12	2023	6Diax12		14	28.28	50	3960		Non Engraved
4												
5						THE	RING					
6					}	READ IN	207			-		
7					1	OF THY	ر تیب اند کی خلق ر	<u></u>		I		
8					887			5		I		
9										-		
10						-LA	IORE.			I		
11					-					I		
12												
13												
14												
15												
16							-					
Witness	sed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACl318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 6510 Dr. Umbreen

To: Mr. Shahzad Munir

Resident Engineer, G3 Engineering Consultants (Pvt) Ltd.

Project: Consultancy Services for Master Planning Designing and Resident Type Supervision of the Scheme

Strengthening of University of Narowal.

Our Ref. No. CL/CED/ 3991 Dated: 18-01-24

Your Ref. No. G3/237/RE/138 Dated: 08-01-24 (BS 3921**)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 09-01-24 Tested on: 18-01-24 in dry/wet condition



Test Specification



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	28				8.9 x 4.3 x 3	3595	3115	38.27	38	2224	15.41	
2	28				9 x 4.3 x 3	3720	3260	38.7	44	2547	14.11	
3	28				8.9 x 4.3 x 2.9	3565	3185	38.27	46	2692	11.93	
4	28				8.9 x 4.3 x 3	3670	3300	38.27	46	2692	11.21	
5	28				9 x 4.3 x 3	3675	3235	38.7	45	2605	13.6	
6) å	KEAU N	200	X				
7					- 7	OF THY	ر تاب المراقع ا	<u> </u>				
8								3				
9						1						
10						-1A	IORE.					
11												
12												
13												
14												
15							-				-	
16												
Witness	sed by:				•							

Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 6538 Dr. Ubaid

To: Mr. Muhammad Sohail Anjum

Project Manager, MS IT Tower, Lahore.

Project: Construction of MS IT Tower at Plot 450,451 Johar Town, Lahore.

Our Ref. No. CL/CED/ 3992 Dated: 18-01-24 <u>Test Specification</u>

Your Ref. No. MSITT/UET/2024/C-004 Dated: 13-01-24

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 15-01-24 Tested on: 18-01-24 in dry/wet condition



(ASTM C39)



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	мм	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	No.1 (3000 Psi)	16	12	2023	6Diax12		14	28.28	32	2535		Engraved
2	No.4 (3000 Psi)	16	12	2023	6Diax12		13.8	28.28	30	2376		Engraved
3	No.7 (3000 Psi)	16	12	2023	6Diax12		13.8	28.28	36	2851		Engraved
4						/						
5						THE	RING					
6)	READ IN	200					
7					3	OF THY RORD WHO OREATES	ر تیب ان کی خلق ر	133				
8								AS .				
9						10						
10						LA	IORE.					
11												
12												
13												
14												
15			-								-	
16												
Witness	ed by: Nil											

witnessed by: Nii

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACl318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

6537 Dr. M. Burhan

To: Mr. Waqas Ali

Variant, 25-t, Gulberg-II, Lahore.

Project: Construction of Colums (C1-7, C1-8, SH-2, CL-9, C1-10, C1-11, C1-13, C1-14, SH-4,5)

Our Ref. No. CL/CED/ 3993 Dated: 18-01-24 <u>Test Specification</u>

Your Ref. No. VA/29/136 Dated: 12-01-24 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-01-24 Tested on: 18-01-24 in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	6th Floor Columns	8	12	2023	6Diax12		14	28.28	72	5703		Non Engraved
2	6th Floor Columns	8	12	2023	6Diax12		14	28.28	70	5545		Non Engraved
3	6th Floor Columns	8	12	2023	6Diax12		15	28.28	70	5545		Non Engraved
4						/						
5						THE	RING					
6)	READ IN	200	X				
7					3	OF THY	ر تجب اند في خلق ر	E				
8												
9						1		~ /				
10						-1A	IORE.					
11												
12				-								
13				-								
14												
15										-		
16												
Witness	ed by: Mr. Babar A	Ali. C	NIC #	‡ 3520°	1-9967694-3							

Witnessed by: Mr. Babar Ali, CNIC # 35201-9967694-3

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACl318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

6537 Dr. M. Burhan

To: Mr. Waqas Ali

Variant, 25-t, Gulberg-II, Lahore.

Project: Construction of Colums (Lift Wall, C1-12)

 Our Ref. No. CL/CED/
 3994
 Dated:
 18-01-24
 Test Specification

 Your Ref. No.
 VA/29/135
 Dated:
 12-01-24
 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-01-24 Tested on: 18-01-24 in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	6th Floor Lift Wall	4	12	2023	6Diax12		14	28.28	77	6099		Non Engraved
2	6th Floor Lift Wall	4	12	2023	6Diax12		14	28.28	81	6416		Non Engraved
3	6th Floor Lift Wall	4	12	2023	6Diax12		14	28.28	56	4436	1	Non Engraved
4										I		
5						HEINE	RING			I		
6					}	READ IN	207			I	-	-
7						OF THY	ر بجب اند فی طاق ر	===		-		
8								5		I		
9										I		
10						(A	IORE.					
11										I		
12							-			I		
13							-			I		
14												
15												
16												

Witnessed by: Mr. Babar Ali, CNIC # 35201-9967694-3

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 6536 Dr. Ubaid

To: Mr. Muhammad Asif

Project Manager, Imperium Developers.

Project: Construction of Sixty6 at Gulberg-III, Lahore.

Our Ref. No. CL/CED/ 3995 Dated: 18-01-24 <u>Test Specification</u>

Your Ref. No. IMP/66/09/135 Dated: 12-01-24 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-01-24 Tested on: 18-01-24 in dry/wet condition





Sr. No.	Sr. No. Mark*		ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	5000 Psi	25	11	2023	6Diax12		14	28.28	94	7446		Non Engraved
2	5000 Psi	25	11	2023	6Diax12		14.4	28.28	72	5703		Non Engraved
3												
4						/						
5						THE	RING					
6) a	KEAU N	200	X				
7					- 2	OF THY	ان کی خلق ر ان کی خلق ر	<u> </u>				
8								5-				
9						10		~ /				
10						/A	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by: Mr. Muhammad Tahir Ayaz, CNIC # 35202-3320913-1

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL
A carbon copy for

A carbon copy for the report has been retained in the lab for record.

> 6536 Dr. Ubaid

To: Mr. Muhammad Asif

Project Manager, Imperium Developers.

Project: Construction of Sixty6 at Gulberg-III, Lahore.

Our Ref. No. CL/CED/ 3996 Dated: 18-01-24 <u>Test Specification</u>

Your Ref. No. IMP/66/09/136 Dated: 12-01-24 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-01-24 Tested on: 18-01-24 in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	5000 Psi	30	11	2023	6Diax12		13.8	28.28	95	7525		Non Engraved
2	5000 Psi	30	11	2023	6Diax12		13.8	28.28	95	7525		Non Engraved
3												
4												
5					(THE	RING					
6)	READ IN	200	K				
7					17	OF THY	از بی ااز کی خلق ر	<u> </u>				
8												
9								~/				
10						LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by: Mr. Muhammad Tahir Ayaz, CNIC # 35202-3320913-1

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 6536 Dr. Ubaid

To: Mr. Muhammad Asif

Project Manager, Imperium Developers.

Project: Construction of Sixty6 at Gulberg-III, Lahore.

Our Ref. No. CL/CED/ 3997 Dated: 18-01-24 <u>Test Specification</u>

Your Ref. No. IMP/66/09/137 Dated: 12-01-24 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 12-01-24 Tested on: 18-01-24 in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	5000 Psi	5	12	2023	6Diax12		13.8	28.28	84	6653		Non Engraved
2	5000 Psi	5	12	2023	6Diax12		14.4	28.28	84	6653		Non Engraved
3												
4						/						
5						THE	RING					
6						KEAD IN	200	X				
7					- 2	OF THY	ر تیب الدی خلق ر	E				
8							-					
9)?	10		~ /				
10						/A	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by: Mr. Muhammad Tahir Ayaz, CNIC # 35202-3320913-1

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/
1. * as engraved on the specimens (if any)

^{2. **} BS3921 requires average of ten clay brick samples for crushing strength and water absorption

^{3. ***} BS5328 requires mean of two cube sample strength at 28 days as characteristic strength

^{4. ****} ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

^{1.} The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)

^{2.} The test results are recommended to be interpreted in the light of above factors by the engineer.