

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 7315 Dr. Umbreen

To: Director ADS-I,

Office of Director ADS-I, Lahore Development Authority UD.Wing. (M/s M. Karamat Builders)

Project: Development of Signal Free Corridor from Main Boulevard Gulberg (Center Point) to Walton Road

(Defence Morr) .Construction of Additional Sump Well for Khan Colony Lahore Cantt.

Our Ref. No. CL/CED/ 5107 Dated: 20/06/2024

Your Ref. No. D(ADS-I)/LDA/367 Dated: 12/06/2024

Test Specification

(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13/06/2024 Tested on: 20/06/2024 in dry/wet condition





Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Well	12	5	2024	6Diax12		13.4	28.28	60	4752		Non Engraved
2	Well	12	5	2024	6Diax12		14	28.28	73	5782		Non Engraved
3	Well	12	5	2024	6Diax12		13	28.28	80	6337		Non Engraved
4	Well	12	5	2024	6Diax12		14	28.28	74	5861		Non Engraved
5	Well	12	5	2024	6Diax12	MARIE	RI 14	28.28	94	7446		Non Engraved
6	Well	12	5	2024	6Diax12	[KEAD IN	13.2	28.28	54	4277		Non Engraved
7						THE NAME OF THY LORD WHO	()	3				
8					- 00	JOHANES		5 _				
9						7,-		5/				
10						"-LA	IORE					
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 7304 Dr. Umbreen

To: Hussain Construction Company

DHA-Phase-8, Broadway, Lahore.

Project: Construction of Allied School (CMH Medical and Dental College Lahore)

Our Ref. No. CL/CED/ 5108 Dated: 20/06/2024

Your Ref. No. Nil Dated: Nil (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13/06/2024 Tested on: 20/06/2024 in dry/wet condition



Test Specification



Sr. No. Mark*		Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	3rd F.Slab(1:2:4) (3000 Psi)	15	5	2024	6Diax12		14	28.28	54	4277		Engraved
2	3rd F.Slab(1:2:4) (3000 Psi)	15	5	2024	6Diax12		14	28.28	54	4277		Engraved
3	3rd F.Slab(1:2:4) (3000 Psi)	15	5	2024	6Diax12		14	28.28	58	4594		Engraved
4												
5						RINE	RINA					
6						READ IN	2001					
7						THE NAME OF THY LORD WHO	() () () () () () () () () ()	3				
8					80	Juliano						
9								5 /				
10						-LA	ORE					
11												
12												
13												
14												
15												
16										-		

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL**

A carbon copy for the report has been retained in the lab for record.

> 7289 Dr. Umbreen

To: Mr. Gul Wagas Shahid

Unirazz Services

Project: Construction of Syed Wajid Ali Shah Auditorium Al-Aleem Medical College, Gulab Devi Hospital

Lahore.

Our Ref. No. CL/CED/ 5109 Dated: 20/06/2024 **Test Specification**

Your Ref. No. USPL/2206 10/06/2024 Dated:

(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

10/06/2024 Tested on: 20/06/2024 Specimens received on: in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	A1-2, A3-2, D3-2, D5- 2	3	6	2024	6Diax12		13	28.28	44	3485		Non Engraved
2	A1-2, A3-2, D3-2, D5- 2	3	6	2024	6Diax12		13	28.28	46	3644		Non Engraved
3	A1-2, A3-2, D3-2, D5- 2	3	6	2024	6Diax12		13.2	28.28	40	3168		Non Engraved
4	A1-1, A4-1, B2-1, C1- 1,D2-1, D5-1	4	5	2024	6Diax12		13	28.28	50	3960		Non Engraved
5	A1-1, A4-1, B2-1, C1- 1,D2-1, D5-1	4	5	2024	6Diax12	CTNE	R 13	28.28	52	4119		Non Engraved
6	A1-1, A4-1, B2-1, C1- 1,D2-1, D5-1	4	5	2024	6Diax12	READ IN	13	28.28	62	4911		Non Engraved
7						THE NAME OF THY LORD WHO		1				
8					ss	Johnson		II)				
9						_	I					
10						-LA	ORL					
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1.The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2.The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 7287 Dr. Umbreen

To: Mr. Muhammad Waseem

Site Engineer, Jaffar Builders Engineers & Contractors.

Project: Boundary Wall Coca Sundar Green.

Our Ref. No. CL/CED/ 5110 Dated: 20/06/2024

Your Ref. No. JBCT-01 Dated: 10/06/2024 (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 10/06/2024 Tested on: 20/06/2024 in dry/wet condition



Test Specification



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	мм	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1		30	5	2024	6Diax12		13	28.28	40	3168		Engraved
2		30	5	2024	6Diax12		13	28.28	38	3010		Engraved
3		30	5	2024	6Diax12		13	28.28	34	2693		Engraved
4												
5						GINE	RING					
6						READ IN	District Control					
7						THE NAME OF THY LORD WHO	1 <u>1 </u>					
8												
9								·				
10						/A	IORE					
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 7280 Dr. Umbreen

To: Mr. Faisal Bhatti

Ittefaq Building Solutions (Pvt.) Ltd.

Our Ref. No. CL/CED/ 5111

Project: Construction of Mr. Chugtai House Residence at Plot #74 Muneer Road Cantt. Lahore. (Ali House)

3,...

Dated:

20/06/2024

Your Ref. No. Nil Dated: 07/06/2024

Test Specification
(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 07/06/2024 Tested on: 20/06/2024 in dry/wet condition

ONLINE REPORT

Sr. No.	. No. Mark*		sting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Pool Bed (4000 Psi)	30	4	2024	6Diax12		14	28.28	56	4436		Non Engraved
	Pool Bed (400)	30	4	2024	6Diax12		13.6	28.28	44	3485		Non Engraved
3	Pool Bed (4000 Psi)	30	4	2024	6Diax12		14	28.28	64	5069		Non Engraved
4												
5						GINE	RINTE					
6						READ IN	2001	X				
7						THE NAME OF THY LORD WHO	(e)(E				
8					ss	JONES .						
9								5/				
10						-LA	ORE					
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 7280 Dr. Umbreen

To: Mr. Faisal Bhatti

Ittefaq Building Solutions (Pvt.) Ltd.

Our Ref. No. CL/CED/ 5112

Project: Construction of Mr. Chugtai House Residence at Plot #74 Muneer Road Cantt. Lahore. (Omar House)

Dated:

20/06/2024

Your Ref. No. Nil Dated: 07/06/2024

Test Specification

(ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 07/06/2024 Tested on: 20/06/2024 in dry/wet condition



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	F/F Columns (4000 Psi)	24	4	2024	6Diax12		14	28.28	62	4911		Non Engraved
2	F/F Columns (4000 Psi)	24	4	2024	6Diax12		14	28.28	62	4911		Non Engraved
3	F/F Columns (4000 Psi)	24	4	2024	6Diax12		14	28.28	66	5228		Non Engraved
4												
5						RINE	RINZ					
6						READ IN	2001	X				
7						THE NAME OF THY LORD WHO	<u>رغي</u> العاد خلف	£ 6				
8					ss	Johnson				1		
9						_	I	6/		1		
10						LA	OR					
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 7279 Dr. Umbreen

To: Mr. M. Abrar Ahmad

M.Sc. Structural Engineer, Abrar Ahmad Associates

Project: Construction of 49 Ghaznavi Comm. Bahria Town Lahore.

Our Ref. No. CL/CED/ 5113 Dated: 20/06/2024

Your Ref. No. Nil Dated: Nil (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 07/06/2024 Tested on: 20/06/2024 in dry/wet condition



Test Specification



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	5th Floor Slab	30	5	2024	6Diax12		12.4	28.28	24	1901		Engraved
2	5th Floor Slab	30	5	2024	6Diax12		12	28.28	21	1663		Engraved
3	5th Floor Slab	30	5	2024	6Diax12		11.4	28.28	18	1426		Engraved
4												
5						GINE	RINE					
6)	READ IN	2001	X				
7						THE NAME OF THY LORD WHO	()	a				
8					80		<u> </u>	N/O				
9								5 /				
10						-LA	ORE					
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 7279 Dr. Umbreen

To: Mr. M. Abrar Ahmad

M.Sc. Structural Engineer, Abrar Ahmad Associates

Project: Construction of 49 Ghaznavi Comm. Bahria Town Lahore.

Our Ref. No. CL/CED/ 5114 Dated: 20/06/2024

Your Ref. No. Nil Dated: Nil (ASTM C39)

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 07/06/2024 Tested on: 20/06/2024 in dry/wet condition



Test Specification



Sr. No. Mark*		Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	4th Floor Slab	8	5	2024	6Diax12		13	28.28	36	2851		Engraved
2	4th Floor Slab	8	5	2024	6Diax12		13	28.28	44	3485		Engraved
3	4th Floor Slab	8	5	2024	6Diax12		13	28.28	42	3327		Engraved
4												
5						GINE	RING					
6)	READ IN	2001	X				
7						THE NAME OF THY LORD WHO	ا المارغات					
8					80			N/O				
9												
10						LA	ORE					
11												
12												
13												
14												
15												
16										-		

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 7306 Dr. Umbreen

To: Mr. Shahzad Mukhtar

Project Manager, Aitchison College Lahore.

Project: Construction of Riding Pavilion Aitchison College Lahore.

Our Ref. No. CL/CED/ 5115 Dated: 20/06/2024

Your Ref. No. P- Dated: 13/06/2024

COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 13/06/2024 Tested on: 20/06/2024 in dry/wet condition



Test Specification

(ASTM C39)



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)		(Imp.Tons)		on (%)	
1	3000 Psi	14	5	2024	6Diax12		13.4	28.28	68	5386		Non Engraved
2												
3												
4												
5						GINE	RINE					
6						READIN	2001					
7						THE NAME OF THY LORD WHO		E			-	
8					ss	JONES .					-	
9								5/			-	
10						-LA	ORE					
11												
12											-	
13											-	
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. * as engraved on the specimens (if any)
- 2. ** BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. *** BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. **** ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.