

University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

6828 Dr. M. Yousaf

To: Mr. Muhammad Imran Khan

Material Engineer, PIPAL HOUSE A-BLOCK

Project: Reconstruction of PIPAL House A-Block Lahore. (M/s Uni-Build Associates Pvt. Ltd.)

Our Ref. No. CL/CED/ 4416 Dated: 11-03-24 **Test Specification** 

Your Ref. No. 343/ECSP/PH/ME/41 Dated: 02-03-24

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 07-03-24 Tested on: 11-03-24 in dry/wet condition



( ASTM C39 )



Sr. No.	Mark*			Date*	Size	Wet Weight	Dry Weight	Area of X-Section		Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Electric Rooms Slab	3	2	2024	6Diax12		13.4	28.28	64	5069		Engraved
2	Electric Rooms Slab	3	2	2024	6Diax12		13.4	28.28	55	4356		Engraved
3	Electric Rooms Slab	3	2	2024	6Diax12		13.4	28.28	57	4515		Engraved
4										-		
5						HHE	RING			I		
6						READ IN	207			-		
7						OF THY	ا از فی طلق ر	====				
8								<u>_</u>				
9						-						
10						LA	IORE.			I		
11			-							I		
12			-				-			I		
13												
14												
15												
16										-		
Witness	ed by: Nil										•	

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACl318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

6826 Dr. M. Yousaf

To: Mr. Muhammad Farman

Resident Engineer, Jinnah Hospital Lahore.

Project: Resident Construction Supervision for "Revamping of Jinnah Hospital, Lahore." (New Construction

of "Reception and Toilet Block")

Our Ref. No. CL/CED/ 4417 Dated: 11-03-24

Your Ref. No. ECSP/RE/387/20 Dated: 23-02-24

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-03-24 Tested on: 11-03-24 in dry/wet condition



**Test Specification** 

( ASTM C39 )



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Footing Columns (Caps) Footing Columns	16	2	2024	6Diax12		13	28.28	46	3644		Engraved
2	Footing Columns (Caps)	16	2	2024	6Diax12		13	28.28	47	3723		Engraved
3					-		I			I		
4										I		
5						HEINE	RING			I		
6					}	READ IN	207			I		
7					-	OF THY	الله في خلق ر الله في خلق ر	<u> </u>		-		
8					887			la No		I		
9										I		
10						-LA	IOR L			I		
11										-		
12												
13												
14												
15												
16												
Witness	ed by: Nil											

witnessed by: Nii

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

6825 Dr. M. Yousaf

To: **Project Manager** 

AL HAMRA TOWN, M/s Premier Town Developers and Construction.

Project: Construction of 100,000 Gallons Over Head Water Tank at AL HAMRA TOWN LAHORE. (Over Head

Water Tank Shaft Level (40ft)).

Our Ref. No. CL/CED/ 4418 Dated: 11-03-24

Your Ref. No. ALHM/OHW/0305 Dated: 05-03-24 ( ASTM C39 )

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 06-03-24 Tested on: 11-03-24 in dry/wet condition



**Test Specification** 



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	3000Psi (1:2:4)	17	2	2024	6Diax12		13	28.28	35	2772		Non Engraved
2	3000Psi (1:2:4)	17	2	2024	6Diax12		13	28.28	28	2218		Non Engraved
3												
4						/						
5						THE	RING					
6					)	READ IN	200	<b></b> -				
7			1		1	OF THY	ر تیب اند کی خلق ر	<u></u>		I		
8								ASN.				
9						-						
10						(A	IORE.					
11			-							I		
12												
13										I		
14										I		
15												
16							1			I		
Witness	ed by: Nil				-							

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Mobile: 0307-0496895 Landline: 042-99029245 & 042-99029202

**ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

6829 Dr. M. Yousaf

To: Mr. Muhammad Sajjad **Project Incharge** 

Project: Construction of House No. 60, C Block Model Town, Lahore.

Our Ref. No. CL/CED/ 4419 Dated: 11-03-24 **Test Specification** 

Your Ref. No. Dated: Nil ( ASTM C39 )

#### COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 07-03-24 Tested on: 11-03-24 in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Raft, (3000 Psi)	29	2	2024	6Diax12		13	28.28	66	5228		Non Engraved
2	Raft, (3000 Psi)	29	2	2024	6Diax12		13	28.28	66	5228		Non Engraved
3	Raft, (3000 Psi)	29	2	2024	6Diax12		13	28.28	66	5228		Non Engraved
4												
5						THE	RING					
6			-		}	READ IN	207			-		
7					3	OF THY  RORD WHO  OREATES	ر تیب ان کی خلق ر	133				
8								AS .				
9						-						
10						LA	IORE.					
11			-							-		
12										-		
13										-		
14												
15							-					
16					_		-					
Witness	sed by: Nil				-							

Witnessea by: Nii

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACl318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

6836 Dr. M. Yousaf

To: Engr. Hassan Mahmmod

Resident Engineer, G3 Engineering Consultants (Pvt) Ltd.

Project: Construction of DHA Newlife Residency Appartments at 273/1 Q Block Phase-II DHA, Lahore.

(Contractor: M/s Ghousia Engineering & Construction Pvt. Ltd. Lahore)

Our Ref. No. CL/CED/ 4420 Dated: 11-03-24 <u>Test Specification</u>

Your Ref. No. G3/DHA-NLD/RE/219 Dated: 04-03-24 (ASTM C39)

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 08-03-24 Tested on: 11-03-24 in dry/wet condition





Sr. No.	Sr. No. Mark*		Casting Date*		Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	Block-A&B (4000 Psi)	6	2	2024	6Diax12		14	28.28	68	5386		Engraved
2	Block-A&B (4000 Psi)	6	2	2024	6Diax12		13	28.28	59	4673		Engraved
3	Block-A&B (4000 Psi)	6	2	2024	6Diax12		14	28.28	65	5149		Engraved
4												
5						THE	RING					
6						READ IN	2071					
7					1	OF THY LORD WHO CREATES	ر تاب ان کی خلق ر	133		I	I	
8					887			<b>5</b>		I	I	
9								<u> </u>			-	
10						LA	IORE.					
11												
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

6787 Dr. M. Yousaf

To: Mr. M. Usman Rauf

Resident Engineer, Highways and Transportation Engineering Division. NESPAK (Pvt) Ltd.

Project: Repair and Maintenance of Different Roads / Streets in the jurisdiction of MCL. (MCL Projects)

Our Ref. No. CL/CED/ 4421 Dated: 11-03-24 <u>Test Specification</u>

Your Ref. No. 4084/103/MUR/104/1277 Dated: 16-02-24

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 28-02-24 Tested on: 11-03-24 in dry/wet condition



(BS 3921\*\*)



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	мм	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	RH				8.9 x 4.3 x 3.1	3900	3450	38.27	64	3746	13.04	
2	RH				8.9 x 4.3 x 3	3840	3435	38.27	58	3395	11.79	
3	RH				8.8 x 4.4 x 3.2	3940	3545	38.72	54	3124	11.14	
4	RH				8.8 x 4.3 x 3.2	3895	3515	37.84	50	2960	10.81	
5	RH				9 x 4.3 x 3.2	3940	3565	38.7	53	3068	10.52	
6	RH				8.8 x 4.4 x 3	3900	3550	38.72	58	3355	9.86	
7					3	OF THY	ر تجب الدي خلق ر	E				
8								<b>3</b>				
9						-						
10						LA	ORE					
11										I		
12												
13										I		
14										-		
15										-	-	
16										-	-	
Witness	sed by:											

#### Witnessed by:

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

6805 Dr. M. Yousaf

To: Mr. M. Usman Rauf

Resident Engineer, Highways and Transportation Engineering Division. NESPAK (Pvt) Ltd.

Project: Repair and Improvement of Roads and Streets Islamia Park Chah Jamu Walla Sodiwal and Union

Park (Samanabad Zone). (MCL Projects)

Our Ref. No. CL/CED/ 4422

Dated: 11-03-24

15-02-24

Dated:

**Test Specification** (BS 3921\*\*)

Your Ref. No. 4084/103/MUR/104/1779

#### COMPRESSION TEST REPORT

#### Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 04-03-24 Tested on: 11-03-24 in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	ММ	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	1000				8.9 x 4.4 x 3	3680	3290	39.16	44	2517	11.85	
2	1000				9 x 4.4 x 3	3755	3345	39.6	44	2489	12.26	
3	1000				9 x 4.4 x 3	3800	3365	39.6	43	2432	12.93	
4	1000				9 x 4.4 x 3	3745	3350	39.6	32	1810	11.79	
5	1000				8.9 x 4.4 x 2.9	3530	3135	39.16	36	2059	12.6	
6	1000				8.9 x 4.4 x 3	3685	3265	39.16	35	2002	12.86	
7					3	OF THY	ر تجب الدي خلق ر	- 13				
8								(B)				
9						1						
10						-1A	IORE.					
11												
12												
13												
14												
15							-				-	
16											-	
Witness	sed by:				_							

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 6841 Dr. M.Yousaf

To: Mr. M. Usman Rauf

Resident Engineer, Highways and Transportation Engineering Division. NESPAK (Pvt) Ltd.

Project: Restoration of Road Cut at Old F.C College Road, Katchi Abadi Haji Dera Restaurant Gol Chakar Main Market Allama Iqbal Road Near Garhi Shahu Police Station & Wasa Tube Well Makkah Colony, Gulberg Zone,

Our Ref. No. CL/CED/ 4423 Dated: 11-03-24 <u>Test Specification</u>

Your Ref. No. 4084/103/MUR/104/1270 Dated: 10-02-24 (BS 1881-116)

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 08-03-24 Tested on: 11-03-24 in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1		27	12	2023	6x6x6		8	36	98	6098		Non Engraved
2		27	12	2023	6x6x6		8.4	36	110	6844		Non Engraved
3		27	12	2023	6x6x6		8.4	36	103	6409		Non Engraved
4												
5		I	-			THE	RING			I		
6		1	-		}	READ IN				I		
7					-	OF THY	ر عِب ا الله في خلق ر	===				
8		I	-		887			<b>5</b>		I		
9		I	-							I		
10		I	-			LA	ORL			I		
11		-								-		
12												
13												
14												
15												
16												

Witnessed by: Nil

Results can also be seen on website <a href="https://civil.uet.edu.pk/concrete-laboratory-reports1/">https://civil.uet.edu.pk/concrete-laboratory-reports1/</a>

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 ORIGINAL

A carbon copy for the report has been retained in the lab for record.

> 6839 Dr. M.Yousaf

To: AREW Fabrication & Construction Pvt. Ltd.

Kahna Nau, Lahore.

Project: Solar Project, NOVA Tex. SKP.

Our Ref. No. CL/CED/ 4424 Dated: 11-03-24

Your Ref. No. Nil Dated: 08-03-24 (BS 1881-116)

## **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 08-03-24 Tested on: 11-03-24 in dry/wet condition



**Test Specification** 



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	мм	YYYY	(in)	(Kg/ gms)	(Kg/ gms)		(Imp.Tons)		on (%)	
1		27	2	2024	6x6x6		7.8	36	73	4542		Non Engraved
2												
3												
4						/						
5						THE	RING					
6					)	READ IN	200	<b>X</b>				
7					3	OF THY  RORD WHO  OREATES	ر تجب الدي خلق ر	E				
8								<b>3</b>				
9						-						
10						LA	ORE					
11										I		
12										I		
13										I		
14										I		
15												
16										-		
Witness	sed by: Nil											

Witnessed by: Nil

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACl318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

> 6839 Dr. M.Yousaf

To: AREW Fabrication & Construction Pvt. Ltd.

Kahna Nau, Lahore.

Project: Solar Project, NOVA Tex. SKP.

Our Ref. No. CL/CED/ 4425 Dated: 11-03-24

Your Ref. No. Dated: 08-03-24 (BS 1881-116)

## COMPRESSION TEST REPORT

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 08-03-24 Tested on: 11-03-24 in dry/wet condition



**Test Specification** 



Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti	Remarks
		DD	мм	YYYY	(in)	(Kg/ gms)	(Kg/ gms)		(Imp.Tons)		on (%)	
1		26	2	2024	6x6x6		8.2	36	52	3236		Non Engraved
2												
3												
4						/						
5						THE	RING					
6					)	READ IN	200	<b></b>				
7					3	OF THY  RORD WHO  OREATES	ر تیب ان کی خلق ر	- 13				
8								AS I				
9						-						
10						(A	IORE.					
11												
12							-					
13												
14												
15												
16												
Witness	sed by: Nil											

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACl318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.



University of Engineering and Technology, Lahore. Pakistan Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895 **ORIGINAL** 

A carbon copy for the report has been retained in the lab for record.

> 6833 Dr. M.Yousaf

To: **Sub Divisional Officer** 

**Building Sub Division Nankana Sahib.** 

Project: Construction / Rehabilitation / Improvement of Offices, ARCS E-Registration Centers, Sub-Registrar

Offices etc in Punjab ARC Center One at Nanakana Sahib.

Our Ref. No. CL/CED/ 4426 Dated: 11-03-24 **Test Specification** 

Your Ref. No. 205/SDO/BSD/NNS Dated: 15-02-24 (BS 1881-116)

#### **COMPRESSION TEST REPORT**

Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 07-03-24 Tested on: 11-03-24 in dry/wet condition





Sr. No.	Mark*	Cas	ting	Date*	Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Absorpti	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)	on (%)	
1	RCC Columns (1:1.5:3)	16	1	2024	6x6x6		8	36	103	6409		Non Engraved
2	RCC Columns (1:1.5:3)	16	1	2024	6x6x6		8	36	87	5413		Non Engraved
3												
4												
5						THE	RING					
6					}	READ IN	207					
7					17	OF THY LEGRO WHO CREATES	ر بجب ان فی خلق ر	E				
8												
9						-						
10						(A	IORE.					
11												
12												
13												
14												
15												
16												
Witness	ed by: Nil											

Witnessea by: Nii

Results can also be seen on website https://civil.uet.edu.pk/concrete-laboratory-reports1/

- 1. \* as engraved on the specimens (if any)
- 2. \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- 3. \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- 4. \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as comprerssive strength

- 1. The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- 2. The test results are recommended to be interpreted in the light of above factors by the engineer.