



# Plain and Reinforced Concrete Laboratory

## Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan  
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL**

A carbon copy for the report has been retained in the lab for record.

9072  
Dr. Aqsa

To: Mr. Asad Shiekh  
CEO, SAR Construction Company

Project: Construction of Al-Ghani Garden Phase-7.

Our Ref. No. CL/CED/ 7653-1 of 2

Dated: 11/03/2025

Test Specification

Your Ref. No. SAR/AI-Ghani Garden Phase-7/03/25

Dated: 10/03/2025

( ---- )

## COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 10/03/2025 Tested on: 11/03/2025 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorption (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	Rectangular, Grey, 60mm	---	---	---	7.8x3.8x2.4	---	2815	29.64	66	4988	---	---
2	Rectangular, Grey, 60mm	---	---	---	7.8x3.8x2.4	---	2705	29.64	56	4232	---	---
3	Rectangular, Grey, 60mm	---	---	---	7.8x3.8x2.4	---	2790	29.64	56	4232	---	---
4	---	---	---	---	---	---	---	---	---	---	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---
6	---	---	---	---	---	---	---	---	---	---	---	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by: Nil

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports1/>

- \* as engraved on the specimens (if any)
- \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

**Note:** Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory



# Plain and Reinforced Concrete Laboratory

## Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan  
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL**

A carbon copy for the report has been retained in the lab for record.

9072

Dr. Aqsa

To: Mr. Asad Shiekh  
CEO, SAR Construction Company

Project: Construction of Al-Ghani Garden Phase-7.

Our Ref. No. CL/CED/ 7653-2 of 2

Dated: 11/03/2025

Test Specification

Your Ref. No. SAR/Al-Ghani Garden Phase-7/03/25

Dated: 10/03/2025

( ---- )

## COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 10/03/2025 Tested on: 11/03/2025 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorption (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	Kerb Stone	---	---	---	6x6x6	---	7.6	36	27	1680	---	Cut Cube
2	Kerb Stone	---	---	---	6x6x6	---	7.6	36	26	1618	---	Cut Cube
3	Kerb Stone	---	---	---	6x6x6	---	8	36	26	1618	---	Cut Cube
4	---	---	---	---	---	---	---	---	---	---	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---
6	---	---	---	---	---	---	---	---	---	---	---	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by: Nil

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports1/>

- \* as engraved on the specimens (if any)
- \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- \*\*\*\* ACI318-08 requires mean of two sample (6"x12" cylinder) strength at 28 days as compressive strength

**Note:** Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory



# Plain and Reinforced Concrete Laboratory

## Civil Engineering Department

University of Engineering and Technology, Lahore, Pakistan  
Landline: 042-99029245 & 042-99029202 Mobile: 0307-0496895

**ORIGINAL**

A carbon copy for the report has been retained in the lab for record.

9079

Dr. Aqsa

To: Mr. Ghulam Abbas  
CEO, Eagle Construction Company

Project: Metro Cash & Carry Store Ravi Road, Lahore.

Our Ref. No. CL/CED/ 7654

Dated: 11/03/2025

Test Specification

Your Ref. No. Nil

Dated: Nil

( ---- )

## COMPRESSION TEST REPORT



Concrete Cubes/Concrete Cylinders/Bricks/Cores/Tuff Tiles/Pavers

Specimens received on: 10/03/2025 Tested on: 11/03/2025 in dry/wet condition

Sr. No.	Mark*	Casting Date*			Size	Wet Weight	Dry Weight	Area of X-Section	Ultimate load	Ultimate Stress	Water Absorpti on (%)	Remarks
		DD	MM	YYYY	(in)	(Kg/ gms)	(Kg/ gms)	(Sq. in)	(Imp.Tons)	(psi)		
1	Rectangular, Grey, 60mm	---	---	---	7.8x3.8x2.4	---	2815	29.64	86	6499	---	---
2	Rectangular, Grey, 60mm	---	---	---	7.8x3.8x2.4	---	2695	29.64	61	4610	---	---
3	Rectangular, Grey, 60mm	---	---	---	7.8x3.8x2.4	---	2935	29.64	88	6650	---	---
4	Rectangular, Grey, 60mm	---	---	---	7.8x3.8x2.4	---	2680	29.64	76	5744	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---
6	---	---	---	---	---	---	---	---	---	---	---	---
7	---	---	---	---	---	---	---	---	---	---	---	---
8	---	---	---	---	---	---	---	---	---	---	---	---
9	---	---	---	---	---	---	---	---	---	---	---	---
10	---	---	---	---	---	---	---	---	---	---	---	---
11	---	---	---	---	---	---	---	---	---	---	---	---
12	---	---	---	---	---	---	---	---	---	---	---	---
13	---	---	---	---	---	---	---	---	---	---	---	---
14	---	---	---	---	---	---	---	---	---	---	---	---
15	---	---	---	---	---	---	---	---	---	---	---	---
16	---	---	---	---	---	---	---	---	---	---	---	---

Witnessed by: Nil

Results can also be seen on website <https://civil.uet.edu.pk/concrete-laboratory-reports1/>

- \* as engraved on the specimens (if any)
- \*\* BS3921 requires average of ten clay brick samples for crushing strength and water absorption
- \*\*\* BS5328 requires mean of two cube sample strength at 28 days as characteristic strength
- \*\*\*\* ACI318-08 requires mean of two sample (6"diax12" cylinder) strength at 28 days as compressive strength

**Note:** Above results pertain to the unsealed samples supplied to the laboratory

- The laboratory is not responsible for sampling, originality and construction conditions (such as mix proportion, w/c ratio, compaction, curing and quality of ingredients)
- The test results are recommended to be interpreted in the light of above factors by the engineer.

Supervisor (Lab)

Director/Dy. Director Concrete Laboratory