

Test Performed By: Dr Asad Ali Gillani

Hafiz Saeed Ur Rehman
Resident Engineer
NESPAK Lahore.
(Remodeling And Upgradation Of Nullah & Walton Road Pkg-I)

Client Reference: 4702/13/HSR/09/137

SOM Laboratory Reference: CED/SOM/1350(Page-1/1)

Test: Compression Test

Sample Type: Cat Eyes, Aluminium Stud

Dated: 29-04-2025

Dated: 05-06-2025

Test Results

Sr. No.	Sample Type	Top Dimensions (mm)	Bottom Dimensions (mm)	Thickness (mm)	Inclination (Degree)	Compression Load (Kg)
1	Cat Eyes, Swareflex (White)	82.3 x 60.7	99.3 x 99.5	17.8	38.62°	23721
2	Cat Eyes 3M (Yellow)	74.4 x 44.6	101.4 x 88.9	15.6	31.55°	8012
3	Aluminium Stud (CBD)	104.9 x 62.4	153 x 100.8	37.6	59.42	50224

Note: Please always confirm the results of above report on web: www.uet-civil.edu.pk

Parks & Horticulture Authority Gujranwala.(Renovation Of Gulshan-E-Iqbal Park PHA Gujranwala)

Parks & Horticulture Authority Gujranwala.(Renovation Of Gulshan-E-Iqbal Park PHA Gujranwala)

Ref: 1351(Page-1/1)

Dated: 05-06-2025

Test Specification: ASTM-A-615

Sample Type: Deformed Bar

[illegible]

BEND TEST:

# 6	Sample bend through 180 degrees Satisfactorily without any crack	Note:- Only Six Samples Received and Tested
# 4	Sample bend through 180 degrees Satisfactorily without any crack	

Note: Please always confirm the results of above report on web www.uet-civil.edu.pk