

Transportation Engineering Laboratory (TEL)

Department of Civil Engineering (CED)

UNIVERSITY OF ENGINEERING & TECHNOLOGY (UET)

LAHORE – 54890 (PAKISTAN)



Phone: 092-42-9929202 Cable: UNIVENGTECH Fax: 092-42-9922566

Ref:-----

Date:-----

Engr. Inzamam-ul-Haq
Site Engineer,
SMA Sikander Contractors.

Subject: **Testing of Aggregates**
Monument Site, Suki Kinari, Naran

Dear Sir,

It is with reference to your letter No. Nil dated 05-08-2024.

Please find below the results for the test conducted on the aggregate samples provided to this laboratory on 08-08-2024 through your representative.

Sample # 1

Sieve Analysis (ASTM C-136)

Sieve Size	½"	¾"	#4	#8	#16	#30	#50	#100	#200
%age Passing	100	100	99.11	97.79	93.07	79.50	45.62	9.39	1.57

Sample # 2

Sieve Analysis (ASTM C-136)

Sieve Size	1 ½"	1"	¾"	½"	¾"	#4
%age Passing	100	97.89	36.86	0.50	0	0

Sample # 3

Sieve Analysis (ASTM C-136)

Sieve Size	3"	2 ½"	2"	1 ½"	1"	¾"	½"	¾"	#4
%age Passing	100	94.90	34.11	0	0	0	0	0	0

If you have further query, please do not hesitate to contact the undersigned.

Best Regards,

Director
Transportation Engineering Laboratory

Note:

1. This test report is based solely on the particular sample(s) supplied by the client and should not be reproduced in parts.
2. Sampling has not been performed by Transportation Engineering Laboratory (TEL), UET and TEL-UET does not accept the responsibility that the sample(s) supplied is/are truly representative sample(s) of any batch or stock or entire project.
3. While TEL-UET agrees to take every reasonable precaution to ensure validity of its test results, it assumes no liability thereof beyond the amount of the fee charged for the analysis or test.
4. The party shall assume full responsibility for the ethical use of the results in the test reports and the TEL-UET shall be held free from any and all claims which may result from the use of such data by client or others.
5. This test report shall not be reproduced wholly or in parts unless negotiated.