

Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To, M/.S Global Dairy Tech Lahore

Reference # CED/TFL <u>37250 (Dr. M Rizwan Riaz)</u>

Reference of the request letter # Nil

Dated: 25-10-2021

Tension Test Report (Page -1/1)

Date of Test 26-10-2021 Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size (inch)		Area (in²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal	Actual	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)	₩ E	R
1	0.374	3/8	0.374	0.11	0.110	3500	4600	70200	70100	92200	92200	1.10	13.8	
-		-	-	-	-	-	-	-	-	-	-	-		
-		-	-	-	-	-	-	-	-	-	-	-		
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
			N	ote: on	ly one s	sample fo	r tensile	and one	sample fo	or bend t	est			
	Bend Test													

3/8" Dia Bar Bend Test Through 180° is Satisfactory

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples

LAHOSE .

STRUCTURAL ENGINEERING DIVISION

Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To,
Resident Engineer
Construction Supervision Consultants (CSC)
CAREC – Regional Improving Border Services (RIBS) Project

Reference # CED/TFL <u>37251 (Dr. M Rizwan Riaz)</u> Dated: 25-10-2021 Reference of the request letter # 5065059/CAREC-RIBS/CHAMAN/RE-364Dated: 20-10-2021

Tension Test Report (Page -1/2)

Date of Test 26-10-2021 Gauge length 640 mm

Description Steel Strand Tensile Test as per ASTM A-416-94a

Sr. No.	Nominal Diameter	Nominal Weight	Measured weight	Yield st clause	_	Breaking strength clause (6.2)		Young's Modulus of Elasticity "E"	% Elongation	Remarks / Coil No.
	(mm)	(kg/km)	(kg/km)	(kg)	(kN)	(kg) (kN)		GPa	%	Rema
1	12.70 (1/2")	775.0	787.0	17100	167.75	19500	191.30	199	>3.50	xx
-	-	-	-	1	-	-	-	-	1	ı
-	-	-	•	ı	-	-	-	-	ı	ı
-	-	-	•	ı	-	-	-	-	ı	ı
-	-	-	-	-	-	-	-	-	1	-
-	-	-	-	-	-	-	-	-	-	-

Only one sample for Test

Note:

- 1. Modulus of Elasticity is based on nominal steel area of the steel strand vide clause 13.3 of ASTM A416a
- 2. Load versus percentage strain graphs are attached

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples

NERRO (SERVICE SERVICE SERVICE


STRUCTURAL ENGINEERING DIVISION

Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To,
Resident Engineer
Construction Supervision Consultants (CSC)
CAREC – Regional Improving Border Services (RIBS) Project

Reference # CED/TFL <u>37251 (Dr. M Rizwan Riaz)</u> Dated: 25-10-2021 Reference of the request letter # 5065059/CAREC-RIBS/CHAMAN/RE-364Dated: 20-10-2021

Graph (Page -2/2)



I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To,

Project Manager

CM Engineering (Pvt) Ltd

Project Enfra Share Rollout Site ID: USKSK08, USKSK10, S-7442, S-7441, S-7443, S-7449, S-

7448, S-7457

S-7438

Reference # CED/TFL 37252 (Dr. M Rizwan Riaz)

Dated: 25-10-2021

Reference of the request letter # CME/Steel/Enfra Share Rollout/1000

Dated: 24-10-2021

Tension Test Report (Page -1/1)

Date of Test 26-10-2021 Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size (mm)		Area (in²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
S	(lbs/ft)	Nominal	Actual	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)	₩ E	Re
1	0.374	10	9.51	0.12	0.110	3200	5100	58789	64110	93696	102200	1.30	16.3	
2	0.373	10	9.49	0.12	0.110	3200	5100	58789	64360	93696	102600	1.20	15.0	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	ı	1	-	-	-	-	-	ı	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
10.	Dia	Dan Dan	. J T t	Theresse	1. 1000:	s Satisfac	Bend T	est						

10mm Dia Bar Bend Test Through 180° is Satisfactory

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



Test Floor Laboratory Department of Civil Engineering University of Engineering and Technology Lahore, 54890 Pakistan. Ph: 92-42-99029202

To, Sub Divisional Officer Highway Sub Division, DG Khan

(Construction of Metalled Road from Yaroo to Naow abad Length: 12.00 km District DG Khan

(Phase-I from km no. 8.80 to 8.90 km = 0.10 km (Part-B)

Reference # CED/TFL <u>37253 (Dr. M Rizwan Riaz)</u>

Reference of the request letter # 2371

Dated: 25-10-2021

Dated: 27-08-2021

Tension Test Report (Page -1/1)

Date of Test 26-10-2021 Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Aı (iı	rea 1 ²)	Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)	% E	R
1	0.378	3	0.376	0.11	0.111	3400	5000	68200	67510	100200	99300	1.10	13.8	
2	0.376	3	0.375	0.11	0.111	3400	5000	68200	67780	100200	99700	1.30	16.3	
3	4.314	10	1.271	1.27	1.268	41600	56600	72200	72310	98300	98400	1.60	20.0	
4	4.294	10	1.268	1.27	1.262	40600	55600	70500	70900	96500	97100	1.80	22.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
	Note: only four samples for tensile and two samples for bend test													
	Bend Test													

#3 Bar Bend Test Through 180° is Satisfactory

#10 Bar Bend Test Through 180° is Satisfactory

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

I/C Testing Laboratoires UET Lahore, Pakistan.

- 1- You can See your reports On Internet in the following web site http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2. The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples