



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

Ref: CED/TFL/06/5280
2024

Dated: 27-06-

Dated of Test: 04-07-2024

To

Resident Engineer
NESPAK
Repair and Maintenance / Rehabilitation of PCC Faisal Sweets Street and
Links Nabi Pura Badami Bagh, Ravi Zone Lahore.

Subject: **TESTING OF R.C.C. PIPE [ASTM-C76 - 08a]** (Page # 1/1)

Reference to your letter No. 4084/103/MUR/104/1842, dated 21.05.2024

on the subject cited above. One R.C.C. Pipe as received by us has been tested. The results are tabulated as under.

Sr. No	Nominal Size	Total Length	Loaded Length	External Diameter	Internal Diameter	Wall Thickness	Proof load	Ultimate Load	Proof Stress	Ultimate Stress
	(inch)	(foot)	(foot)	(inch)	(inch)	(inch)	(kg)	(kg)	Pound/Linear foot/foot	Pound/Linear foot/foot
1	12	7.79	7.32	15.94	11.82	2.06	11500	15200	3519	4651

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Project Manager,
HIGH-Q
Construction of HIGH-Q Mall at 3-A, Gulberg II, Lahore.

Reference # CED/TFL **5288** (Dr. Safeer Abbas)
Reference of the request letter # QC/HQ/CIVIL/219

Dated: 01-07-2024
Dated: 01-07-2024

Tension Test Report (Page -1/1)

Date of Test 04-07-2024
Gauge length 8 inches
Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size (mm)		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal	Actual	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.402	10	9.85	0.12	0.118	3700	5300	67975	69030	97370	98900	1.20	15.0	
2	0.407	10	9.91	0.12	0.120	3900	5300	71650	71930	97370	97800	1.00	12.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
10mm Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratories
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Engineer's Repres Resident
NESPAK – TurkPak jv
Construction of Green Building for EMC, EPD and Allied New Entities Established
Under PGDP (DLI-2, PGDP) Lahore.

Reference # CED/TFL **5289** (Dr. Safeer Abbass)
Reference of the request letter # 4731/MAA/03/51

Dated: 01-07-2024
Dated: 01-07-2024

Tension Test Report (Page -1/1)

Date of Test 04-07-2024
Gauge length 8 inches
Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.372	3	0.373	0.11	0.109	3100	4800	62200	62470	96200	96800	1.10	13.8	Markhor
2	0.373	3	0.374	0.11	0.110	3100	4800	62200	62350	96200	96600	1.20	15.0	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Resident Engineer
 NESPAK – TurkPak jv
 Reconstruction of Lady Willingdon Hospital, Lahore.

Reference # CED/TFL **5291** (Dr. Safeer Abbass)
 Reference of the request letter # 4720/13/MA/04/40

Dated: 02-07-2024
 Dated: 25-06-2024

Tension Test Report (Page -1/1)

Date of Test 04-07-2024
 Gauge length 8 inches
 Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.372	3	0.373	0.11	0.109	3900	4600	78200	78540	92200	92700	0.80	10.0	AF Steel
2	0.373	3	0.374	0.11	0.110	3900	4500	78200	78340	90200	90400	0.80	10.0	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- The above results pertain to sample /samples supplied to this laboratory.
- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Senior Manager Construction
BPS (Private) Limited.
Beaconhouse School System
Wapda Town Lahore

Reference # CED/TFL **5292** (Dr. Safeer Abbass)
Reference of the request letter # Nil

Dated: 02-07-2024
Dated: 01-07-2024

Tension Test Report (Page -1/1)

Date of Test 04-07-2024
Gauge length 8 inches
Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.364	3	0.369	0.11	0.107	3200	4700	64200	65910	94200	96800	1.20	15.0	
2	0.369	3	0.372	0.11	0.109	3100	4700	62200	62940	94200	95500	1.10	13.8	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

Ref: CED/TFL/07/5293

Dated: 02-07-2024

Dated of Test: 04-07-2024

To

Resident Engineer
Engineering Consulting Services Punjab (Pvt) Limited.
Program for Strategic Transformation / Revamping of Allama Iqbal Teaching
Hospital, Sialkot

Subject: **TESTING OF R.C.C. PIPE [ASTM-C76 - 08a] (Page # 1/1)**

Reference to your letter No. ECSP/RE/199/06, dated 20.05.2024 on the subject cited above. Two R.C.C. Pipes as received by us have been tested. The results are tabulated as under.

Sr. No	Nominal Size	Total Length	Loaded Length	External Diameter	Internal Diameter	Wall Thickness	Proof load	Ultimate Load	Proof Stress	Ultimate Stress
	(inch)	(foot)	(foot)	(inch)	(inch)	(inch)	(kg)	(kg)	Pound/Linear foot/foot	Pound/Linear foot/foot
1	12	7.80	7.36	16.14	11.97	2.09	12000	17000	3604	5106
2	18	7.76	7.30	23.11	17.70	2.71	9000	12000	1844	2458

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

Ref: CED/TFL/07/5294

Dated: 02-07-2024

Dated of Test: 04-07-2024

To

Resident Engineer
MMP - NESPAK - ACE
PCP (Package-II)
Addition of Manholes and Supply of Dewatering Sites in Kamoke City.

Subject: **TESTING OF R.C.C. PIPE [ASTM-C76 - 08a]** (Page # 1/1)

Reference to your letter No. PCP/P-2/RE/IS/601, dated 25.06.2024 on the subject cited above. One R.C.C. Pipe as received by us has been tested. The results are tabulated as under.

Sr. No	Nominal Size	Total Length	Loaded Length	External Diameter	Internal Diameter	Wall Thickness	Proof load	Ultimate Load	Proof Stress	Ultimate Stress
	(inch)	(foot)	(foot)	(inch)	(inch)	(inch)	(kg)	(kg)	Pound/Linear foot/foot	Pound/Linear foot/foot
1	18	7.76	7.30	23.15	17.64	2.76	9500	13000	1953	2673

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Chief QS
Maconsult
Revamping of Services Hospital Lahore

Reference # CED/TFL **5295** (Dr. Safeer Abbass)
Reference of the request letter # Revamping/Services/Camp/64

Dated: 02-07-2024
Dated: 02-07-2024

Tension Test Report (Page -1/1)

Date of Test 04-07-2024
Gauge length 8 inches
Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.375	3	0.375	0.11	0.110	3500	4800	70200	70030	96200	96100	1.40	17.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only one sample for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Senior Manager Construction
Educational Services(Pvt) Ltd.
Beaconhouse School System
Sargodha Cantt Campus

Reference # CED/TFL **5298** (Dr. Safeer Abbass)
Reference of the request letter # Nil

Dated: 03-07-2024
Dated: 02-07-2024

Tension Test Report (Page -1/1)

Date of Test 04-07-2024
Gauge length 8 inches
Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.379	3	0.377	0.11	0.112	3400	4900	68200	67190	98200	96900	1.00	12.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only one sample for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Sr. Engineer, Civil, KCP (W&S)
Pakistan Atomic Energy Commission
Jauharabad
“Construction of Laundry with CSSD Buildings at PGHJ.”

Reference # CED/TFL **5299** (Dr. Safeer Abbas)

Dated: 03-07-2024

Reference of the request letter # KCP(W&S)-Hops-(CLB)/2023

Dated: 02-07-2024

Tension Test Report (Page -1/1)

Date of Test 04-07-2024

Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.371	3	0.373	0.11	0.109	3900	5100	78200	78820	102200	103100	0.80	10.0	
2	0.363	3	0.369	0.11	0.107	3500	4800	70200	72290	96200	99200	1.10	13.8	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

Ref: CED/TFL/07/5300

Dated: 03-07-2024

Dated of Test: 04-07-2024

To

Resident Engineer
Master Consulting Engineers (Pvt) Ltd.
"Up-Gradation of D.H.Q Hospital Hafizabad (Group No. 4)

Subject: **TESTING OF R.C.C. PIPE [ASTM-C76 - 08a]** (Page # 1/1)

Reference to your letter No. MCE/DHQfzd/24/132, dated 08.05.2024 on the subject cited above. Two R.C.C. Pipes as received by us have been tested. The results are tabulated as under.

Sr. No	Nominal Size	Total Length	Loaded Length	External Diameter	Internal Diameter	Wall Thickness	Proof load	Ultimate Load	Proof Stress	Ultimate Stress
	(inch)	(foot)	(foot)	(inch)	(inch)	(inch)	(kg)	(kg)	Pound/Linear foot/foot	Pound/Linear foot/foot
1	12	7.76	7.30	15.94	11.98	1.98	12500	16800	3783	5084
2	15	7.83	7.34	19.61	14.97	2.32	9500	13800	2289	3325

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Executive Engineer
Highways Division
Narowal

(Widening / Improvement of Road from Sialkot Cantt to Jassar Garrison Length = 69.00 km, in District Narowal.”

Reference # CED/TFL **5301** (Dr. Safeer Abbas)

Dated: 03-07-2024

Reference of the request letter # 1050/DB

Dated: 10-06-2024

Tension Test Report (Page -1/1)

Date of Test 04-07-2024

Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.377	3	0.375	0.11	0.111	2900	4400	58200	57730	88200	87600	1.60	20.0	
2	0.390	3	0.382	0.11	0.115	3200	4700	64200	61460	94200	90300	1.40	17.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Project Manager
Atlas Power Ltd.
Sheikhupura

Reference # CED/TFL **5302** (Dr. Safeer Abbass)
Reference of the request letter # Nil

Dated: 03-07-2024
Dated: 02-07-2024

Tension Test Report (Page -1/1)

Date of Test 04-07-2024
Gauge length 8 inches
Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.378	3	0.376	0.11	0.111	3700	4700	74200	73440	94200	93300	1.10	13.8	
2	0.377	3	0.376	0.11	0.111	3700	4700	74200	73560	94200	93500	0.90	11.3	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile test														
Bend Test														

I/C Testing Laboratories
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

M/S Altec International
Lahore

Reference # CED/TFL **5303** (Dr. Safeer Abbas)
Reference of the request letter # Nil

Dated: 04-07-2024
Dated: 02-07-2024

Tension Test Report (Page – 1/1)

Date of Test 04-07-2024
Description Steel Wire Rope Tensile Test

Sr. No.	Nominal Diameter	Measured weight	Breaking Load	Remarks / Coil No.
	(mm)	(kg/m)	(kg)	
1	8.3	0.25	3900	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
Only one sample for Test				

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Manager Planning and Developers
Noon Developers & Marketing
Canal Heights 3-B, Block B, Noon Avenue, New Muslim Town, Lahore.

Reference # CED/TFL **5305** (Dr. Asad Ali)
Reference of the request letter # CH/ST/01/24

Dated: 04-07-2024
Dated: 04-07-2024

Tension Test Report (Page -1/1)

Date of Test 04-07-2024
Gauge length 8 inches
Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.370	3	0.372	0.11	0.109	4430	5200	88800	89720	104200	105400	1.00	12.5	
2	0.369	3	0.372	0.11	0.109	4200	5050	84200	85290	101200	102600	1.00	12.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratories
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples