



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Material Engineer
 NESPAK – EPCM Consultants
 Punjab Intermediate Cities Improvement Investment Program (PICIP)
 Consultancy Services for Engineering, Procurement and Construction Management
 Wastewater Treatment Plant (WWTP) in North Zone Sahiwal

Reference # CED/TFL **5985** (Dr. M Kashif)

Dated: 12-11-2024

Reference of the request letter # 3976/11/MIA/SWL/WWTP/01/613

Dated: 11-11-2024

Tension Test Report (Page -1/2)

Date of Test 15-11-2024

Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.376	3	0.375	0.11	0.111	3500	5200	70200	69790	104200	103700	1.20	15.0	Ittefaq Steel
2	0.376	3	0.375	0.11	0.111	3700	5300	74200	73790	106200	105700	1.20	15.0	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Material Engineer
NESPAK – EPCM Consultants
Punjab Intermediate Cities Improvement Investment Program (PICIP)
Consultancy Services for Engineering, Procurement and Construction Management
Wastewater Treatment Plant (WWTP) in North Zone Sahiwal

Reference # CED/TFL **5985** (Dr. M Kashif)

Dated: 12-11-2024

Reference of the request letter # 3976/11/MIA/SWL/WWTP/01/615

Dated: 11-11-2024

Tension Test Report (Page -2/2)

Date of Test 15-11-2024

Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.376	3	0.375	0.11	0.111	3800	4900	76200	75770	98200	97800	0.80	10.0	Mughal Steel
2	0.375	3	0.374	0.11	0.110	3800	4800	76200	76090	96200	96200	0.90	11.3	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Resident Engineer
Development Consultancy Services (Pvt) Ltd
Development of University of Sahiwal at District Sahiwal
Construction of Academic Block, Admin Block, Mosque and External Development.

Reference # CED/TFL **5986** (Dr. M Kashif)

Dated: 12-11-2024

Reference of the request letter # DCS/RE/UOS/2024/1106

Dated: 06-11-2024

Tension Test Report (Page -1/1)

Date of Test 15-11-2024

Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight (lbs/ft)	Diameter/ Size		Area (in ²)		Yield load (kg)	Breaking Load (kg)	Yield Stress (psi)		Ultimate Stress (psi)		Elongation (inch)	% Elongation	Remarks
		Nominal (#)	Actual (inch)	Nominal	Actual			Nominal	Actual	Nominal	Actual			
1	0.364	3	0.369	0.11	0.107	4000	5000	80200	82360	100200	103000	0.80	10.0	
2	0.365	3	0.370	0.11	0.107	4200	5100	84200	86290	102200	104800	0.80	10.0	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratories
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Sub Divisional Officer
Buildings Sub Division
Chiniot.

(Programme for Revamping of 552 BHUs of North & Central Punjab (Phase 1) of District Chiniot ADP No. 364 for Year of 2024-25 District Chiniot.)

Reference # CED/TFL **5987** (Dr. M Kashif)

Dated: 13-11-2024

Reference of the request letter # 107/CT

Dated: 26-09-2024

Tension Test Report (Page -1/1)

Date of Test 15-11-2024

Gauge length 8 inches

Description Deformed Steel Bar Tensile Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.376	3	0.375	0.11	0.111	3300	5000	66200	65780	100200	99700	1.20	15.0	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only one sample for tensile test														
Bend Test														

I/C Testing Laboratories
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Project Manager
 Nine Arches
 132 E1 Gulberg 2.

Reference # CED/TFL **5988** (Dr. M Kashif)
 Reference of the request letter # Nil

Dated: 13-11-2024
 Dated: 13-11-2024

Tension Test Report (Page -1/1)

Date of Test 15-11-2024
 Gauge length 8 inches
 Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size (mm)		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal	Actual	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.367	3	0.371	0.11	0.108	3500	4800	70200	71460	96200	98000	1.10	13.8	
2	0.365	3	0.370	0.11	0.107	3200	4600	64200	65690	92200	94500	1.20	15.0	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

HQ 495 Engr Group
Frontier Works Organization (FWO)
Gulberg - III, Lahore.

Reference # CED/TFL **5991** (Dr. M Kashif)

Dated: 14-11-2024

Reference of the request letter # PC920/Testing/KamranSteel/Ord

Dated: 13-11-2024

Tension Test Report (Page -1/1)

Date of Test 15-11-2024

Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.357	3	0.366	0.11	0.105	3400	4700	68200	71380	94200	98700	1.20	15.0	Kamran Steel
2	0.361	3	0.367	0.11	0.106	3800	4900	76200	79010	98200	101900	0.80	10.0	
3	4.255	10	1.262	1.27	1.251	36600	52800	63600	64500	91700	93100	1.40	17.5	
4	4.265	10	1.263	1.27	1.254	38400	53600	66700	67520	93100	94300	1.40	17.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only four samples for tensile and two sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														
#10 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

QAQC Manager
Zameen Development
Zameen Neo

Construction of Zameen Neo at Plot # 13, Block-H, Gulberg III, Lahore.

Reference # CED/TFL **5994** (Dr. M Kashif)

Dated: 14-11-2024

Reference of the request letter # ZD/QAQC/NEO/08

Dated: 14-11-2024

Tension Test Report (Page -1/1)

Date of Test 15-11-2024

Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.371	3	0.373	0.11	0.109	3500	4900	70200	70700	98200	99000	1.20	15.0	
2	0.372	3	0.373	0.11	0.109	3600	5000	72200	72620	100200	100900	1.00	12.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Director P & D,
King Edward Medical University
Construction of Bio Safety Lab Level III KEMU, Lahore.

Reference # CED/TFL **5995** (Dr. M Kashif)
Reference of the request letter # P&D/KEMU 927-29

Dated: 14-11-2024
Dated: 14-11-2024

Tension Test Report (Page -1/1)

Date of Test 15-11-2024
Gauge length 8 inches
Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.371	3	0.372	0.11	0.109	3400	5100	68200	68780	102200	103200	1.00	12.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only one sample for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratories
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Project Engineer (Maintenance)
Defence Housing Authority, Gujranwala
“External Electrification Sys (UG) Sector 1A DHA Gwa.”

Reference # CED/TFL **5996** (Dr. M Kashif)

Dated: 14-11-2024

Reference of the request letter # 318/35/08/Maint/UG Elec 1A Extn

Dated: 12-11-2024

Tension Test Report (Page -1/1)

Date of Test 15-11-2024

Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size (mm)		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal	Actual	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.376	10	9.53	0.12	0.111	3500	4900	64301	69750	90021	97700	1.40	17.5	Sheikhoo Steel
2	0.374	10	9.51	0.12	0.110	3500	4900	64301	70100	90021	98200	1.40	17.5	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
10mm Dia Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratories
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,
 Manager Procurement
 Gharibwal Cement Limited.
 Lahore

Reference # CED/TFL **5999** (Dr. Safeer Abbas)
 Reference of the request letter # GCL/Purchase/UET/TEST/006

Dated: 15-11-2024
 Dated: 15-11-2024

Tension Test Report (Page -1/1)

Date of Test 15-11-2024
 Gauge length 8 inches
 Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size (mm)		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal	Actual	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	4.262	32	32.08	1.25	1.253	41200	54600	72664	72490	96297	96100	1.40	17.5	
2	4.251	32	32.04	1.25	1.250	42200	55200	74427	74430	97355	97400	1.50	18.8	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
32mm Dia Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratoires
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples



STRUCTURAL ENGINEERING DIVISION
Test Floor Laboratory
Department of Civil Engineering
University of Engineering and Technology Lahore, 54890
Pakistan. Ph: 92-42-99029202

To,

Dy Dir Infra
Defence Housing Authority, Gujranwala
“Construction of Bdy Wall (Selected Locations) – Sector E.”

Reference # CED/TFL **6002** (Dr. M Kashif)

Dated: 15-11-2024

Reference of the request letter # 111/DD/Lab/Tameer/53

Dated: 05-11-2024

Tension Test Report (Page -1/1)

Date of Test 15-11-2024

Gauge length 8 inches

Description Deformed Steel Bar Tensile and Bend Test as per ASTM-A615

Sr. No.	Weight	Diameter/ Size		Area (in ²)		Yield load	Breaking Load	Yield Stress (psi)		Ultimate Stress (psi)		Elongation	% Elongation	Remarks
	(lbs/ft)	Nominal (#)	Actual (inch)	Nominal	Actual	(kg)	(kg)	Nominal	Actual	Nominal	Actual	(inch)		
1	0.378	3	0.376	0.11	0.111	4000	5200	80200	79400	104200	103300	0.80	10.0	
2	0.379	3	0.376	0.11	0.111	4000	5100	80200	79220	102200	101000	0.80	10.0	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Note: only two samples for tensile and one sample for bend test														
Bend Test														
#3 Bar Bend Test Through 180° is Satisfactory														

I/C Testing Laboratories
UET Lahore, Pakistan.

Note:

- 1- You can See your reports On Internet in the following web site
http://www.uet.edu.pk/faculties/facultiesinfo/civil/index.html?RID=testing_reports
- 2- The above results pertain to sample /samples supplied to this laboratory.
- 3- Sealed sample / Unsealed sample / Marked sample/Signed Samples